# BULK DENSITY LIST

National BULK BAG

- ✓ Over 50 types of bulk bags in-stock
- ✓ Same-day shipping is available
- ✓ Contact us about your custom bag needs
- ✓ We can manufacture, warehouse, and ship as needed

| Material | Bulk Density lbs/ft³ | Bulk Density g/cc |
|---|---|---|
| Abrasive | 150 | 2.40 |
| Abrasive Compound | 148 | 2.37 |
| Abrasive Mix | 153 | 2.45 |
| Abrasive Wheel Mix | 150 | 2.40 |
| AC Teat Dust | 60 | 0.96 |
| Accelerator | 31 | 0.50 |
| Acetate | 35 | 0.56 |
| Acetate Flakes | 21 | 0.34 |
| Acrawax "C" | 32 | 0.51 |
| Acrawax | 15 | 0.24 |
| Acrawax & Carbon Black | 34 | 0.54 |
| Acrylic Fibers | 9 | 0.14 |
| Acrylic Concentrate Pellets (1/8") | 38 | 0.61 |
| Acrylic Pellets (1/8") | 38 | 0.61 |
| Acrylic Resin | 32 | 0.51 |
| Activated Aluminum | 15 | 0.24 |
| Activated Carbon | 20 | 0.32 |
| Adipic Acid | 40 | 0.64 |
| Aero-Cil | 8 | 0.13 |
| Alcanol | 39 | 0.62 |
| Alfalfa Seed | 45-48 | 0.72-0.77 |
| Alfalfa Meal, Dehydrated 13% | 16-18 | 0.26-0.29 |
| Alfalfa Meal, Dehydrated 17% | 18-22 | 0.29-0.35 |
| Alfalfa Meal, Suncured 13% | 14 | 0.22 |
| Alfalfa Leaf Meal | 14.5 | 0.23 |
| Alfalfa Stem Meal | 12 | 0.19 |
| Alfalfa Pellets 13% | 41-43 | 0.66-0.69 |
| Alfalfa Pellets 17% | 41-43 | 0.66-0.69 |
| Alfalfa Meal, fine ground | 15-22 | 0.24-0.35 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Alodine No. 41 | 92 | 1.47 |
| Alodine 12005 | 79 | 1.27 |
| Alum | 50 | 0.80 |
| Alum/Pigment Mix | 30 | 0.48 |
| Alumina | 40 | 0.64 |
| Alumina, Activated | 48 | 0.77 |
| Alumina, Alcan | 46 | 0.74 |
| Alumina, Calcined | 63 | 1.01 |
| Alumina, Corhart | 83 | 1.33 |
| Alumina, FAH-KDH | 45 | 0.72 |
| Alumina, Hydrate | 68 | 1.09 |
| Alumina, Kyanite | 77 | 1.23 |
| Alumina & Lime Mix | 65 | 1.04 |
| Alumina, Metal Grade | 67 | 1.07 |
| Alumina Powder | 18 | 0.29 |
| Alumina, Precipitator Dust | 54 | 0.86 |
| Alumina, Reacted | 65 | 1.04 |
| Alumina, Sandy | 60 | 0.96 |
| Alumina, Tabular Dust | 21 | 0.34 |
| Aluminum Benzoate | 11 | 0.18 |
| Aluminum Chlorhydrate | 55 | 0.88 |
| Aluminum Chloride | 51 | 0.82 |
| Aluminum Dross | 81 | 1.30 |
| Aluminum Etchant | 55 | 0.88 |
| Aluminum Filament 200X | 75 | 1.20 |
| Aluminum Flake | 150 | 2.40 |
| Aluminum Fluoride | 55 | 0.88 |
| Aluminum Magnesium Silicate | 21 | 0.34 |
| Aluminum Oxide | 80 | 1.28 |
| Aluminum Oxide, Calcined | 33 | 0.53 |
| Aluminum Powder | 44 | 0.70 |
| Aluminum Silicate | 33 | 0.53 |
| Aluminum Silicate (Catalyst) | 53 | 0.85 |
| Aluminum Sulfate | 65 | 1.04 |
| Aluminum Sulphate, Ground | 50 | 0.80 |
| Aluminum Trihydrate | 45 | 0.72 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Aluminum Wire, Chopped | 35 | 0.56 |
| Ammonium Bromide | 76 | 1.22 |
| Ammonium Chloride | 38 | 0.61 |
| Ammonium Nitrate | 49 | 0.78 |
| Ammonium Nitrate Prills | 38 | 0.61 |
| Ammonium Perchloride | 62 | 0.99 |
| Ammonium Phosphate | 55 | 0.88 |
| Ammonium Sulfate | 69 | 1.11 |
| Amorphous Silica | 11 | 0.18 |
| Anthracite, Powdered | 35 | 0.56 |
| Antimony Oxide | 44 | 0.70 |
| Antioxidant (Granules) | 41 | 0.66 |
| Antioxidant (Powder) | 28 | 0.45 |
| Apple Slices, Dried | 15 | 0.24 |
| Aquafloc | 10 | 0.16 |
| Aqua Nuchar | 10 | 0.16 |
| Arasan | 25 | 0.40 |
| Arizona Road Dust | 54 | 0.86 |
| Arsenic Trioxide | 41 | 0.66 |
| Asbestos | 22 | 0.35 |
| Asbestos Fiber (Long) | 16 | 0.26 |
| Asbestos Fiber (Short) | 19 | 0.30 |
| Asbestos Fiber | 20 | 0.32 |
| Asbestos Fiber 7R | 15 | 0.24 |
| Asbestos Powder | 28 | 0.45 |
| Asbestos Shorts | 26 | 0.42 |
| Ascorbic Acid (Coarse) | 45 | 0.72 |
| Ascorbic Acid (Fine) | 32 | 0.51 |
| Ash, ground | 105 | 1.68 |
| Ashes, dry loose | 38 | 0.61 |
| Ashes, wet loose | 47 | 0.75 |
| Atrazine (Herbicide) | 30 | 0.48 |
| Attapulgite | 40 | 0.64 |
| Attasorb | 18 | 0.29 |
| Atticote | 22 | 0.35 |
| Baking Powder | 56 | 0.90 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Barbasco Root | 33 | 0.53 |
| Barites | 120 | 1.92 |
| Barium Carbonate | 55 | 0.88 |
| Barium Oxide | 63 | 1.01 |
| Barium Stearate | 13 | 0.21 |
| Barium Sulphate | 60 | 0.96 |
| Barley (Whole) | 38-43 | 0.61-0.69 |
| Barley, Fine Ground | 46 | 0.74 |
| Barley, Ground | 24-26 | 0.38-0.42 |
| Barley, Malted | 30.5 | 0.49 |
| Barley Meal | 28 | 28 |
| Barley, Rolled | 21-24 | 21-24 |
| Barley, Scoured | 41 | 41 |
| Bauxite | 45 | 45 |
| Beans, (Soya) | 46.3 | 46.3 |
| Beans, White | 43-48 | 43-48 |
| Beet Pulp | 16-20 | 16-20 |
| Bentonite | 50 | 50 |
| Bentonite (Coarse) | 60 | 60 |
| Bicarbonate of Soda | 62 | 62 |
| Biscuit Pre-Mix | 60 | 60 |
| Binder Starch | 41 | 41 |
| Binder (T-Gel) | 31 | 31 |
| Binder 812 | 41 | 41 |
| Bisphenol | 37 | 37 |
| Bisphenol Flake | 60 | 60 |
| Black Coloring | 30 | 30 |
| Bleach Compound | 60 | 60 |
| Blood Meal | 38.5 | 38.5 |
| Blood Flour | 30 | 30 |
| Blue Dye | 40 | 40 |
| Blue Grass Seed | 11 | 11 |
| Blue Powder, Metal | 142 | 142 |
| Bone, Ground Dry | 75 | 75 |
| Bone Meal, Loose | 50-60 | 50-60 |
| Bone and Meat Meal, Loose | 45 | 45 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Borax | 60 | 0.96 |
| Borax (Granular) | 60 | 0.96 |
| Borax (Puffed) | 12 | 0.19 |
| Boric Acid | 54 | 0.86 |
| Brake Lining Compound | 30 | 0.48 |
| Bran | 35 | 0.56 |
| Brass Powder | 100 | 1.60 |
| Bread Chucks | 10 | 0.16 |
| Bread Crumbs | 6 | 0.10 |
| Brewers Grains, Dry | 15.5 | 0.25 |
| Bromo Seltzer | 38 | 0.61 |
| Bronze Powder | 78 | 1.25 |
| Broom Corn Seed | 41.8 | 0.67 |
| Brown Gravy Mix | 38 | 0.61 |
| Buckwheat (whole) | 37-41 | 0.59-0.66 |
| Buckwheat Bran | 15.5 | 0.25 |
| Buckwheat Flour | 41 | 0.66 |
| Buckwheat Hulls | 13 | 0.21 |
| Buckwheat Middlings | 22 | 0.35 |
| Buttermilk, Dried | 31 | 0.50 |
| Cab-O-Sil | 2 | 0.03 |
| Cake Mix | 44 | 0.70 |
| Calcium | 30 | 0.48 |
| Calcium Borate | 61 | 0.98 |
| Calcium Carbide, crushed | 80 | 1.28 |
| Calcium Carbonate | 44 | 0.70 |
| Calcium Chloride | 60 | 0.96 |
| Cal. Chloro Fluoro Phosphate | 53 | 0.85 |
| Calcium Fluoride | 102 | 1.63 |
| Calcium Hydroxide | 40 | 0.64 |
| Calcium Phosphate | 48 | 0.77 |
| Calcium Silicate | 10 | 0.16 |
| Calcium Stearate | 20 | 0.32 |
| Calcium Sulfate | 45 | 0.72 |
| Cane Seed | 41 | 0.66 |
| Car Rug Stock | 46 | 0.74 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Carbofrax (C-4) | 100 | 1.60 |
| Carbon, Activated | 17 | 0.27 |
| Carbon (Pelletized) | 42 | 0.67 |
| Carbon Black | 35 | 0.56 |
| Carbon Black Mix | 77 | 1.23 |
| Carbon Black & Graphite | 45 | 0.72 |
| Carbon Black (Beads) | 19 | 0.30 |
| Carbon Black (Nuchar) | 11 | 0.18 |
| Carbon Black (Pelletized) | 22 | 0.35 |
| Carbon Crystallized | 58 | 0.93 |
| Carbon Granules | 59 | 0.95 |
| Carbon Dust | 38 | 0.61 |
| Carbon-Teflon Mix | 32 | 0.51 |
| Carbon Flour | 57 | 0.91 |
| Carbon Lampblack | 8 | 0.13 |
| Carbon Masterbatch | 41 | 0.66 |
| Casein | 36 | 0.58 |
| Casting Mix | 150 | 2.40 |
| Catalyst, Bead | 50 | 0.80 |
| Catalyst, Synthetic | 39 | 0.62 |
| Catalyst, Zeolitic | 45 | 0.72 |
| Caustic Potash, Bead | 65 | 1.04 |
| Caustic Soda | 31 | 0.50 |
| Celaflock | 11 | 0.18 |
| Celaton FP4 | 14 | 0.22 |
| Celcon Flake | 23 | 0.37 |
| Celcon Pellets | 50 | 0.80 |
| Celite | 10 | 0.16 |
| Celite 535 | 10 | 0.16 |
| Cellflo | 12 | 0.19 |
| Cellulose Acetate | 10 | 0.16 |
| Cellulose Denvative | 45 | 0.72 |
| Cellulose Floc | 22 | 0.35 |
| Cellulose Gum | 27 | 0.43 |
| Cement | 85 | 1.36 |
| Cement Dust | 50 | 0.80 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Cement (Portland) | 94 | 1.51 |
| Cement (Portland) Clinker | 95 | 1.52 |
| Cement (Root Canal) | 67 | 1.07 |
| Cement (C-10 Sealing) | 56 | 0.90 |
| Ceramic Compound | 85 | 1.36 |
| Ceramitalc | 54 | 0.86 |
| Cereal (Amerikor A-52) | 12 | 0.19 |
| Cereal Mix | 43 | 0.69 |
| Cenum Oxide | 62 | 0.99 |
| Charcoal (Powder) | 24 | 0.38 |
| Chemco Burnishing Compound | 35 | 0.56 |
| Chickory | 34 | 0.54 |
| Chickory (Powder) | 30 | 0.48 |
| Chili Spice | 45 | 0.72 |
| Chlorine Compound | 28 | 0.45 |
| Chlorine (Powder) | 36 | 0.58 |
| Chocolate Drink Mix | 26 | 0.42 |
| Chopped TFE Cones | 46 | 0.74 |
| Chopped Hose (Cheerios) | 50 | 0.80 |
| Chromic Acid Powder | 100 | 1.60 |
| Cinders, Blast Furnace | 57 | 0.91 |
| Cinders, Coal, Ashes & Clinker | 40 | 0.64 |
| Cinnamon Powder | 35 | 0.56 |
| Citric Acid | 48 | 0.77 |
| Citrus Pulp, Dry | 20.5 | 0.33 |
| Clay | 50 | 0.80 |
| Clay (Bentonite) | 50 | 0.80 |
| Clay (Calcined) | 30 | 0.48 |
| Clay (Fine) | 62 | 0.99 |
| Clay (Fines) | 70 | 1.12 |
| Clay (Georgia) | 65 | 1.04 |
| Clay (Granite) | 32 | 0.51 |
| Clay (Helium) | 36 | 0.58 |
| Clay (Kaolin) | 48 | 0.77 |
| Clay P2 | 48 | 0.77 |
| Clay & Petro Ag | 55 | 0.88 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density | |
|---|---|---|
| | lbs/ft³ | g/cc |
| Clay product | 33 | 0.53 |
| Clay (Pure) | 60 | 0.96 |
| Clay (Super White) | 30 | 0.48 |
| Clay (Talc) | 52 | 0.83 |
| Clay-Talc-Flint | 62 | 0.99 |
| Clearon Powder | 40 | 0.64 |
| Clinker Dust | 94 | 1.51 |
| Clover Seed | 48 | 0.77 |
| CMC Powder | 52 | 0.83 |
| Coagulant | 36 | 0.58 |
| Coal Anthracity | 55-60 | 0.88-0.96 |
| Coal (Granules) | 52 | 0.83 |
| Coal (Pulverized) | 38 | 0.61 |
| Coal Bituminous | 52 | 0.83 |
| Coal Dust | 35 | 0.56 |
| Coal Powder | 40 | 0.64 |
| Coal (Powder MRD) | 41 | 0.66 |
| Coal (Powdered SRC) | 39 | 0.62 |
| Coaltrol M | 42 | 0.67 |
| Cobalt Carbonate | 60 | 0.96 |
| Cobalt Fines | 256 | 4.10 |
| Cobalt Oxide, 10% Moisture | 114 | 1.83 |
| Cobalt Sulfate | 48 | 0.77 |
| Cocoa | 35 | 0.56 |
| Cocoa Flavoring | 55 | 0.88 |
| Cocoa Shells | 30 | 0.48 |
| Coconut Chips | 38 | 0.61 |
| Coffee, Green (Beans) | 37-39 | 0.59-0.62 |
| Coffee, Roasted (Beans) | 22-24 | 0.35-0.38 |
| Coffee (Flavoring) | 28 | 0.45 |
| Coffee (Instant) | 19 | 0.30 |
| Coke, Average Lump | 28-32 | 0.45-0.51 |
| Coke, Breeze | 30-34 | 0.48-0.54 |
| Coke (Granules) | 52 | 0.83 |
| Coke, Petroleum Lump | 40-50 | 0.64-0.80 |
| Coke, Calcined (Fines) | 59 | 0.95 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Coke, Calcined (Coarse) | 56 | 0.90 |
| Coke, Calcined (Intermediate) | 59 | 0.95 |
| Coke Dust | 15 | 0.24 |
| Coke Fines | 39 | 0.62 |
| Coke, Petroleum CRS 393 | 48 | 0.77 |
| Coke, Pulverized | 45 | 0.72 |
| Colemanite | 57 | 0.91 |
| Colloidal Lime | 49 | 0.78 |
| Collupulin | 19 | 0.30 |
| Cookie Meal | 38 | 0.61 |
| Copolymer Beads | 41 | 0.66 |
| Copolymer Flake | 23 | 0.37 |
| Copper (Fines) | 101 | 1.62 |
| Copper, Flotation | 35 | 0.56 |
| Copper Hydroxide | 25 | 0.40 |
| Copper Pellets (1/32") | 240 | 3.84 |
| Copper Sulfate | 52 | 0.83 |
| Copper Phosphorous Pellets | 265 | 4.24 |
| Copra Meal, Loose | 27 | 0.43 |
| Cork, Solid | 15 | 0.24 |
| Cork, In Bales | 8-9 | 0.13-0.14 |
| Cork, Ground | 4-5 | 0.06-0.08 |
| Corn, (Whole Shelled) | 45 | 0.72 |
| Corn Bran | 13 | 0.21 |
| Corn, Cracked (Coarse) | 40 | 0.64 |
| Corn, Chops (Fine) | 36-39 | 0.58-0.62 |
| Corn, Chops (Medium) | 38-42 | 0.61-0.67 |
| Corn, Chops (Coarse) | 40-44 | 0.64-0.70 |
| Corn, Cobs | 17 | 0.27 |
| Corn Distillers Dried Grains | 18.5 | 0.30 |
| Corn Distillers Dried Solubles | 25.5 | 0.41 |
| Corn, Ear | 56 | 0.90 |
| Corn Flour | 51 | 0.82 |
| Corn Germ Meal | 35 | 0.56 |
| Corn Gluten Feed | 26-33 | 0.40-0.53 |
| Corn Gluten Meal | 32-43 | 0.51-0.69 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Corn Grits | 40-43 | 0.64-0.69 |
| Corn, Ground | 34-36 | 0.54-0.58 |
| Corn, Hominy Feed | 25-28 | 0.40-0.45 |
| Corn, Kibbled | 20-22 | 0.32-0.35 |
| Corn Mash | 45 | 0.72 |
| Corn Meal | 40 | 0.64 |
| Corn Oil Meal | 33-36 | 0.53-0.58 |
| Corn Starch | 42 | 0.67 |
| Corn Sugar | 20.5 | 0.33 |
| Cottonseed w/Lint | 18-25 | 0.29-0.40 |
| Cottonseed Cake | 40-45 | 0.64-0.72 |
| Cottonseed Delinted | 25-35 | 0.40-0.56 |
| Cottonseed Flour | 56 | 0.90 |
| Cottonseed Hulls | 12 | 0.19 |
| Cottonseed Meats | 40 | 0.64 |
| Cow Peas | 45 | 0.72 |
| Cryolite | 86 | 1.38 |
| Crystal Flo | 67 | 1.07 |
| Cullet, Glass Average | 85-100 | 1.36-1.60 |
| Cullet, Glass .75" x 0' | 80-90 | 1.28-1.44 |
| Cupric Oxide | 110 | 1.76 |
| Dacron Flakes | 32 | 0.51 |
| Dairy Flavoring | 38 | 0.61 |
| Delsan | 27 | 0.43 |
| Detergent (Flake) | 32 | 0.51 |
| Detergent (Powder) | 38 | 0.61 |
| Davis 888 Black | 38 | 0.61 |
| Deflourinated Phosphate | 97 | 1.55 |
| Dental Plaster | 42 | 0.67 |
| Dextrose | 36 | 0.58 |
| Diammonium Phosphate | 50 | 0.80 |
| Diatomaceous Earth | 16 | 0.26 |
| Diatomaceous Earth (Calcined) | 10 | 0.16 |
| Diatomaceous Earth (Celite) | 15 | 0.24 |
| Diatomaceous Earth (Dicalite) | 11 | 0.18 |
| Diatomaceous Earth (Fibra-Flo) | 15 | 0.24 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density | |
|---|---|---|
| | lbs/ft³ | g/cc |
| Diatomaceous Earth (Filtrol) | 14 | 0.22 |
| Diatomaceous Earth (Microcel) | 9-12 | 0.14-0.19 |
| Diatomaceous Earth (Perlite) | 5 | 0.08 |
| Diatomaceous Earth (Supercel) | 10 | 0.16 |
| Diatomaceous Earth Product | 14 | 0.22 |
| Diatomite | 14 | 0.22 |
| Dicalite | 12 | 0.19 |
| Dielectric Compound | 45 | 0.72 |
| Distillers Grains | 18 | 0.29 |
| Dog Food Blend | 54 | 0.86 |
| Dog Food Mixture | 36 | 0.58 |
| Dolomite | 54 | 0.86 |
| Dolomite Lime | 46 | 0.74 |
| Donut Mix | 40 | 0.64 |
| Dough Mix | 37 | 0.59 |
| Drug Additive | 56 | 0.90 |
| Dry Mix | 41 | 0.66 |
| Duramite (Calcium Carb.) | 58 | 0.93 |
| Dye (Fabric) | 25 | 0.40 |
| Dye (Food) | 40 | 0.64 |
| Earth, Common Loam (Dried) | 73 | 1.17 |
| Earth, Common Loam (Moist) | 76 | 1.22 |
| Eggs (Powdered) | 22 | 0.35 |
| Egg Yoke Powder | 23 | 0.37 |
| Electrolyte | 60 | 0.96 |
| Epoxy Molding, Preblend | 50 | 0.80 |
| Epoxy Powder | 49 | 0.78 |
| Explosive Compound | 36 | 0.58 |
| Extrude Regrind | 39 | 0.62 |
| Fab | 20 | 0.32 |
| Fanna | 45 | 0.72 |
| Feldspar | 62 | 0.99 |
| Fermate | 15 | 0.24 |
| Ferric Chloride | 43 | 0.69 |
| Ferric Sulfate | 61 | 0.98 |
| Ferro Silicate | 78 | 1.25 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Ferro Silicon | 87 | 1.39 |
| Ferrous Carbonate | 85-90 | 1.36-1.44 |
| Fertilizer | 37 | 0.59 |
| Fiberglass | 22 | 0.35 |
| Fiberglass (1/8" Chop) | 20 | 0.32 |
| Fiberglass (1/4" Chop) | 18 | 0.29 |
| Fiberglass (1/2" Chop) | 17 | 0.27 |
| Fiberglass Pellet Blend | 22 | 0.35 |
| Fiberglass Powder Blend | 30 | 0.48 |
| Filter Cake (Centifuge) | 40 | 0.64 |
| Filter-Cel | 9 | 0.14 |
| Filtrol | 30 | 0.48 |
| Filtrol Clay Grade 105 | 50 | 0.80 |
| Fine Powder | 127 | 2.03 |
| Fire Soot | 64 | 1.03 |
| Fireclay | 72 | 1.15 |
| Firemate | 24 | 0.38 |
| Fish Meal | 30-47 | 0.48-0.75 |
| Flame Retardant | 38 | 0.61 |
| Flaxseed | 43.5 | 0.70 |
| Flint | 97 | 1.55 |
| Floc | 13 | 0.21 |
| Floc (Solka) | 9 | 0.14 |
| Flour | 48 | 0.77 |
| Flour (Barley) | 38 | 0.61 |
| Flour (Barley Malt) | 45 | 0.72 |
| Flour (Corn) | 39 | 0.62 |
| Flour (Rye) | 42 | 0.67 |
| Flour (Soy) | 44 | 0.70 |
| Flour (Soya) | 40 | 0.64 |
| Flour (Wheat) | 42 | 0.67 |
| Flue Dust | 54 | 0.86 |
| Fluorspar | 100-125 | 1.60-2.00 |
| Fluorelent Powder | 35 | 0.56 |
| Fluorescent Powder | 68 | 1.09 |
| Fluorescent Powder (Moist) | 84 | 1.35 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Fluoride Compound | 42 | 0.67 |
| Fluorite | 78 | 1.25 |
| Flux | 145 | 2.32 |
| Flux Fines | 100 | 1.60 |
| Fly Ash | 65 | 1.04 |
| Foods Coloring | 39 | 0.62 |
| Foundry Additive Mixture | 80 | 1.28 |
| Foundry premix | 40 | 0.64 |
| Frodex 24 | 38 | 0.61 |
| Frosting Mix | 38 | 0.61 |
| Fuel Additives | 30 | 0.48 |
| Fuel Treatment | 40 | 0.64 |
| Fullers Earth | 35 | 0.56 |
| Fullers Earth Rods | 43 | 0.69 |
| Fumaric Acid | 40 | 0.64 |
| Fungicide | 26 | 0.42 |
| Garlic (Flakes) | 22 | 0.35 |
| Garlic (Powder) | 20 | 0.32 |
| Gelatin | 45 | 0.72 |
| Geon Resin | 22 | 0.35 |
| Gilsonite Fines | 49 | 0.78 |
| Glass (Frit) | 144 | 2.31 |
| Glass (Ground) | 103 | 1.65 |
| Glass (Powder) | 103 | 1.65 |
| Glass Batch Material | 90-110 | 1.44-1.76 |
| Glass Batch Mix | 87 | 1.39 |
| Glass Beads | 100 | 1.60 |
| Glass Microspheres | 62 | 0.99 |
| Glitter Flakes | 32 | 0.51 |
| Glycerine Green Catalyst | 42 | 0.67 |
| Glue | 53 | 0.85 |
| Gold Powder | 53 | 0.85 |
| Goulac | 30 | 0.48 |
| Graham Cracker Crust | 15 | 0.24 |
| Grain | 36 | 0.58 |
| Granite, Crushed | 97 | 1.55 |
| Granodine 663 | 68 | 1.09 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Granular Material | 48 | 0.77 |
| Granulated Polyurethane | 22 | 0.35 |
| Graphite | 48 | 0.77 |
| Graphite (Flakes) | 42 | 0.67 |
| Graphite (Granules) | 68 | 1.09 |
| Graphite (Powder) | 35 | 0.56 |
| Graphite (Pulverized) | 22 | 0.35 |
| Graphite (Scrap) | 59 | 0.95 |
| Glass Fiber | 8 | 0.13 |
| Gravel | 110 | 1.76 |
| Green Powder | 57 | 0.91 |
| Grinding Compound | 99 | 1.59 |
| Ground Bone | 50 | 0.80 |
| Grout | 70 | 1.12 |
| Gum Base | 42 | 0.67 |
| Gum Granules | 36 | 0.58 |
| Gum Resin | 32 | 0.51 |
| Gypsum | 54 | 0.86 |
| Gypsum (Calcined) | 55 | 0.88 |
| Gypsum (Ground) | 42 | 0.67 |
| Gypsum Stucco | 50 | 0.80 |
| Halon | 22 | 0.35 |
| Hampseed | 35.3 | 0.56 |
| Hash Spice | 66 | 1.06 |
| Hell Blue Dye | 19 | 0.30 |
| Hexahicel | 32 | 0.51 |
| Hexa-Melamine | 33 | 0.53 |
| Hexamine | 42 | 0.67 |
| Hexa-Silene | 30 | 0.48 |
| Hisil | 11 | 0.18 |
| Hydraflake | 36 | 0.58 |
| Hydrocarbon Compound | 36 | 0.58 |
| Hydrocide | 90 | 1.44 |
| Hyvar X (Herbicide) | 25 | 0.40 |
| Ice, Crushed | 35-45 | 0.56-0.72 |
| Ilmenite | 35 | 0.56 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Inhibitor Compound | 44 | 0.70 |
| Insecticide | 30 | 0.48 |
| Iodized Mixture | 18 | 0.29 |
| Ional | 49 | 0.78 |
| Irganox | 17 | 0.27 |
| Iron Chromite | 114 | 1.83 |
| Iron Filings | 180 | 2.88 |
| Iron Ore | 162 | 2.59 |
| Iron Oxide | 80 | 1.28 |
| Iron Oxide (Black) | 161 | 2.58 |
| Iron Oxide (Red) | 69 | 1.11 |
| Iron Powder | 175 | 2.80 |
| Iron Sulfate | 80 | 1.28 |
| Isophthalic Acid | 46 | 0.74 |
| Kafir and Milo (Grain Sorghum) | 40-46 | 0.64-.074 |
| Kaolin | 49 | 0.78 |
| Kaolin Clay | 50 | 0.80 |
| Karaya Gum | 45 | 0.72 |
| Ken-L-Biskit | 30 | 0.48 |
| Ken-L-Meal | 33 | 0.53 |
| Kiln Feed Mix | 73 | 1.17 |
| Kix Mixture | 48 | 0.77 |
| Kohinor | 49 | 0.78 |
| Kralex Powder | 42 | 0.67 |
| Lamisay Flour | 34 | 0.54 |
| Lampblack | 44 | 0.70 |
| Latex Powder | 89 | 1.43 |
| Latikia | 35 | 0.56 |
| Lead Arsenate | 90 | 1.44 |
| Lead Carbonate | 81 | 1.30 |
| Lead Chloride Crystals | 72 | 1.15 |
| Lead Oxide | 63 | 1.01 |
| Lead Stabilizer | 43 | 0.69 |
| Licorice Powder | 28 | 0.45 |
| Ligno Sulfinate | 30 | 0.48 |
| Lignone | 36 | 0.58 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Lignosol | 24 | 0.38 |
| Lime | 35 | 0.56 |
| Lime (Colloidal) | 42 | 0.67 |
| Lime (Dolomitic) | 42 | 0.67 |
| Lime (Granular) | 80 | 1.28 |
| Lime (Hydrated) | 40 | 0.64 |
| Lime (Quick) | 55 | 0.88 |
| Lime (Pebble) | 45 | 0.72 |
| Lime (Pulverized Quick) | 60 | 0.96 |
| Lime, Rock Dust | 82 | 1.31 |
| Limestone | 60 | 0.96 |
| Limestone (Ground) | 59 | 0.95 |
| Limestone (Pulverized) | 68 | 1.09 |
| Limestone Dust | 69 | 1.11 |
| Limestone Filler | 63 | 1.01 |
| Limestone Flour | 69 | 1.11 |
| Linseed Meal | 23-28 | 0.37-0.45 |
| Litharge | 182 | 2.92 |
| Magnesia | 78 | 1.25 |
| Magnesite | 27 | 0.43 |
| Magnesite Light | 40 | 0.64 |
| Magnesium Carbonate | 12 | 0.19 |
| Magnesium Chloride | 12 | 0.19 |
| Magnesium Chips | 60 | 0.96 |
| Magnesium Oxide | 65 | 1.04 |
| Magnesium Silicate | 58 | 0.93 |
| Magnesium Stearate | 21 | 0.34 |
| Magnesium Sulfate | 52 | 0.83 |
| Magnesium Hydroxide | 39 | 0.62 |
| Magnetite | 165 | 2.64 |
| Malt Powder | 41 | 0.66 |
| Malt Sprouts | 13-16 | 0.21-0.26 |
| Malted Barley Flour | 40 | 0.64 |
| Malted Wheat Flour | 41 | 0.66 |
| Maltrin Maltodestrin | 48 | 0.77 |
| Manganese Dioxide | 70 | 1.12 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Manganese Ore | 110 | 1.76 |
| Mannitol | 38 | 0.61 |
| Manzate | 35 | 0.56 |
| Marasperse | 25 | 0.40 |
| Marble (Granular) | 80 | 1.28 |
| Marble (Ground) | 93 | 1.49 |
| Meat Meal | 37 | 0.59 |
| Meat Tenderizer | 35 | 0.56 |
| Melamine | 45 | 0.72 |
| Melamine Powder | 32 | 0.51 |
| Metallic Flakes | 35 | 0.56 |
| Metallic Powder | 165 | 2.64 |
| Metasol | 38 | 0.61 |
| Metallic Baghouse Dust | 70 | 1.12 |
| Methocel | 26 | 0.42 |
| Mica (Flakes) | 10 | 0.16 |
| Mica (Powder) | 41 | 0.66 |
| Mica Soapstone | 47 | 0.75 |
| Microcel | 28 | 0.45 |
| Milk (Non-Fat Dry) | 35 | 0.56 |
| Milk (Powdered) | 13 | 0.21 |
| Milk (Powdered Whole) | 35 | 0.56 |
| Milk (Whole) | 32 | 0.51 |
| Milltown | 35 | 0.56 |
| Millet | 40 | 0.64 |
| Milo, Ground | 32-36 | 0.51-0.58 |
| Mineral Oxide | 35 | 0.56 |
| Mineral Core Dust | 15 | 0.24 |
| Mira-Flo | 10 | 0.16 |
| Molasses Feed | 20-25 | 0.32-0.40 |
| Mold Inhibitor | 40 | 0.64 |
| Molding Compound | 42 | 0.67 |
| Molding Powder | 42 | 0.67 |
| Molding Sand | 75 | 1.20 |
| Monosodium Phosphate | 55 | 0.88 |
| Molybdenum Disulfide | 44 | 0.70 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Molybdenum Oxide | 98 | 1.57 |
| Molybdic Oxide | 16 | 0.26 |
| Mushroom Particles (Dry) | 51 | 0.82 |
| Mustard Compound | 21 | 0.34 |
| Mustard Powdered | 16 | 0.26 |
| Mustard Spice A | 50 | 0.80 |
| Mustard Spice B | 45 | 0.72 |
| Multiclone Dust | 75 | 1.20 |
| Myverol | 40 | 0.64 |
| Naphthalene Flakes | 36 | 0.58 |
| Natrosol | 28 | 0.45 |
| Neutral Granules | 24 | 0.38 |
| News Print & Sawdust | 2 | 0.03 |
| Nickel | 60 | 0.96 |
| Nickel Ore Dust | 60 | 0.96 |
| Nickel Oxide | 28 | 0.45 |
| Nickel Powder | 75 | 1.20 |
| Nitrate of Soda | 85 | 1.36 |
| Nitro-Carbo-Nitrate | 66 | 1.06 |
| Nodule Dust, Coke | 53 | 0.85 |
| Nopco Feed Supplement | 40 | 0.64 |
| NVX | 26 | 0.42 |
| Nuchar | 12 | 0.19 |
| Nuts (Almonds) | 29 | 0.46 |
| Nuts (Cashews) | 31 | 0.50 |
| Nuts (Peanuts) | 33 | 0.53 |
| Nylon Fibers | 10 | 0.16 |
| Nylon Flakes | 32 | 0.51 |
| Nylon pellets (1/8") | 35 | 0.56 |
| Nylon Powder | 39 | 0.62 |
| Oats | 27 | 0.43 |
| Oat Flour | 33 | 0.53 |
| Oats (Ground) | 29 | 0.46 |
| Oats Groats (Whole) | 46.5 | 0.74 |
| Oats, Hulls | 8 | 0.13 |
| Oat Middlings | 38 | 0.61 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Oats (Rolled) | 19-24 | 0.30-0.38 |
| Onions (Chopped) | 14 | 0.22 |
| Onions (Minced) | 8 | 0.13 |
| Onions (Powdered) | 25 | 0.40 |
| Opalon PVC | 30 | 0.48 |
| Opalon Pellets (1/4") | 33 | 0.53 |
| Opti White Pigment | 47 | 0.75 |
| Orzan | 29 | 0.46 |
| Orlon, Polymer, Powder | 30 | 0.48 |
| Oxpyridmidine | 23 | 0.37 |
| Oxalic Acid | 52 | 0.83 |
| Oxychloride | 36 | 0.58 |
| Oyster Shell, (Ground, -0.5") | 53 | 0.85 |
| Paint Float 600 | 40 | 0.64 |
| Paper Dust | 5 | 0.08 |
| Paper Sequins | 15 | 0.24 |
| Paraformaldehyde | 40 | 0.64 |
| Parsley Flakes | 3 | 0.05 |
| Parzate | 19 | 0.30 |
| Paste Resin | 31 | 0.50 |
| Peanut Brittle | 36 | 0.58 |
| Peanut Meal | 28 | 0.45 |
| Peanuts (Unshelled) | 17-24 | 0.27-0.38 |
| Peanuts (Shelled) | 43 | 0.69 |
| Peat Moss | 10 | 0.16 |
| Penford Gum Starch | 38 | 0.61 |
| Penicillin Compound | 22 | 0.35 |
| Pentaerythritol | 44 | 0.70 |
| Pentarythritol | 50 | 0.80 |
| Peppermint | 32 | 0.51 |
| Peppermint Powder | 34 | 0.54 |
| Peppers (Chopped) | 21 | 0.34 |
| Peppers (Whole) | 16 | 0.26 |
| Perlite | 15 | 0.24 |
| Perlite Filter Aid | 8 | 0.13 |
| Perlite Ore | 65 | 1.04 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Petro-Ag (Granular) | 43 | 0.69 |
| Petro-Ag (Powder) | 40 | 0.64 |
| Petroleum Coke | 55 | 0.88 |
| Petroeum Coke Dust | 25 | 0.40 |
| Pharmaceutical Mix | 31 | 0.50 |
| Pharmaceutical Lubricant | 9 | 0.14 |
| Phenobac | 30 | 0.48 |
| Phenofil | 30 | 0.48 |
| Phenol Formaldehyde | 30 | 0.48 |
| Phenolic Powder | 32 | 0.51 |
| Phosphate | 80 | 1.28 |
| Phosphate Rock Crushed | 69 | 1.11 |
| Phosphate Rock Dust | 90 | 1.44 |
| Phosphate Rock Ground | 70 | 1.12 |
| Phosphate Tri-Calcium | 68 | 1.09 |
| Phosphate Rock Powder | 90 | 1.44 |
| Phosphorous Penta Sulfide | 75 | 1.20 |
| Phosphorous Pentoxide | 40 | 0.64 |
| Phthalic Anhydride | 52 | 0.83 |
| Pie Crust Mix | 35 | 0.56 |
| Pigment | 9 | 0.14 |
| Pitch | 37 | 0.59 |
| Plaster of Paris | 49 | 0.78 |
| Plastic (Beads) | 46 | 0.74 |
| Plastic (Chopped j") | 38 | 0.61 |
| Plastic (Cubes) | 38 | 0.61 |
| Plastic (Flakes) Large | 19 | 0.30 |
| Plastic (Flakes) Small | 34 | 0.54 |
| Plastic (Flakes) | 48 | 0.77 |
| Plastic (Flakes) 3/8" | 48 | 0.77 |
| Plastic (Pellets) | 45 | 0.72 |
| Plastic material Coloring | 35 | 0.56 |
| Plastic Spheres (1/16") | 43 | 0.69 |
| Plastic Powder | 42 | 0.67 |
| Plastic Powder (A) | 41 | 0.66 |
| Plastic Powder (B) | 26 | 0.42 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Plastic Resin | 40 | 0.64 |
| Plastic Scrap 7/8" Flakes | 40 | 0.64 |
| Polycarbonate Resin | 44 | 0.70 |
| Polyester Adhesive Powder | 30 | 0.48 |
| Polyester Cubes | 47 | 0.75 |
| Polyester Film Fragments | 6 | 0.10 |
| Polyester Flakes | 27 | 0.43 |
| Polyester Resin | 34 | 0.54 |
| Polyethylene | 43 | 0.69 |
| Polyethylene Beads | 42 | 0.67 |
| Polyethylene Film | 8 | 0.13 |
| Polyethylene Flakes | 6 | 0.10 |
| Polyethylene Granular | 30 | 0.48 |
| Polyethylene Pellets (1/8") | 36 | 0.58 |
| Polyethylene Pellets | 35 | 0.56 |
| Polyethylene Powder | 35 | 0.56 |
| Polyhedral Alcohol | 37 | 0.59 |
| Polymer | 20 | 0.32 |
| Polymer Reagent | 39 | 0.62 |
| Polymer Resin | 38 | 0.61 |
| Polymide Resin | 31 | 0.50 |
| Polyolefin Pellets (3/32") | 21 | 0.34 |
| Polypropylene | 30 | 0.48 |
| Polypropylene Flakes | 22 | 0.35 |
| Polypropylene Pellets (1/8") | 32 | 0.51 |
| Polypropylene Powder | 33 | 0.53 |
| Polystyrene Beads (1/16") | 40 | 0.64 |
| Polystyrene Pellets | 40 | 0.64 |
| Polystyrene Pellets (1/8") | 38 | 0.61 |
| Polystyrene Powder | 33 | 0.53 |
| Polystyrene Scrap | 31 | 0.50 |
| Polyurethane Pellets (1/8") | 45 | 0.72 |
| Polyvinyl Acetate | 39 | 0.62 |
| Polyvinyl Alcohol | 39 | 0.62 |
| Polyvinyl Chloride | 41 | 0.66 |
| Polyvinyl Chloride (Pellets 1/8") | 39 | 0.62 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Polyvinyl Chloride (Regrind) | 18 | 0.29 |
| Pork Spice | 72 | 1.15 |
| Potassium Bromide (5% Moist.) | 114 | 1.83 |
| Potassium Carbonate (Potash) | 74 | 1.19 |
| Potassium Chloride | 60 | 0.96 |
| Potassium Iodate | 129 | 2.07 |
| Potassium Muriate | 68 | 1.09 |
| Potassium Sulfate | 90 | 1.44 |
| Potatoes (Flakes) | 13 | 0.21 |
| Potatoes (Powdered) | 48 | 0.77 |
| Potting Soil | 16 | 0.26 |
| Poultry Meal | 34-39 | 0.54-0.62 |
| Powdered Sugar | 35 | 0.56 |
| Pre-Mix | 35 | 0.56 |
| Precipitator Dust | 46 | 0.74 |
| Propellant (Solid Dry) | 48 | 0.77 |
| Protein Supplement | 34 | 0.54 |
| Prussian Blue | 36 | 0.58 |
| Protein Blend | 44 | 0.70 |
| Pumice Powder | 39 | 0.62 |
| Purezaust Pellets | 50 | 0.80 |
| PVC Chips | 54 | 0.86 |
| PVC Resin | 32 | 0.51 |
| Pynte Cinders | 124 | 1.99 |
| Q-Cel | 12 | 0.19 |
| Quartz, 0.5" Screenings | 80-90 | 1.28-1.44 |
| Quartz, 1.5 - 3" Lumps | 85-95 | 1.36-1.52 |
| Rag (Chopped) | 8 | 0.13 |
| Raisins (Moist) | 38 | 0.61 |
| Rapeseed | 48.3 | 0.77 |
| Records (Ground Plastics) | 41 | 0.66 |
| Red Color Concentrate | 32 | 0.51 |
| Red Lead | 165 | 2.64 |
| Red Oxide Pigment | 72 | 1.15 |
| Refractory Mix | 96 | 1.54 |
| Resin, Synthetic H.D. | 34 | 0.54 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Resin-Luron | 40 | 0.64 |
| Resimene | 35 | 0.56 |
| Resin Binder | 35 | 0.56 |
| Resinous Polymer | 22 | 0.35 |
| Rice & Vitamin Mix | 48 | 0.77 |
| Rice, Cream & W/Vitamins | 48 | 0.77 |
| Rice | 45 | 0.72 |
| Rice Bran | 26 | 0.42 |
| Rice (Puffed) | 6 | 0.10 |
| Rock Salt | 68 | 1.09 |
| Rolaids (Mix Powder) | 65 | 1.04 |
| Rouge Compound | 58 | 0.93 |
| Rubber Composition Powder | 34 | 0.54 |
| Rubber Compound | 38 | 0.61 |
| Rubber Crumb | 22 | 0.35 |
| Rubber Foam (Chopped) | 3 | 0.05 |
| Rubber (Granules) | 28 | 0.45 |
| Rubber Pellets (Irregular) | 29 | 0.46 |
| Rubber Powder | 33 | 0.53 |
| Rutile & Coke | 91 | 1.46 |
| Rye Bran | 15-20 | 0.24-0.32 |
| Rye Feed | 33 | 0.53 |
| Rye, Malted | 32 | 0.51 |
| Rye, Middlings | 42 | 0.67 |
| Rye Shorts | 33.5 | 0.54 |
| Rye, Whole | 43-45 | 0.69-0.72 |
| Sage Leaves | 18 | 0.29 |
| Salt, Fine Table | 86 | 1.38 |
| Salt, Clay | 38 | 0.61 |
| Salt, Granulated | 80 | 1.28 |
| Salt (Flake) | 42 | 0.67 |
| Salt (Flour) | 64 | 1.03 |
| Salt and Myverol | 54 | 0.86 |
| Sand | 99 | 1.59 |
| Sand (Dry) | 110 | 1.76 |
| Sand (Fine) | 125 | 2.00 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Sand (Moist) | 130 | 2.08 |
| Sand (Molding) | 78 | 1.25 |
| Sand, Foundry | 100 | 1.60 |
| Sand, Foundry, Coarse | 96 | 1.54 |
| Sand, Foundry, Fine | 104 | 1.67 |
| Sand, Foundry, NJ Silica | 97 | 1.55 |
| Sand-Kaolin Mix | 53 | 0.85 |
| Santonox | 25 | 0.40 |
| Saran Powder | 35 | 0.56 |
| Sawdust (Coarse) | 25 | 0.40 |
| Sawdust (Fine) | 18 | 0.29 |
| Sawdust (Moist) | 28 | 0.45 |
| Seal Coal | 32 | 0.51 |
| Seasoning Blend | 30 | 0.48 |
| Seed (Grass) | 44 | 0.70 |
| Selenium Powder | 62 | 0.99 |
| Separan Fine | 48 | 0.77 |
| Shellac Resin | 81 | 1.30 |
| Silene | 15 | 0.24 |
| Silene & Zinc Stearate | 15 | 0.24 |
| Silflo, Filter Aid | 10 | 0.16 |
| Silica Cubes | 45 | 0.72 |
| Silica Flour | 80 | 1.28 |
| Silica Gel | 42 | 0.67 |
| Silica Gel, Sorbead | 55 | 0.88 |
| Silica Sand | 81 | 1.30 |
| Silicon Carbide | 45 | 0.72 |
| Silicon Dioxide | 3 | 0.05 |
| Silver (Powder) | 69 | 1.11 |
| Slate, Crushed | 100 | 1.60 |
| SMA | 35 | 0.56 |
| SMA Pellets | 42 | 0.67 |
| Soap Flakes | 29 | 0.46 |
| Soap Powder | 36 | 0.58 |
| Soapstone | 47 | 0.75 |
| Soda Ash | 54 | 0.86 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Soda Ash-Iron Chromite | 77 | 1.23 |
| Sodium Bicarbonate | 50 | 0.80 |
| Sodium Aluminate | 61 | 0.98 |
| Sodium Borate | 77 | 1.23 |
| Sodium Chloride | 83 | 1.33 |
| Sodium Hydrosulfate | 70 | 1.12 |
| Sodium Hydroxide | 60 | 0.96 |
| Sodium Hydrosulphate | 73 | 1.17 |
| Sodium Hydrosulphite | 73 | 1.17 |
| Sodium Benzoate | 47 | 0.75 |
| Sodium Bisulphate | 90 | 1.44 |
| Sodium Caseinate | 21 | 0.34 |
| Sodium Chloride | 80 | 1.28 |
| Sodium Metasilicate | 70 | 1.12 |
| Sodium Naptholine Sulph. | 27 | 0.43 |
| Sodium Nitrate | 84 | 1.35 |
| Sodium Perborate | 53 | 0.85 |
| Sodium Phosphate VNX | 80 | 1.28 |
| Sodium Phospho Aluminate | 68 | 1.09 |
| Sodium Pyrophosphate | 63 | 1.01 |
| Sodium Silicate | 32 | 0.51 |
| Sodium Sulfate | 85 | 1.36 |
| Sodium Sulfite | 102 | 1.63 |
| Sodium Thiosulfate | 55 | 0.88 |
| Sodium Tripolyphosphate | 60 | 0.96 |
| Somagen Sol | 19 | 0.30 |
| Sorghum Seed | 32-35 | 0.51-0.56 |
| Soybeans | 48 | 0.77 |
| Soybean Flakes | 36 | 0.58 |
| Soybean Hulls | 25 | 0.40 |
| Soybean Meal | 40 | 0.64 |
| Spice (Barbecue) | 30 | 0.48 |
| Spice Blend | 36 | 0.58 |
| Sponge Iron | 150 | 2.40 |
| Stabilizer | 71 | 1.14 |
| Stabilizer (Food) | 54 | 0.86 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Stabilizer (Plastic) | 67 | 1.07 |
| Starch (Corn) | 43 | 0.69 |
| Starch (Granular) | 46 | 0.74 |
| Starch (Powder) | 40 | 0.64 |
| Starch-Industrial Binder | 43 | 0.69 |
| Starch-Mile | 39 | 0.62 |
| Sta-Nut | 53 | 0.85 |
| Stearic Acid (Flakes) | 32 | 0.51 |
| Stearic Acid (Powder) | 36 | 0.58 |
| Stearate Blend | 41 | 0.66 |
| Steel Powder | 150 | 2.40 |
| Steel Grit | 225 | 3.60 |
| Stone-Dust | 90 | 1.44 |
| Styrene Beads | 45 | 0.72 |
| Sucrose | 53 | 0.85 |
| Sucrose Octoacetate | 33 | 0.53 |
| Sugar (Dextrose) | 39 | 0.62 |
| Sugar (Granulated) | 44 | 0.70 |
| Sugar (Powdered) | 35 | 0.56 |
| Sugar (Beet) | 50 | 0.80 |
| Sugar Ind. | 46 | 0.74 |
| Sulphur | 45 | 0.72 |
| Sulphur (Granular) | 70 | 1.12 |
| Sunflower Seed | 38.5 | 0.62 |
| Super Phosphate | 70 | 1.12 |
| Talc | 35 | 0.56 |
| Talcum Powder | 55 | 0.88 |
| Tantalum Powder | 40 | 0.64 |
| Tea | 27 | 0.43 |
| Tea (Flakes) | 24 | 0.38 |
| Tea (Powdered) | 27 | 0.43 |
| Teflon (Powdered) | 29 | 0.46 |
| Teflon (Fiber) | 30 | 0.48 |
| Teflon (Granules) | 36 | 0.58 |
| Teflon Pellets (1/8") | 60 | 0.96 |
| Terepthalic Acid | 30 | 0.48 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Thiamine | 47 | 0.75 |
| Thionex | 30 | 0.48 |
| Thorium Oxide | 62 | 0.99 |
| Tide | 40 | 0.64 |
| Titanium Dioxide | 48 | 0.77 |
| Titanium Sponge | 60 | 0.96 |
| Tobacco (Powdered) | 28 | 0.45 |
| Tobacco (Cigarette) | 12 | 0.19 |
| Tobacco (Leaves) | 6 | 0.10 |
| Trap Rock | 91 | 1.46 |
| Tricalcium Phosphate | 85 | 1.36 |
| Trichlorocyanuric Acid | 50 | 0.80 |
| Tripolyphosphate | 80 | 1.28 |
| Trisodium Phosphate | 50 | 0.80 |
| Triplact | 12 | 0.19 |
| Tungsten Carbide | 250 | 4.00 |
| Tumaric (Acid Fines) | 51 | 0.82 |
| Uranium (Granules) | 184 | 2.95 |
| Uranium (Compound) | 191 | 3.06 |
| Uranium Oxide | 108 | 1.73 |
| Urea | 42 | 0.67 |
| Urea Formaldehyde | 36 | 0.58 |
| Urea Prills | 45 | 0.72 |
| Urea Molding Powder | 45 | 0.72 |
| Urea Powder | 39 | 0.62 |
| Urethane Foam | 18 | 0.29 |
| Vanadium Catalyst | 40 | 0.64 |
| Vegetable Oil Powder | 34 | 0.54 |
| Vermiculite | 62 | 0.99 |
| Vicrum | 35 | 0.56 |
| Vicron | 34 | 0.54 |
| Vicron (Limestone) | 62 | 0.99 |
| Vinyl Acetate | 36 | 0.58 |
| Vinyl Blend | 40 | 0.64 |
| Vinyl Compound | 36 | 0.58 |
| Vinyl Chips (Irregular) | 20 | 0.32 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com

| Material | Bulk Density lbs/ft³ | g/cc |
|---|---|---|
| Vinyl Pellets (1/8") | 36 | 0.58 |
| Vinyl Powder | 34 | 0.54 |
| Vinyl Resin | 36 | 0.58 |
| Vinyl Copolymer Resin | 40 | 0.64 |
| Vitamin Additive | 41 | 0.66 |
| Vitamin Enrichment | 40 | 0.64 |
| Vitamin Compound | 42 | 0.67 |
| Vitamin Mix | 44 | 0.70 |
| Vitamin Powder | 35 | 0.56 |
| Viton Rubber Crumb | 33 | 0.53 |
| Waffle Mix | 42 | 0.67 |
| Water Softener Compound | 39 | 0.62 |
| Wax | 27 | 0.43 |
| Wax (Flake) | 50 | 0.80 |
| Wax (Powder) | 38 | 0.61 |
| Wheat Bran | 11-16 | 0.18-0.26 |
| Wheat, Cracked | 35 | 0.56 |
| Wheat (Cut) | 46 | 0.74 |
| Wheat Hulls | 44 | 0.70 |
| Wheat Flour | 30 | 0.48 |
| Wheat Glutten | 43 | 0.69 |
| Wheat Middlings | 15 | 0.24 |
| Wheat (Shaved) | 34 | 0.54 |
| Wheat, Whole | 45-52 | 0.72-0.83 |
| Whey | 35 | 0.56 |
| White Lead | 72-100 | 1.15-1.60 |
| White Powder | 40 | 0.64 |
| Wood Chips (2"x2"x3") | 30 | 0.48 |
| Wood Flour | 20 | 0.32 |
| Wood Cellulose | 18 | 0.29 |
| Wood Chips | 18 | 0.29 |
| Wood Shavings | 10 | 0.16 |
| Yeast | 59 | 0.95 |



1 888 237 4224
Info@nationalbulkbag.com
www.nationalbulkbag.com