



भारतीय रबड़ गवेषण संस्थान
THE RUBBER RESEARCH INSTITUTE OF INDIA
 (वाणिज्य एवं उद्योग मंत्रालय, भारत सरकार)
 (Ministry of Commerce & Industry, Government of India)

Phone : 91-481-2353311(10 lines)
 Grams : RUBRBOARD
 Fax : 91-481-2354474
 Email : ddtc@rubberboard.org.in
 Website : <http://www.rubberboard.org.in>

रबड़ बोर्ड
RUBBER BOARD
कोट्टयम - 9

TECHNICAL CONSULTANCY DIVISION

KOTTAYAM 686 009

TEST REPORT

Report Number : 6782

30/08/2019

Reported for :

M/s. Indofrench Agrotech,
 231/2, Villianur Via, Poothurai,
 Vanur - TK,
 Villupuram - Dist,
 Tamilnadu - 605111.

Clients letter No and date : Letter dated 02/08/2019
 Title of the test : Latex foam as per IS 1741- 1960

Sample details

Sample	Latex foam
Lab ID No.	9589
Identification of the sample tested	Latex foam
Date of receipt of the sample	06/08/2019
Date of completion of the test	30/08/2019

Test Results

Sl. No	Test Parameter	Method	Specification	Results	Remarks
1	Odour	IS 1741-1960	No objectionable odour	No objectionable odour	Passed
2	Indentation hardness index, kg		7-20- Soft 21-35- Medium 36-50-Hard 51-100-Extra Hard	70	Extra Hard
3	Reduction in indentation hardness index, after flexing, %		20 Max.	12.7	Passed
4	Reduction in thickness, after flexing, %		5 Max.	1.5	Passed
5	Change in indentation hardness index, after ageing, 70°C for 7 days, %		± 20 Max.	2.5	Passed
6	Compression set under constant strain(Method A), %		15 Max.	4	Passed
7	Whole sample compression set(Method B), %		5 Max.	Nil	Passed
8	Copper, percent by mass		0.001 Max.	trace	Passed
9	Manganese, percent by mass		0.005 Max.	trace	Passed

Reported by:

Approved by

डॉ सिबी वर्गीस, संयुक्त निदेशक (त प)
 Dr. Siby Varghese, Joint Director (T C)
 भारतीय रबड़ अनुसंधान संस्थान, रबड़ बोर्ड
 Rubber Research Institute of India, Rubber Board
 वाणिज्य एवं उद्योग मंत्रालय, भारत सरकार
 Ministry of Commerce & Industry Govt. of India
 कोट्टयम - 9, Kerala

Joint Director (TC)
 (Authorized Signatory)

Note: 1. Results relate only to the items tested. This report should not be reproduced except in full without the written consent of the Technical Consultancy Division, Rubber Research Institute of India, Kottayam.
 2. Please be assured that the data we obtained with your samples will be held in strict confidence.