

	AzureSky		
	Method Validation for Ash Determination	Document no: AS003MV	
	Compiled by:	Tshepo Maponya – Laboratory Supervisor	
	Approved by:	Nonhlanhla Msibi -Operations Manager	

CONTROLLED DOCUMENT

Contents

Introduction 2
Objective 2
Method Extract 2
Samples Matrices 3
Apparatus 3
Performance Characteristics 4
Accuracy 4
Repeatability 6
Reproducibility 8
Precision 9
RUGGEDNESS-ROBUSTNESS 11

Effective date	Rev status	Next review date
02/2026	01	02/2029

	AzureSky		
	Method Validation for Ash Determination	Document no: AS003MV	
	Compiled by:	Tshepo Maponya – Laboratory Supervisor	
	Approved by:	Nonhlanhla Msibi -Operations Manager	

Uncertainty of Measurement..... 15

Introduction

Method validation involves determining how well a method performs, understanding its limitations, and identifying the factors that may affect its performance and to what degree. It also ensures that the method is suitable and reliable for addressing a specific analytical task.

Objective


The objective for this document is to validate the proposed procedure AS003WI used to determine the %ash content in coal, ensuring its accuracy, precision, reproducibility, ruggedness, robustness per ISO 1711

Method Extract

Ash determination is a rapid method for estimating the inorganic residue of coal by subjecting a sample to high-temperature combustion (typically 815°C) over a set period (Refer to AS002WI).

CONTROLLED DOCUMENT

Effective date	Rev status	Next review date
02/2026	01	02/2029

	AzureSky		
	Method Validation for Ash Determination	**Document no: AS003MV**	
	Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
	Approved by:	**Nonhlanhla Msibi -Operations Manager**	

Samples Matrices

Bituminous Coal- Medium grade coal with carbon content commonly used in power generation.


The sample shall be prepared according to instructions on the preparation of sample as per ASOO1IW. The top size for general analysis determination should be < 212 µm.

Apparatus

- Muffle furnace
- Weighing balance
- Desiccator

CONTROLLED DOCUMENT

Effective date	Rev status	Next review date
02/2026	01	02/2029

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
Approved by:	**Nonhlanhla Msibi -Operations Manager**	

Performance Characteristics

Performance characteristics are the key parameters to be addressed to ensure the method is fit for its intended purpose.

Accuracy

Accuracy - The accuracy of an analytical method is the extent to which test results generated by the method and the true value agree. Accuracy can also be described as the closeness of agreement between the value that is adopted, either as a conventional, true, or accepted reference value, and the value found.

A sample of known value CRM AS002 was analysed 10 times, with the results captured as follows:

LIMS NO	Original	Duplicate	Average
1337	22.08	22.17	22.13
1338	22.10	21.92	22.01
1339	22.59	22.54	22.57
1340	22.55	22.69	22.62
1341	22.60	22.47	22.53
1342	22.36	22.74	22.55
1343	22.67	22.5	22.58
1344	22.61	22.72	22.67

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT

1345	22.64	22.61	22.62
Overall average			**22.48**
Standard deviation			**0.23559**

Percentage recovery


$$\%\text{Percentage Recovery} = \left(\frac{\text{ReferenceValue}}{\text{Validation Average}}\right) * 100$$

$$= \left(\frac{22.50}{22.48}\right) * 100$$

$$= 100.089\%$$

- 100.089% is extremely close to 100%, indicating very high agreement with the reference value.
- This suggest that the method is accurately measuring ash content since it is comparing with the referenced value. This value is well within the commonly accepted accuracy range of 95–105%.

CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
Approved by:	**Nonhlanhla Msibi -Operations Manager**	


Repeatability

Repeatability refers to the precision of the method under the same conditions (same operator, equipment, lab, short time frame). It evaluates the consistency of the method when repeated on the same sample**.** It is an acceptable limit between an original and a duplicate of the same sample that is analysed under the same conditions.

LIMS NO	Original	Duplicate	Average	Difference	2% Average
1337	22.08	22.17	22.13	0.09	0.443
1338	22.10	21.92	22.01	0.09	0.440
1339	22.59	22.54	22.57	0.05	0.451
1340	22.55	22.69	22.62	0.14	0.452
1341	22.60	22.47	22.53	0.13	0.451
1342	22.36	22.74	22.55	0.38	0.451
1343	22.67	22.5	22.58	0.17	0.452
1344	22.61	22.72	22.67	0.11	0.453
1345	22.64	22.61	22.62	0.03	0.452
Overall average			**22.48**		**0.450**
Standard deviation	**0.23559**				
RSD	**1,0482067**				

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT

	AzureSky		
	Method Validation for Ash Determination		**Document no: AS003MV**
	Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
	Approved by:	**Nonhlanhla Msibi -Operations Manager**	

The repeatability limits and conditions as per ISO 1171 are given as follows:

- Samples that have an ash value that is less than or equal to 10%, the repeatability for such samples is 0.2%
- Samples that have an ash value that is greater than 10% have a repeatability that is given as 2% of the average.

Since the ash values for the reference material used accommodates the second condition, the targeted limit will be 2% of their averages. The averages and their differences are given on the table and all we found within the limits, rendering the method repeatable as per the outlined limits and conditions.

CONTROLLED DOCUMENT

Effective date	Rev status	Next review date
02/2026	01	02/2029

Reproducibility

Reproducibility is the degree of agreement between results obtained using the same method on identical test material/sample, but under different conditions. These conditions may include different analysts, different laboratories, different equipment or instruments, different days or time intervals. Ash determination has a reproducibility of 3% of the average as its reproducibility.

Reproducibility was addressed by analysis of a sample and comparing the two sets of results analysed by two analysts under the same conditions to check if the method is reproducible.

Sample no	Analyst 1	Analyst 2	Average	Difference	3% Mean
1	32,94	32,83	32,885	0,11	0,9866
2	32,99	32,17	32,58	0,82	0,9774
3	32,78	31,92	32,35	0,86	0,9705
4	32,69	32,22	32,455	0,47	0,9737
5	32,65	32,7	32,675	0,05	0,9803
6	32,59	32,77	32,68	0,18	0,9804
7	32,54	32,76	32,65	0,22	0,9795
8	32,25	31,59	31,92	0,66	0,9576
9	32,16	32,89	32,525	0,73	0,9758
10	32,21	32,62	32,415	0,41	0,9725

CONTROLLED DOCUMENT


Applying the reproducibility limits as outlined in ISO 1171 set at 3% of the averages, all the results are under their calculated 3% of mean, rendering the method reproducible.

Precision

Precision- The closeness of agreement between independent test results obtained by replicate measurements in the same or similar samples under specified conditions. It is usually expressed as the standard deviation, relative standard deviation or %RSD.

	Analyst 1	Analyst 2	Average
	22,13	22,24	22,19
	22,01	22,04	22,03
	22,67	22,83	22,75
	22,62	23	22,81
	22,53	22,65	22,55
	22,55	22,6	22,58
	22,58	22,8	22,69
Average	22,44	22,59	22,51
STD Deviation	0,2602	0,3412	0,2942

CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
	Compiled by:	**Tshepo Maponya – Laboratory Supervisor** 
	Approved by:	**Nonhlanhla Msibi -Operations Manager** 

Assigned Value **22.50**

The precision of the ash determination method was evaluated in accordance with ISO 1171:1997 for bituminous coal. For a certified value of approximately 22.50 % ash, the standard specifies a repeatability limit (r) of ±2 % of the mean, equivalent to ±0.45 % ash. The observed standard deviations from two independent trials were 0.26 % and 0.30 % ash, both within the specified reproducibility limit. These results confirm that the method meets the precision requirements of ISO 1171 and is suitable for the determination of ash content in bituminous coal within the scope of the laboratory's accreditation.

SUMMARY

Groups	*Count*	*Sum*	*Average*	*Variance*
Analyst 1	7	157,09	22,44143	0,067681
Analyst 2	7	158,16	22,59429	0,116395

ANOVA

Source of Variation	*SS*	*df*	*MS*	*F*	*P-value*	*F crit*
Between Groups	0,081779	1	0,081779	0,88853	0,364467	4,747225

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT

Within Groups	1,104457	12	0,092038
Total	1,186236	13	

Since F-stat is less than the F-critical, and the p-value is >0.05. There is no significant difference between the two analysts
Which implies that the method passes the precision test
The method demostrated good precision with the RSD values at 1,16 and 1,51, both of which fall well within general acceptable limits i.e<2 for analytical methods

RUGGEDNESS-ROBUSTNESS

The ruggedness study will encompass introducing a slight deviation on the procedure to evaluate how low out of range analysis room temperature affects the accuracy of ash determination. The results will be studied statistically using ANOVA and Welch's T-test.

LIMS no	Normal Conditions (19-26 oC)	Out Of Range Temperature (15 August 2025)	LIMS no
1431	21,95	22,06	**1476**
1432	22,22	22,38	**1477**
1433	22,12	21,97	**1478**

CONTROLLED DOCUMENT

1434	22,05	21,94	**1479**
1435	22,03	22,03	**1480**
1436	22,08	21,80	**1481**
1437	22,06	22,19	**1482**
1438	22,19	21,83	**1483**
1439	22,20	22,08	**1484**
1440	22,22	22,09	**1485**
Mean	22,11	22,04	
STD Dev	0,0929516	0,169708901	
RSD	0,420367223	0,770108913	
ABS Difference	0,075		

Comparison (Normal Conditions VS Stressed Conditions)

- Δ (Stress – Normal) = **−0.075 ash**
- **Welch t-test**: t = 1.23, p = 0.24 → **not significant** (95 %)
- **95 % CI for Δ**: (−0.206 to +0.056)

CONTROLLED DOCUMENT

- **ISO 1171 reproducibility limit**: ±0.66 ash
  - |Δ| = 0.075 ≤ 0.66 → **Within tolerance limits**

Anova: Single Factor

SUMMARY

Groups	*Count*	*Sum*	*Average*	*Variance*
Normal Conditions (19-26 oC)	10	221,12	22,112	0,00864
Out Of Range Temperature (15 August 2025)	10	220,37	22,037	0,028801

ANOVA

Source of Variation	*SS*	*df*	*MS*	*F*	*P-value*	*F crit*
Between Groups	0,028125	1	0,028125	1,502359	0,236104	4,413873
Within Groups	0,33697	18	0,018721			
Total	0,365095	19				

CONTROLLED DOCUMENT


Both a **Welch's t-test** (t = 1.23, p = 0.24) and a **single-factor ANOVA** (F = 1.50, F-critical = 4.41, p = 0.236) were performed to compare ash content results obtained under normal ambient conditions (20–25 °C) and stressed conditions (11–15 °C).

Both statistical approaches showed **no significant difference** between the two groups (p > 0.05), and the observed mean difference (0.075 ash) was also well within the ISO 1171 reproducibility-based acceptance margin (±0.66 3%).

Therefore, the method is demonstrated to be robust against variations in ambient temperature within the tested range.

Welch's t-test was selected as it does not assume equal variances. Calculations were performed in [Excel/Stats software], yielding t = 1.23, df = 16.9, p = 0.24. Since p > 0.05 and |Δ| ≤ 0.45 %, the method is robust to analysis room temperature variation.

CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
Approved by:	**Nonhlanhla Msibi -Operations Manager**	

Uncertainty of Measurement


Uncertainty of Measurement is a key element of method validation. It provides an estimate of the doubt associated with a result, considering all potential sources of variability. Evaluating uncertainty ensures that reported values are reliable, comparable and scientifically sound. This section presents the approach used to estimate and express the measurement uncertainty for ash determination.

U of Furnace Calibration(k=2)	**±4 ^{O}C**
Operating Temperature	**±815 ^{O}C**
U of Furnace Calibration	**2 ^{O}C**
UoM	**0,245398773**

To calculate Uom of balance	
UoM on calibration certificate	**0,00015**
Average mass of sample	**0,67475**
CRM 002	**22,5**
UoM	**0,005001853**

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
	Compiled by:	**Tshepo Maponya – Laboratory Supervisor** 
	Approved by:	**Nonhlanhla Msibi -Operations Manager** 

CONTROLLED DOCUMENT

2. Uncertainty sources table

Sources of UoM	Symbol	Standard Uncertainty (U)	U^2	Divisor	Sensitivity coefficient
CRM Uncertainty	U1	0,135	0,018225	2	1
Balance Calibration	U2	0,005001853	2,50185E-05	2	1
Furnace Calibration	U4	0,245398773	0,060220558	2	1

3. Combined Uncertainty

Combined uncertainty (Uc) **0,28**

4. Expanded Uncertainty

Expanded uncertainty (k=2) **0,56**

Effective date	Rev status	Next review date
02/2026	01	02/2029

5. Final Reporting statement


Expanded Uncertainty (k=2)	**0,56**
Confidence level:	**95%**
Traceability	**All components traceable to SI unit via calibrated instruments**

Conclusion

The validation results for the determination of ash content in coal demonstrate that the method meets the requirements for accuracy, precision, robustness, and reproducibility and UoM as assessed. The observed performance characteristics are consistent with the assigned values of the certified reference material (AS 002) and fall within the acceptable limits specified by ISO 1171:2010 and applicable laboratory quality standards (ISO/IEC 17025).

Accordingly, the method is deemed fit for purpose for routine analysis of ash content in coal, and results generated using this method can be considered reliable and in conformity with international standards.


CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
	Compiled by:	**Tshepo Maponya – Laboratory Supervisor** 
	Approved by:	**Nonhlanhla Msibi -Operations Manager** 

Characteristic (per TR 26)	Technical Justification for Omission
Limit of Detection (LOD)	Ash determination is a macro-analytical gravimetric method used to quantify bulk components, not trace levels. The LOD is not a critical parameter because the ash content in the samples (Hardcoal) is significantly higher (typically >1%) than the detection limits of the analytical balance (0.0001g).
Limit of Quantitation (LOQ)	Similar to LOD, the LOQ is not applicable for high-mass gravimetric analysis. The method is designed to measure total inorganic residue where the result is far above the "noise" level of the measurement system.
Linearity	Linearity is applicable to instrumental methods using calibration curves (e.g., ICP or UV-Vis sulphur analyzers). For gravimetric Ash determination, the relationship between the analyte (mass) and the result is inherently linear based on the laws of physics. No calibration curve is generated; therefore, linearity studies are not technically relevant.
Selectivity / Specificity	Selectivity in Ash determination is operationally defined by the method conditions (e.g., incineration at 815°C ± 10°C for coal). The method is non-specific by design, as it measures the total residue remaining after oxidation. Potential interferences are addressed via the temperature control and atmosphere specified in the ISO standard.

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT

	AzureSky	
	Method Validation for Ash Determination	**Document no: AS003MV**
Compiled by:	**Tshepo Maponya – Laboratory Supervisor**	
Approved by:	**Nonhlanhla Msibi -Operations Manager**	

Characteristic (per TR 26)	**Technical Justification for Omission**
Stability	**The analyte (Ash/Inorganic residue) is the stable remains of a combustion process. Once the sample has been cooled in a desiccator to a stable mass, the residue is chemically inert and stable. Stability of the final residue is managed by the "cooling to constant mass" protocol within the procedure itself.**

Revision

Revision no	Content changed	Reason for revision
01	No changes, additional information inserted which is a table for justification of omission of performance characteristics	Incomplete documentation, improvement to suffice TR-26

Effective date	Rev status	Next review date
02/2026	01	02/2029

CONTROLLED DOCUMENT