F 03-09

sanas South African National Accreditation System

NON-CONFORMANCE, CORRECTIVE ACTION AND CLEARANCE REPORT

SANAS No.: T1195

Organisation Name: AZurasky PTY (LTD)	NC Report Number: NC06
Area/Scope Assessed: Coal Testing	Assessor / Inspector / Expert: NCHILIZA

PART 1: DETAILED OBSERVATION

At the time of Assessment There was no validation for Total Moisture Method.

Signed (Representative):

Signed (Team Leader / Inspector):

MAJOR: [X] MINOR: [ ]

Reference No. of relevant Guide / Standard / Requirement: ISO/IEC 17025 7.2

Date: 08/04/26

PART 2: ROOT CAUSE ANALYSIS

(Provide an analysis of the extent and cause of the nonconformity)

Inadequate planning with regards to TM being on the scope of accreditation the lab did not have adequate data in order to perform the validation and since there wasn't a plan in place it made it difficult to execute the process.

PART 3: CORRECTIVE ACTION TAKEN

(Clearly indicate what corrective action was taken, and attach supporting evidence of implementation)

Conduct analysis from competent personnel and also do method validation report for TM.

Date: 14/04/2026

Signed (Representative):

PART 4: CORRECTIVE ACTION VERIFIED AND CLEARED

(Comment on whether the corrective action is sufficient and appropriate)

Date:

Signed: Assessor / Inspector/Expert:

PART 5: FOLLOW-UP AT NEXT ASSESSMENT

(Comment on the implementation of the corrective actions)

Date:

Signed: Assessor / Inspector/Expert:


©SANAS

AS001MF

07/25

ROOT CAUSE ANALYSIS FORM

IRQ NO: NCOG (SANAS)



SUPERVISOR

AS004MF 07/25

BRAINSTORMING FORM

IRQ no: NC06 (SANAS)

Brainstorming team

Keitumetse Maleka
Stiepo Maponya
Fiso Nyamisi

What went wrong? There was no method validation/verification for TM1 at the time of assessment.

Why 1: Why the CAB had no validation for TM? Lack of proper planning with regards to adding ~~TM1~~ into the scope of accreditation.

Why 2: Why was there improper planning? The lab initially did not intend to have TM1 for SANAS audit/assessment but later added the method.

Supervisor:

	AzureSky	
AzurESky	ISO Total Moisture Method Validation	Document no: ASMV 005
	Compiled by:	Sifiso Nyambi - Laboratory Manager
	Approved by:	Nonhlanhla Msibi -Operations Manager

Method Validation/Verification Report

Test Method: Determination of Volatile Matter

Standard Method: ISO 589

Matrix: Coal samples

Laboratory: AzureSky

Analyst: Sifiso Nyambi and Tshepo Maponya


Date: 11/04/2026 to 15/04/2026

1. Objective and Scope

Objective: To verify that the laboratory can successfully implement ISO 589 (Method B-air drying) and achieve the precision and bias requirements specified in the standard.

Scope: Applies to Total Moisture analysis in different types of coal e.g., bituminous and anthracite; using drying oven and top pan.

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

	AzureSky	
AzurESky	ISO Total Moisture Method Validation	Document no: ASMV 005
	Compiled by: Sifiso Nyambi - Laboratory Manager	
	Approved by: Nonhlanhla Maibi -Operations Manager	

2. References

- ISO 589: Hard coal and coke — Determination of Total Moisture
- ISO/IEC 17025:2017 Clause 7.2.
- Laboratory Quality Manual

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

	AzureSky	
AzurESky	ISO Total Moisture Method Validation	Document no: ASMV 005
	Compiled by: Sifiso Nyambi - Laboratory Manager	
	Approved by: Nonhlanhla Msibi -Operations Manager	

3.Equipment and traceability

Equipment Name	Company ID	Calibration due date	UoM (from certificate)
Crusher (-25mm)	AS8284	NA	NA
Crusher (-10mm)	AS8809	NA	NA
Crusher (-3mm)	AS5935	NA	NA
Drying Oven (107 °C)	AS8501 (NKOT M02.5 A+B)	December 2026	± 1 °C
Riffler splitter	NA	NA	NA
Cone and quarter	NA	NA	NA
Pans	(Numbered on pans)	NA	NA
Top Pan	AS00A31	March 2027	± 0.3 g

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

4. Reagents and Materials

- Certified Reference Material (CRMs): PT samples from the month of March 2026 were used, these were provided by Coal Concept. Given that TM does not have a CRM, the CAB has used the "consensus mean" from the PT report as the assigned value.
- Gases: Drying in air (oven capable of maintaining 105-110 °C for 3-5 hours)

5. Personnel Competency

The following personnel have been trained on SOP AS015IW and are deemed competent to perform the verification.

- Sifiso Nyambi
- Tshepo Maponya

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

6. Performance Characteristics

6.1. Accuracy

CRMs for TM are a headache because coal is physically and chemically unstable regarding moisture. As soon as the "bottle" is open, the moisture content begins to change based on the CAB's humidity. This makes the "true value" a moving target.

9 Precision

9.1 Repeatability limit

The results of duplicate determinations, carried out in the same laboratory by the same operator with the same apparatus on representative portions weighed out at the same time from the same sample, should not differ by more than the values given in the second column of Table 1.

9.2 Reproducibility critical difference

Since the humidity conditions in different laboratories vary, it is not possible to quote a limiting value for reproducibility critical difference for first-stage moisture. For total moisture, the results from two different laboratories should not differ by more than the values given in the third column of Table 1.

Table 1 — Precision

Property	Repeatability limit %	Reproducibility critical difference %
Second-stage moisture	0,3	Not applicable
Total moisture	0,5	1,5

Intermediate Precision

Date	Analyst	Result (%)
12/04/2026	Sifiso Nyambi	5.11
11/04/2026	Tshepo Maponya	5.11
%RSD	0.4334	1.2891
Combined RSD	1.72	

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

Since a CRM is not a viable option, the lab has opted to using the precision data in Table 1 (above) of the ISO 589 to prove its competence. Below is a detailed description of how:

1. Repeatability limit (0.5%)

This is the primary tool for internal verification. It tells us how much "noise" is allowed between two tests of the same sample done by the same person on the same equipment.

Criteria for acceptance: Every single pair's difference must be less than or equal to 0.5%

The table below shows the analysis conducted by the CAB for TM verification.

Run # (LIMS no)	Analyst	Result A (%)	Result B (%)	Difference	Run # (LIMS no)	Analyst	Result A (%)	Result B (%)	Difference
11328	*Sifiso Nyambi*	5.1	5.1	0.03	11333	*Tshepo Maponya*	5.1	5.1	0.0
11329	*Sifiso Nyambi*	5.2	5.1	0.06	11334	*Tshepo Maponya*	5.0	5.2	0.2
11330	*Sifiso Nyambi*	5.1	5.1	0.02	11335	*Tshepo Maponya*	5.1	5.1	0.0
11331	*Sifiso Nyambi*	5.1	5.1	0.02	11336	*Tshepo Maponya*	5.0	5.2	0.2
11332	*Sifiso Nyambi*	5.1	5.1	0	11337	*Tshepo Maponya*	5.1	5.1	0.0
Mean		**5.11**	**0.02**		**Mean**		**5.11**	**0.07**	

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

Verification Goal: If ≥95% of the duplicates fall within 0.5% limit, then the CAB has successfully verified it's repeatability objectives.

Conclusion: Since all the duplicates from the above table are within the 0.5% limit. The lab has successfully verified its repeatability criteria.

2. Reproducibility (≤1.5%)


Since there is not a CRM to check for bias, the lab shall use inter-laboratory comparison.

Criteria: The difference between CABs result and the mean of the PT must be <1.5%.

a) Using report 69 issued on date 31th October 2025 by Coal Concept. The CAB's lab ID 143e.
   - CABs TM and z-score, 8.0% and 0.12; respectively.
   - Average: 7.9
   - Difference = 8.0 – 7.9 = 0.1%

   Conclusion: Since 0.1% < 1.5%. **Reproducibility has been proven.**

b) Using report 71 issued on date 28th February 2026 by Coal Concept. The CAB's lab ID 143e.
   - CABs TM and z-score, 4.5% and -1.13; respectively.
   - Average: 5.1

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

- Difference = 5.1 – 4.5 = 0.6%

Conclusion: Since 0.6% < 1.5%. **Reproducibility has been proven.**

3. Accuracy without CRM

Since CRM is unavailable, ISO 17025 Clause 7.7.1 offers several "workarounds" to ensure validity of results.

- Proficiency Testing: The CAB's z-score has consistently been between -1 and 1, which proves the CABs ability to produce accurate TM results.
- The replicate testing also proves consistency in results, if the above data is considered- all the differences in replicate results were <0.5%

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

7. Measurement Uncertainty (Mu)

Budget Uncertainty table below:

Uncertainty Component	Source of Data	Type A or B	Distribution	Sensitivity Coefficient	Standard Uncertainty	(Standard Uncertainty) ^2
Repeatability	Lab Validation data	A	Normal	1	0.0003	0.00000009
Balance Calibration	Calibration Cert	B	Normal/Rectangular	1	0.0003	0.00000009
Balance resolution	Manufacturer spec	B	Rectangular	1	2.9E-05	8.33333E-10
Oven	Validation/Calibration	B	Rectangular	1	0.002697898	7.27866E-06
Weight of sample	Measurement process	B	Rectangular	1	0.001003	1.00601E-06
Sample preparation	Lab Validation data	A	Normal	1	0.0052	0.00002704
Combined Uncertainty	0.005958849					
Expanded uncertainty	0.011917298					

- Expanded Uncertainty (U): ± () %
- Coverage Factor (k): 2 (at 95% CI)

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

Other factors Influencing Uncertainty for TM

- Sample homogeneity
- Loss of moisture during prep
- Oven Temperature gradients
- Sample Mass
- Airflow

AzureSky		
ISO Total Moisture Method Validation		Document no: ASMV 005
Compiled by:	Sifiso Nyambi - Laboratory Manager	
Approved by:	Nonhlanhla Msibi -Operations Manager	

7. Deviations from Standard method

- None

8. Conclusion and Statement of Fitness for purpose.

Based on the data presented in this report, the laboratory has demonstrated that it meets the performance requirements of ISO 589. The method is considered fit for purpose for the analysis of Total Moisture in coal within the defined scope.

9. Approval

Date: 16-04-2026

Reviewed by: Tshepo Maponya (Laboratory Supervisor)

Authorised by: Nonhlanhla Msibi (Operations Manager)

Date issued	Revision Date	Next Revision Date
04/2026	00	04/2028

LIMS data for TM validation

