AzurESky	
AS012TF	CRUSHER EFFICIENCY

Compiled by:	**Sifiso Nyambi- Laboratory Manager**	
Approved by:	**Nonhlanhla Msibi- Operations Manager**	

CRUSHERS EFFICIENCY

DATE: _____ **Equipment No:** _____ Crusher's Size: ___
Operator's name:_____

Initial sample mass (kg)	
Mass of crushed sample (kg)	
Mass of oversize material (kg)	
Mass of undersize material (kg)	

EFFECIENCY = _____ DUST LOSS: =_____

DATE: _____ **Equipment No**: _____ **Crusher's Size:** _____
Operator's name: _____

Initial sample mass (kg)	
Mass of crushed sample (kg)	
Mass of oversize material (kg)	
Mass of undersize material (kg)	

EFFECIENCY = _____ DUST LOSS: =_____

DATE: _____ Equipment No: _____ **Crusher's Size:** _____
Operator's name_____

Initial sample mass (kg)	
Mass of crushed sample (kg)	
Mass of oversized material (kg)	
Mass of undersize material (kg)	

EFFECIENCY = _____ DUST LOSS: =_____

AzurESky	
AS012TF	CRUSHER EFFICIENCY

Compiled by:	**Sifiso Nyambi- Laboratory Manager**	
Approved by:	**Nonhlanhla Msibi- Operations Manager**	

NB: CRUSHER EFFICIENCY MUST BE ≥ 90%; DUST LOSS ≤ 10%

Supervisor's signature: _____

CALCULATIONS:

%Efficiency= $\frac{Mass\ of\ undersize}{Mass\ of\ crushed\ sample} X100$

%Dust loss= $\frac{Initial\ sample\ mass - mass\ of\ crushed\ sample}{Intitial\ sample\ mass} X100$

Comments:

_____

_____

_____

Note: *Should the crusher efficiency or dust loss test fail to come right after a duplicate has been done, then the shift supervisor must be informed to investigate. Should all internal investigations prove fruitless then an artisan should be called out.*