

Pearl Ply Technical Data Sheet (TDS Matrix)

Mechanical, Chemical & Structural Engineering Test Report

1. PHYSICAL & MECHANICAL PROPERTIES

- Density: 750 to 820 kg/m³ (High-density Gurjan & Hardwood core).
- Moisture Content: 6% to 8% (Stabilized in computerized jet veneer dryers).
- Screw Holding Capacity: > 2650 N (Face) | > 1650 N (Edge) tested per IS:1734 Part 10.
- Nail Holding Capacity: > 1400 N (Face) | > 950 N (Edge) tested per IS:1734 Part 10.

2. ADHESIVE RESIN & CHEMICAL COMPOSITION

- Resin Type: 100% Unextended Phenol Formaldehyde Synthetic Resin.
- Formaldehyde Emission: E0 Certified (< 0.5 mg/L) tested per CARB Phase 2 & GreenPro standards.
- Preservative Treatment: Vacuum pressure impregnated copper-boron anti-termite shield.

3. DIMENSIONAL ACCURACY & MOISTURE RESISTANCE

- Thickness Tolerance: +/- 0.1 mm (Quad Calibrated).
- Squareness Tolerance: 1 mm per 1000 mm length.
- 24-Hour Water Absorption Swelling: Less than 1.2% in thickness.