

Graphical Abstract

**Topology Optimization strategies for continuous fiber-reinforced and functionally graded anisotropic composite structures:
A brief review**

Yogesh Gandhi, Giangiacomo Minak

Highlights

**Topology Optimization strategies for continuous fiber-reinforced and functionally graded anisotropic composite structures:
A brief review**

Yogesh Gandhi, Giangiacomo Minak

- Research highlight 1

- Research highlight 2

Topology Optimization strategies for continuous fiber-reinforced and functionally graded anisotropic composite structures: A brief review

Yogesh Gandhi^{a,*}, Giangiacomo Minak^a

^aUniversity of Bologna, Department of Industrial Engineering, Forlì, 47121, Emilia-Romagna, Italy

Abstract

Among all types of Additive Manufacturing (AM) technology, Continuous Fiber Fused Filament Fabrication (CF4) can fabricate high-performance composites compared to those manufactured with conventional technologies. AM provides the excellent advantage of a very high degree of reconfigurability, which is in high demand to support the immediate short-term manufacturing chain in medical, transportation, and other industrial applications. Additionally, the CF4 capability enables the fabrication of Continuous Fiber-Reinforced Composite (CFRC) materials and Functionally GRaded Anisotropic Composite (FGRC) structures. The current expedition in AM allows us to integrate Topology Optimization (TO) strategies to design realizable FRC and GFRC structures for a given performance. Various TO strategies for attaining lightweight and high-performance designs have been proposed in the literature, which exploits AM's design freedom. Therefore, the paper attempts to address works related to TO strategies employed to obtain optimal CFRC and FGRC structures. This review intends to overview, compare existing strategies, analyze their similarities and dissimilarities, and discuss challenges and future trends in this field.

Keywords:

topology optimization, anisotropic materials

1. Introduction

Additive Manufacturing. The cost-effective commercially available Additive Manufacturing (AM) or 3D Printing (3DP) technologies eliminate many limitations that previously 30 plagued the manufacturing of highly tailored structural performance for multifunctional [] and multi-physics [] applications. Moreover, the short metamorphosis of AM technologies offers unique capabilities to realize the next-generation lightweight structure have brought great application potentials 35 in several major industries such as aerospace [1, 2], automotive [] and medical[3]. First, AM's unique ability to fabricate a highly complex shape without a substantial increase in fabrication costs, along with the benefit s of reducing manufacturing preparation time, renders these technologies worthy investment 40 for large-scale industries. Moreover, it offers the fabrication of lattice structures-a lightweight design comparative to the solid-filled parts. Thus, offer diversification of design to answers multifunctional material requirements in weight reduction, [4], their ability to dissipate energy [5, 6], heat [7] and vibration 45 [8]. The printed polymer parts frequently consist of carbon nanotubes and short fibre to upgrade their mechanical performance. Still, it cannot outperform [9, 10], the mechanical strength offered by continuous fibre-reinforced composite laminate manufactured using conventional manufacturing tools. Hence, the 25 shortcomings of 3D printed polymer composites aggravated 50

the demand to develop Continuous Fiber Filament Fabrication (CF4) technology. CF4 technology provides a unique opportunity to reduce part distortion warping and support structures during printing, and fibre tension prevents nozzle clogging, a constant lookout with the polymer AM. Additionally, controlling the anisotropic properties of the fibre-reinforced composites can effectively distribute the loads throughout the laminate to maximize the structure's strength and stiffness. Recognizing these potentials of AM, returned a resurgent interest in utilizing the design strategies to exploit AM's performance-driven manufacturing technologies towards enhancing printed parts' overall functional performance. In contrast, to the geometric-driven or/and cost-driven manufacturing of components. The concept of performance-driven manufacturing is known as Design for Additive Manufacturing (DfAM) [11].

Topology optimization. Topology Optimization (TO), one of the DfAM methods, is an iterative design tool to optimize a quantifiable objective while being intended to sustains loads, constraints, and boundary conditions. Topology Optimization is frequently adopted to design structurally sound parts and has subsequently surpassed optimization design tools such as shape and size optimization in isolation. The seminal work of Bendse and Kikuchi [12] introducing the concept of TO on the homogenization method; since then, TO has been developed rapidly. TO approaches can be summarized as follows: the homogenization method [12]; the Solid Isotropic Material with Penalization (SIMP) method [13, 14], the level set method [15, 16], the Evolutionary Structural Optimization (ESO) method [17]; Topology Derivatives and Phase

*Corresponding author

Email addresses: yogesh.gandhi@unibo.it (Yogesh Gandhi),
giangiacomo.minak@unibo.it (Giangiacomo Minak)

Field. The details of these approaches are discussed in the review papers [18, 19, 20] and some emerging TO methods for smooth boundary representation include the 'Metamorphic Development Method' (MDM) [21], and the 'Moving Morphable Method' (MMM) [22]. The general architecture of TO starts with the definition of maximizing or minimizing a single or multi-target-objective function to fulfil a set of constraints such as volume, displacement, or frequency [23]. Then, as part of an iterative process, design variables, Finite Element Analysis (FEA), sensitivity analysis, regularization, and optimization steps are repeated in this order until convergence is achieved [24].

Topology Optimization of fiber-reinforced composite materials. CF4 technology allows fabrication of FRC material with the continuous spatial in-plane variation of fiber angle and fiber volume fraction, thus expanding design space as opposed to variable [25] and constant stiffness laminate [25]. Moreover, CF4 technology can achieve out-of-plane variation of fiber angle due to the fiber-reinforced composite's self-supporting characteristics. Numerous studies have shown that fiber orientation optimization can significantly tailor structural performance such as stress concentration [26], stiffness [27], load-bearing capacity, buckling load, and the natural frequency [28]. Therefore, the design of the FRC structures requires optimization methods that reflect design freedom offered by CF4 technologies, including constraints, to thoroughly exploit the anisotropic properties of FRC material [29]. The optimization concept applied to FRC materials allows finding the optimized material distribution, the optimized orientation of fiber paths, as well as optimized geometric contours of the laminate. Hence, the optimization method for FRC structures with continuous fiber parameterization schemes and optimization algorithms have notable influences on the quality of the solution. The article on the optimization of topology and fiber path orientation and thus, only related works are reviewed.

2. Topology Optimization for continuum structures

2.1. Problem Statement

A general form of topology optimization

2.2. Discrete Topology Optimization

Topology optimization aims to obtain binary solutions representing optimal structural layouts. Therefore, the topology optimization problem is a binary problem representing the void and solid regions of the structure, respectively. The well-known discrete topology optimization method is the Bi-directional Evolutionary Structural Optimization (BESO). Interested readers find comprehensive reviews on the BESO methods in [30, 31]. Another outlook on approaching the discrete problem is using a genetic algorithm [32] that can find "global minimum" and allow handling a discrete variable, but this always sacrifices the computational cost. Furthermore, Sigmund [33] questions the usefulness of non-gradient approaches in Topology Optimization. Finally, Sivapuram et al. [34] combined the features of

BESO and the sequential integer linear programming for discrete topology optimization. The discrete TopOpt uses binary design variables, one for each of the finite elements in the mesh of the structural domain. The design variable 1 implies the finite element is filled with material, 0 indicates void. Consider an objective function $\Phi(\rho, \mathbf{U}(\rho))$, constrained by $g_i \leq g_i^*, i \in [1, M]$, with ρ being the design variables, where N number of finite elements in mesh. The discrete variable optimization problem can be formulated as follows:

$$\begin{aligned} \min_{\rho} : & \Phi(\rho, \mathbf{U}(\rho)) \\ \text{s.t.} : & \sum_{e=1}^N v_e \rho_e = \mathbf{v}^T \rho \leq V^* \\ & : g_i(\rho, \mathbf{U}(\rho)) \leq g_i^*, \quad i = 1, \dots, M \\ & : \rho_e = \begin{cases} 0(\text{void}) \\ 1(\text{material}) \end{cases}, e = 1, \dots, N \\ & : \mathbf{K}(\rho) \mathbf{U} = \mathbf{F} \end{aligned} \quad (1)$$

where \mathbf{K} and \mathbf{U} is the assembled stiffness matrix and displacement vector corresponding to finite elements in the mesh.

2.3. Continuum Topology Optimization

Density-based topology optimization is a broadly received idea considered topology optimization of continuum structures by using continuous density design variables that transform the binary variable optimization problem into a density distribution problem. The design variable can take any value from 0 to 1 such that $\rho \in [0, 1]$. Thus, in such methods [12, 13], optimized solutions do not explicitly exhibit structural boundaries, which challenges solving problems where explicit boundary identification is essential, e.g., in design-dependent and multiphysics problems. The continuous variable optimization problem can be formulated as follows:

$$\begin{aligned} \min_{\rho} : & \Phi(\rho, \mathbf{U}(\rho)) \\ \text{s.t.} : & \sum_{e=1}^N v_e \rho_e = \mathbf{v}^T \rho \leq V^* \\ & : g_i(\rho, \mathbf{U}(\rho)) \leq g_i^*, \quad i = 1, \dots, M \\ & : 0 \leq \rho_{\min} \leq \rho \leq 1 \\ & : \mathbf{K}(\rho) \mathbf{U} = \mathbf{F} \end{aligned} \quad (2)$$

3. Parameterization schemes for fiber orientation

The parameterization scheme implements a numerical description of fiber orientation patterns and defines variables for the optimization. It should ensure spatial continuity of fiber angle so that CF4 technology can produce the structure, and it should also provide enough design freedom so that optimization algorithm can consider more candidate designs.

105 3.1. Continuous Parameterization

The continuous parametrization of fiber orientation design uses the angle itself as the design variable [35, 36]. The design variable is the continuous and independent parameter that provides flexibility in changing the orientation across the design points, with the relaxation of orientation design space. However, handling the continuous fiber orientation design presents difficulties due to a fourth-order transform tensor, which rotates to a given angle composed of multivalued sine and cosine functions, rendering a non-convex optimization problem. Furthermore, optimizing the fiber orientation is susceptible to the initial fiber configuration, thus causing difficulties obtaining the optimized solution. As illustrated in [37], suboptimal solutions [25, 29] are the persistent outcome of a continuous fiber orientation design problem—one brute-force way to avoid it by further relaxing the design space. For instance, free material optimization (FMO)[38, 39] parameterizing each stiffness tensor element independently as the design variable. Thus, securing the scheme from the complexity that stems from the design space’s orientation design variable. However, as compensation, point-wise nonlinear constraints ensure the positive semi-definiteness of the obtained stiffness tensor and link it to the feasible physical design, making this approach challenging. Nomura et al. [40] formulated orientation design variable as a tensor field to simplify the first tensor invariant constraint and remove nonlinear constraints successfully introduced due to the second tensor invariant. Still, as commented, the violation of these constraints is observed at the joint point of the structural members where the orientation shows the discontinuous distribution.

Reasonably arranging the fiber orientation is critical to effectively handling an anisotropic material, which is vital in designing next-generation lightweight composite structures. Frequently, fiber orientation optimization creates difficulty associated with local optima and discontinuous functions. To address this, gradient-free algorithms, such as the genetic algorithm particle swarm algorithm and simulated annealing algorithm [41], are more qualified because of their global searching ability [42, 43]. By allowing differentiable functions, mixed design variables, and discrete space, introduce a relaxed formulation that has the advantage of obtaining fewer local optima. The inefficiency of most gradient-free algorithms requiring numerous function evaluations is impractical for expensive finite element simulations; thus, adoption of gradient-based algorithms, i.e., Optimality Criteria Method (OCM), Method of Moving Asymptotes (MMA) [44], and Sequential Linear Programming (SLP) [45].

In particular, for orthotropic materials, early studies utilizing the analytical derived optimality criterion [46] for optimizing fiber orientation dates back to the pioneering work of Pedersen on strain-based method [47, 48, 49]. In Pedersen’s work, strain energy density transformed into principal strain and concluded that material orientation axes along principal strain axes always give stationary energy density. However, Cheng [50] argued that the discussion is limited to a unit cell case where the orientation variable is separated from the design domain to obtain

extreme strain energy. After that, a similar deduction using iterative optimality criteria [51, 52] formulated the stress-based method [53] by exercising invariant stress field for material orientation. Finally, Diaz and Bendsoe [54] extended the stress-based method for determining the optimal orientation optimization problem corresponding to multiple loads. Despite their similarity, the stress-based method produces a slightly stiffer structure than the strain method because strong couplings exist among the orientational variables when the strain field is used [50]. Conclusively, Gea and Luo [55] demonstrated that the fiber orientation coincides with the principal stress/strain fields for relatively ‘weak’ shear and some shear ‘strong’ types of orthotropic materials. Further, the methods are highly dependent on the initial fiber configuration, and both approaches will fail for shear ‘strong’ type materials due to repeated global minimum solutions. Nevertheless, these methods form the basis for future research on material orientation optimization for fiber-reinforced composite materials. These methods’ shortcomings coerced to formulate the energy-based method introduced by Luo and Gea [56, 57]. The method uses an inclusion cell to estimate the strain fields’ and stress fields’ dependency on fiber orientation by introducing an approximate energy factor. Yet, the dependence of energy factors on the traction stress, material properties, and orientation of the inclusion cell and its surroundings make it challenging to formulate the framework for 3D and complex loading problems. Following the principles of the energy-based method, Yan et al. [58] proposed a hybrid stress-strain method by weighting the mean compliance’s optimality condition in the stress and strain form. Numerical examples demonstrate their method on the shear weak and strong materials and extended for a 3D problem. The assumption on the elemental strain and stress field invariant to the neighboring elemental orientation is considered; however, it may restrict to solve 3D problems and may result in a suboptimal solution.

On the other hand, Shen et al. [59] questioned the lack of understanding about the orientation optimization algorithm to handle arbitrary constraints and loads. A step length scheme for orientation optimization is advised to achieve global descent by normalizing the gradient vector and introducing a parameter to control the magnitude of material orientation in each iteration. However, the verification lacks the effect of adding constraints in the orientation optimization problem on the update scheme, a critical factor for the optimality criteria method. Thus, a more generalized OCM for the topology optimization of transversely isotropic material is demanded from the perspective of scalability and multiloading situations. Recently, Kim et al. [60] interpreted the work of Patnaik et al. [?] on parametric optimization and proposed a generalized optimality criteria method for topology optimization problems. The approach eliminates the compulsion to satisfy the constraints during every optimization iteration but should be met upon convergence.

An alternative is employing curvilinear parameterization schemes that define fiber paths as the graphs of analytical function, which guarantee continuity of fiber angle and have a small number of design variables [61, 62, 63]. Nevertheless, the restrictive design search space will limit the tailorability of the fiber path, thus deteriorates the optimization problem’s stability

[64] and quality of the optimized solution. Adjacent, the parameterization schemes can follow equidistant iso-contours of a level set function to represent curvilinear fiber paths [65, 66], thus naturally ensuring fiber continuity and being often parallel to the neighboring fiber paths. Furthermore, the optimization result becomes highly dependent on the initial configuration, and local solutions often appear [67].

3.2. Discrete Parameterization

The counter scheme reduces the orientation design space to avoid multiple local optima issues where the optimized solution is highly sensitive to the initial fiber configuration. Therefore, Stegmann and Lund [37] stretched the orientation design space by choosing discrete fiber orientation candidates, which are defined apriori, to parametrize the orientation design space into the discrete material candidates. These transversely isotropic material models are defined for different fiber orientations for the same isotropic elasticity tensor. Thus the scheme share some similarities with the multi-material optimization problem in [68, 69]. The suggested scheme assigned weighting functions to different candidates and employed gradient-based optimization with penalization coefficient, forcing the weighting functions to seek a binary design and fiber convergence, i.e., one discrete material at each design point. This method is known as Discrete Material optimization (DMO). DMO laid the foundation for SFP (Shape Function and with Penalization) [70], BCP (Bi-value Coding parametrization) [71] to perform discrete fiber orientation optimization. A comparison between these methodologies utilizing various numerical examples is drawn in [72].

Contrarily to CFAO, it does not incorporate design problems for continuously varying orientation distributions. First, it is an imperative design consideration to circumvent stress constraint and degradation in the strength by order of magnitude lower than continuous fiber paths caused due to fiber discontinuity. Consequently, it permits a limited scope to fully exploit the potential of modern technology's continuously varying orientation in composites [73, 27, 26]. Secondly, these methods fail to address the fiber convergence even against the significant penalization factor; hence, their benefit relies on an optimization algorithm to circumvent impractical mixtures of fiber angles. Third, the discrete parametrization scheme should further minimize the number of design candidates for efficient optimization. Concerning these drawbacks, Kiyono et al. [72] proposed a parametrizing scheme, which is a continuation of the computational approach suggested by Yin and Ananthasuresh [69]. Introducing a normal distribution function as a weighting function in their parametrizing scheme guarantees fiber convergence, low sensitivity to the initial fiber configuration, and the continuity of the fiber orientation. Another different work proposed a Self-Penalization Interpolation Model for Fiber Orientation (SPIMFO) based on convergent Taylor series for sine and cosine functions to optimized composite hyperelastic material [74] and the dynamic design of laminated piezo-composite actuators [75].

3.3. Hybrid Parameterization

Utilizing continuous and discrete methodology benefits is another alternative to fiber orientation optimization. The key idea in the following approaches is to fill the gaps by acknowledging the beneficial characteristics of both strategies to improve computational efficiency and/or reduce local optima and/or resolve and/or fiber continuity manufacturability issues. Therefore, an approach to reduce the risk of falling into local optimal without sacrificing the fiber continuity can use both discrete and continuous parametrization as suggested by Luo et al. [76]. Their work proposed a "coarse to fine" strategy, where the orientation design space is divided into discrete sub-intervals. After that, the CFAO searches for an optimized solution in a sub-interval, where the sub-interval selection problem is solved using the DMO approach. However, no criterion is defined to determine the number of sub-intervals required in advance.

Nevertheless, the proposed strategy provides flexibility to integrate alternatives that are suggested for DMO and CFAO approaches. Nomura et al. [77] studied the cartesian system for orientation design variables to improve initial design dependency and local optima issues encountered in the continuous parameterization approach. The parametrization scheme was further extended to yield an optimized discrete orientation design for a given discrete orientation set in their work. Moreover, the characteristics representing the orientation design variables into the vectorial form consider the 2π ambiguity, which occurs due to the periodic nature of the orientation design variable. Introducing vectorial design variable as a point-wise quadratic inequality constraint yields more interpolated elasticity tensor than the single variable polar representation.

Xia and Shi [78] develops a continuous global function by applying the shepherd interpolation method at scattered design points to represent the fiber orientation throughout the design domain. The benefit of the interpolation function is to ensure fiber continuity while considering reduced orientation design space in contrast with CFAO. Unfortunately, it suffers from the initial configuration and ends at the sub-optimal solution. In another work of Xia [79] applied multilevel optimization for fiber orientation optimization and verified its efficiency against the single-level optimization. Still, the optimization results in different fiber arrangements for different initial fiber orientations. As a result, the efficiency of the multilevel approach relies on the attained fiber orientation field at a coarse level since the optimization at the successive refined level starts from an initial design computed at its neighboring coarser level.

4. functionally graded anisotropic material

Fused deposition modeling (FDM) additive manufacturing technology allows the manufacture of FRC structures with continuous yet spatially varying fiber paths, thus bringing considerably larger design freedom to novel design methods [80, 81, 82]

5. New articles

Shen et. al.[59] proposes normalized gradient by maximum algorithm to update material orientation of anisotropic material using gradient descent method. believe that the gradient descent method is well suited for optimal orientation of fiber due its simplicity and robustness. The first order derivative of compliance with respect to material orientation can be explicitly calculated in closed form. The only unknown coefficient in gradient descent method is the step length can guarantee a global descent direction which converge to a minimum, if chosen wisely. Strain-based method was developed based on the assumption that strain field is constant. Reuschel [42] developed Computer Aided Internal Optimization (CAIO) to align fiber orientation in principle stress direction so as to reduce the internal shear stress which was found to be weakness of FRCs. Brampton [65] combined Luo and Gea's work [57] with level-set method to generate the optimized fiber orientation with continuous fiber path.

5.1. Formulation and optimization algorithm

The compliance is expressed in global form:

$$c = \mathbf{u}^T \mathbb{K} \mathbf{u} \quad (3)$$

Take partial derivative of the global equilibrium equation with respect to the material orientation of the i^{th} element:

$$\frac{\partial c}{\partial \theta_i} = \mathbf{u}^T \frac{\partial \mathbb{K}}{\partial \theta_i} \mathbf{u} \quad (4)$$

Considering the quadrilateral element under plane stress condition, the stiffness matrix formulation is given by

$$\mathbb{K}_i = \sum \omega(\eta, \zeta) \mathbb{B}_i(\eta, \zeta)^T \mathbf{T}_i^T \mathbf{D} \mathbf{T}_i \mathbb{B}_i(\eta, \zeta) |\mathbb{J}_i(\eta, \zeta)| \quad (5)$$

where four integration points are $\eta = \pm \frac{1}{\sqrt{3}}, \zeta = \pm \frac{1}{\sqrt{3}}$, \mathbb{D} is the stress/strain matrix, \mathbb{T}_i is the transformation matrix for the i^{th} element and $\omega(\eta, \zeta)$ is the weight factor.

$$\mathbb{D} = \begin{bmatrix} \frac{E_{11}}{1-\nu_{12}\nu_{21}} & \frac{\nu_{12}E_{11}}{1-\nu_{12}\nu_{21}} & 0 \\ \frac{\nu_{12}E_{11}}{1-\nu_{12}\nu_{21}} & \frac{E_{11}}{1-\nu_{12}\nu_{21}} & 0 \\ 0 & 0 & G_{12} \end{bmatrix} \quad (6)$$

$$\mathbb{T} = \begin{bmatrix} \cos^2 \theta_i & \sin^2 \theta_i & \sin \theta_i \cos \theta_i \\ \sin^2 \theta_i & \cos^2 \theta_i & -\sin \theta_i \cos \theta_i \\ -2 \cos \theta_i \sin \theta_i & 2 \cos \theta_i \sin \theta_i & \cos^2 \theta_i - \sin^2 \theta_i \end{bmatrix}$$

Taking partial derivative of stiffness matrix with respect to θ_i yields:

$$\frac{\partial \mathbb{K}_i}{\partial \theta_i} = \sum \mathbb{B}_i(\eta, \zeta)^T \left(\frac{\partial \mathbf{T}_i^T}{\partial \theta_i} \mathbf{D} \mathbf{T}_i + \mathbf{T}_i^T \mathbf{D} \frac{\partial \mathbb{T}_i}{\partial \theta_i} \right) \mathbb{B}_i(\eta, \zeta) |\mathbb{J}_i(\eta, \zeta)| \quad (7)$$

The 1st order partial derivative of the stiffness with respect to material orientation can be explicitly expressed as a function of transformation matrix and its 1st order derivative.

The 2nd order derivative of compliance is given as the following:

$$\frac{\partial^2 c}{\partial \theta_i \partial \theta_j} = \mathbf{u}^T \frac{\partial \mathbb{K}}{\partial \theta_j} \mathbb{K}^{-1} \frac{\partial \mathbb{K}}{\partial \theta_i} \mathbf{u} - \mathbf{u}^T \frac{\partial^2 \mathbb{K}}{\partial \theta_i \partial \theta_j} \mathbf{u} + \mathbf{u}^T \frac{\partial \mathbb{K}}{\partial \theta_i} \mathbb{K}^{-1} \frac{\partial \mathbb{K}}{\partial \theta_j} \mathbf{u} \quad (8)$$

Desai et al. [83] : Gradient based numerical techniques were adopted for optimizing the topology and fiber orientation concurrently ([35][84]). The optimization approach proposed in [77] offer continuous and discrete sets of angles. It improves local minimum issue inherent to CFAO because the evolving design is independent of previous iteration design Zhou et al. [85] : Structural products with complex geometries are usually assemblies of components with relative simple geometries. This mainly because producing multiple components with simple geometries are often less expensive than producing a single product with complex geometries, even with the additional cost of assembly. A multi-components structural product is to design and optimize its overall geometry first, and then decompose it to refine part boundaries and joint configuration. Such practice, known as two-step approach, is likely to yield sub-optimal solution with respect to overall structural performance and/or manufacturing and assembly costs, since the optimal decomposition obtained in the second step is largely dependent on the optimal overall geometry obtained in the first step. According to the types of the prescribed design domain, topology optimization can be classified into discrete (truss/beam) approaches, pioneered by Dorn, and continuous (pixel/voxel) approaches, pioneered by Bendsoe and Kikuchi [12]. According to the types of optimization algorithm utilized, topology optimization can be classified into gradient methods and genetic algorithm. Recently, non-gradient methods received serious critique [33] from the topology optimization community regarding its applicability in continuum structure problems. It is due, mainly, to its lack of sensitivities and the associated computational inefficiency. However, gradient methods are inapplicable to the problems that have non-differentiable objectives and constraints, for instance, as in case for the manufacturability objectives in the multi-components topology optimization.

A ground topology such that a node represent a structure element and, an edge represent a joint element. A given combination of structure element and joint can be interpreted as unique topology graph

Material density field

In a prescribed, fixed design domain Ω , a characteristic function χ is defined to describe the material domain Ω_d to be optimized:

$$\chi(\mathbf{x}) = \begin{cases} 0, & \forall \mathbf{x} \in \Omega \setminus \Omega_d \\ 1, & \forall \mathbf{x} \in \Omega_d \end{cases} \quad (9)$$

where \mathbf{x} stands for a design point in Ω and $\chi(\mathbf{x})$ is defined by a scalar function ϕ and the Heaviside function H such that:

$$\chi(\mathbf{x}) = H(\phi(\mathbf{x})) = \begin{cases} 0, & \forall \mathbf{x} \in \Omega \setminus \Omega_d \\ 1, & \forall \mathbf{x} \in \Omega_d \end{cases} \quad (10)$$

To eliminate checkerboard patterns therefore generating mesh-independent results, the Helmholtz PDE filter is introduced to regularize ϕ :

$$-R_\phi^2 \nabla^2 \tilde{\phi} + \tilde{\phi} = \phi \quad (10)$$

where R_ϕ is the filter radius, and $\tilde{\phi}$ is the filtered field. Then the density field ρ can be defined by an additional smoothed Heaviside function \tilde{H} :

$$\rho = \tilde{H}(\tilde{\phi}) \quad (11)$$

After the series of regularization from ϕ to ρ , the resulting density field is bounded between 0 and 1.

Material orientation vector field

The Cartesian representation of continuous angles proposed in [77], the original material orientation vector field $v^k = (\xi^k, \eta^k)$ bounded by a box constraint $v^k \in [-1, 1]^2 \times [-1, 1]^2$ if first regularized by Helmholtz PDE filter 10. Then, the (unbounded) \tilde{v}^k is projected back to the original box constraint with smoothed Heaviside function \tilde{H} . The regularized orientation vector field \tilde{v}^k in a box domain is then projected to a circular domain through an isoparametric projection \mathbf{N}^c . The transformation from a box domain to a circular domain eliminates the need of the quadratic constraint for each design point, and ensures singularity-free numerical analysis.

Hybrid approaches

Liu et al. [86]

6. Discussion

The discussion focuses on the suitability of given topology optimization for anisotropic material, given a pre-requisite understanding of the manufacturing process and its limitations. Therefore, the following discussion does not address composite manufacturing technology and its differences to adopt the particular topology optimization method.

The manufacturing design freedom extended by available composite manufacturing processes provides the flexibility to develop and integrate topology optimization approaches for designing anisotropic material orientations [87]. Therefore, the paradigm of performance-driven design focuses on investigating the suitability of topology optimization methods that can fully exploit the design freedom offered by manufacturing technology. Thus, the existing techniques for material orientation are broadcasted into four major classes, as stated previously.

Continuous orientation methods apply to manufacturing techniques with the highest freedom in shape and variable stiffness. Thus, the continuous orientation formulation directs fiber path planning to ensure fiber trajectory curvature, fiber continuity, and offset distance between adjacent fiber deposition. Papapetrou et al. [66] designed part's topology and material orientation simultaneously; the optimized results were post-processed using continuous fiber path planning to ensure realizability. A sequential scheme is proposed [88, 89] where fiber

placement based on load transmission follows isotropic topology optimization contrary to Liu [90], who adopted concurrent fiber path planning and structural topology optimization. The multi-axis material deposition technology using the robotic arm requires an extension of the topology optimization algorithm to envelop the 3D fiber orientation in contrast to in-plane printing. Schmidt et al. [91] introduced azimuth and elevation angles to extend the CFAO method for 3D fiber orientation. In addition, they emphasized the issues of nonconvexity of the compliance and sensitivity to the initial fiber orientation guess study by investigating the orientation parameter space to mitigate the issues [92]. Finally, the realizability of 3D printed composite is studied by Fedulov et al. [93], where they proposed a filtering technique for fast convergence.

Haftka et al. developed

References

References

- [1] D. Kokkinis, M. Schaffner, A. R. Studart, Multimaterial magnetically assisted 3D printing of composite materials, *Nat. Commun.* 6 (2015) 1–10. doi:10.1038/ncomms9643.
- [2] L. Berrocal, R. Fernández, S. González, A. Perrián, S. Tudela, J. Vilanova, L. Rubio, J. M. Martín Márquez, J. Guerrero, F. Lasagni, Topology optimization and additive manufacturing for aerospace components, *Prog. Addit. Manuf.* 4 (2019) 83–95. doi:10.1007/s40964-018-0061-3.
- [3] A. D. Cramer, V. J. Challis, A. P. Roberts, Physically Realizable Three-Dimensional Bone Prosthesis Design With Interpolated Microstructures, *J. Biomech. Eng.* 139. doi:10.1115/1.4035481.
- [4] N. A. Fleck, V. S. Deshpande, M. F. Ashby, Micro-architected materials: past, present and future, *Proc. R. Soc. A Math. Phys. Eng. Sci.* 466 (2010) 2495–2516. doi:10.1098/rspa.2010.0215.
- [5] P. Qiao, M. Yang, F. Bobaru, Impact Mechanics and High-Energy Absorbing Materials: Review, *J. Aerosp. Eng.* 21 (2008) 235–248. doi:10.1061/(ASCE)0893-1321(2008)21:4(235).
- [6] I. Maskery, A. Hussey, A. Panesar, A. Aremu, C. Tuck, I. Ashcroft, R. Hague, An investigation into reinforced and functionally graded lattice structures, *J. Cell. Plast.* 53 (2017) 151–165. doi:10.1177/0021955X16639035.
- [7] A. O. Aremu, J. P. J. Brennan-Craddock, A. Panesar, I. A. Ashcroft, R. J. M. Hague, R. D. Wildman, C. Tuck, A voxel-based method of constructing and skinning conformal and functionally graded lattice structures suitable for additive manufacturing, *Addit. Manuf.* 13 (2017) 1–13. doi:10.1016/j.addma.2016.10.006.
- [8] L. Cheng, X. Liang, E. Belski, X. Wang, J. M. Sietins, S. Ludwick, A. To, Natural Frequency Optimization of Variable-Density Additive Manufactured Lattice Structure: Theory and Experimental Validation, *J. Manuf. Sci. Eng.* 140. doi:10.1115/1.4040622.
- [9] P. Parandoush, D. Lin, A review on additive manufacturing of polymer-fiber composites (dec 2017). doi:10.1016/j.compstruct.2017.08.088.
- [10] Y. Sano, R. Matsuzaki, M. Ueda, A. Todoroki, Y. Hirano, 3D printing of discontinuous and continuous fibre composites using stereolithography, *Addit. Manuf.* 24 (2018) 521–527. doi:10.1016/j.addma.2018.10.033.
- [11] J. Plocher, A. Panesar, Review on design and structural optimisation in additive manufacturing: Towards next-generation lightweight structures, *Mater. & Des.* 183 (2019) 108164. doi:10.1016/j.matdes.2019.108164.
- [12] M. P. Bendsøe, N. Kikuchi, Generating optimal topologies in structural design using a homogenization method, *Comput. Methods Appl. Mech. Eng.* 71 (1988) 197–224. doi:10.1016/0045-7825(88)90086-2.
- [13] M. P. Bendsøe, Optimal shape design as a material distribution problem, *Struct. Optim.* 1 (1989) 193–202. doi:10.1007/BF01650949.

- [14] G. I. N. Rozvany, M. Zhou, T. Birker, Generalized shape optimization without homogenization, *Struct. Optim.* 4 (1992) 250–252. doi:10.1007/BF01742754.
- [15] M. Y. Wang, X. Wang, D. Guo, A level set method for structural topology optimization, *Comput. Methods Appl. Mech. Eng.* 192 (2003) 227–246. doi:10.1016/S0045-7825(02)00559-5.
- [16] G. Allaire, F. Jouve, A.-M. Toader, Structural optimization using sensitivity analysis and a level-set method, *J. Comput. Phys.* 194 (2004) 363–393. doi:10.1016/j.jcp.2003.09.032.
- [17] Y. M. Xie, G. P. Steven, A simple evolutionary procedure for structural optimization, *Comput. Struct.* 49 (1993) 885–896. doi:10.1016/0045-7949(93)90035-C.
- [18] G. I. N. Rozvany, A critical review of established methods of structural topology optimization, *Struct. Multidiscip. Optim.* 37 (2009) 217–237. doi:10.1007/s00158-007-0217-0.
- [19] N. P. Van Dijk, K. Maute, M. Langelaar, F. Van Keulen, Level-set methods for structural topology optimization: A review, *Struct. Multidiscip. Optim.* 48 (2013) 437–472. doi:10.1007/s00158-013-0912-y.
- [20] J. D. Deaton, R. V. Grandhi, A survey of structural and multidisciplinary continuum topology optimization: Post 2000, *Struct. Multidiscip. Optim.* 49 (2014) 1–38. doi:10.1007/s00158-013-0956-z.
- [21] J. S. Liu, G. T. Parks, P. J. Clarkson, Metamorphic Development: A new topology optimization method for continuum structures, *Struct. Multidiscip. Optim.* 20 (2000) 288–300. doi:10.1007/s001580050159.
- [22] C. Liu, Z. Du, W. Zhang, Y. Zhu, X. Guo, Additive Manufacturing-Oriented Design of Graded Lattice Structures Through Explicit Topology Optimization, *J. Appl. Mech.* 84. doi:10.1115/1.4036941.
- [23] H. Li, Z. Luo, M. Xiao, L. Gao, J. Gao, A new multiscale topology optimization method for multiphase composite structures of frequency response with level sets, *Comput. Methods Appl. Mech. Eng.* 356 (2019) 116–144. doi:10.1016/j.cma.2019.07.020.
- [24] M. P. Bendsoe, O. Sigmund, *Topology optimization: theory, methods, and applications*, Springer Science & Business Media, 2013.
- [25] H. Ghiasi, D. Pasini, L. Lessard, Optimum stacking sequence design of composite materials Part I: Constant stiffness design, *Compos. Struct.* 90 (2009) 1–11. doi:10.1016/j.compstruct.2009.01.006.
- [26] K. Sugiyama, R. Matsuzaki, A. V. Malakhov, A. N. Polilov, M. Ueda, A. Todoroki, Y. Hirano, 3D printing of optimized composites with variable fiber volume fraction and stiffness using continuous fiber, *Compos. Sci. Technol.* 186 (2020) 107905. doi:10.1016/j.compscitech.2019.107905.
- [27] A. V. Malakhov, A. N. Polilov, Design of composite structures reinforced curvilinear fibres using FEM, *Compos. Part A Appl. Sci. Manuf.* 87 (2016) 23–28. doi:10.1016/j.compositesa.2016.04.005.
- [28] J. Zhang, W.-H. Zhang, J.-H. Zhu, An extended stress-based method for orientation angle optimization of laminated composite structures, *Acta Mech. Sin.* 27 (2011) 977–985. doi:10.1007/s10409-011-0506-0.
- [29] Y. Xu, J. Zhu, Z. Wu, Y. Cao, Y. Zhao, W. Zhang, A review on the design of laminated composite structures: constant and variable stiffness design and topology optimization, *Adv. Compos. Hybrid Mater.* 1 (2018) 460–477. doi:10.1007/s42114-018-0032-7.
- [30] D. J. Munk, A bidirectional evolutionary structural optimization algorithm for mass minimization with multiple structural constraints, *International Journal for Numerical Methods in Engineering* 118 (2019) 93–120. doi:10.1002/nme.6005.
- [31] L. Xia, Q. Xia, X. Huang, Y. M. Xie, Bi-directional evolutionary structural optimization on advanced structures and materials: A comprehensive review, *Archives of Computational Methods in Engineering* 25 (2018) 437–478. doi:10.1007/s11831-016-9203-2.
- [32] Z. Wang, A. Sobey, A comparative review between Genetic Algorithm use in composite optimisation and the state-of-the-art in evolutionary computation, *Compos. Struct.* 233. doi:10.1016/j.compstruct.2019.111739.
- [33] O. Sigmund, On the usefulness of non-gradient approaches in topology optimization, *Struct. Multidiscip. Optim.* 43 (2011) 589–596. doi:10.1007/s00158-011-0638-7.
- [34] R. Sivapuram, R. Picelli, Y. M. Xie, Topology optimization of binary microstructures involving various non-volume constraints, *Computational Materials Science* 154 (2018) 405–425. doi:10.1016/j.commatsci.2018.08.008.
- [35] M. Bruyneel, C. Fleury, Composite structures optimization using sequential convex programming, *Adv. Eng. Softw.* 33 (2002) 697–711. doi:10.1016/S0965-9978(02)00053-4.
- [36] E. Lindgaard, E. Lund, Optimization formulations for the maximum nonlinear buckling load of composite structures, *Struct. Multidiscip. Optim.* 43 (2011) 631–646. doi:10.1007/s00158-010-0593-8.
- [37] J. Stegmann, E. Lund, Discrete material optimization of general composite shell structures, *Int. J. Numer. Methods Eng.* 62 (14) (2005) 2009–2027. doi:https://doi.org/10.1002/nme.1259.
- [38] J. Zowe, M. Kocvara, M. P. Bendsoe, Free material optimization via mathematical programming, *Math. Program.* 79 (1997) 445–466. doi:10.1007/BF02614328.
- [39] A. Ben-Tal, M. Kocvara, A. Nemirovski, J. Zowe, Free Material Design via Semidefinite Programming: The Multiload Case with Contact Conditions, *SIAM J. Optim.* 9 (1999) 813–832. doi:10.1137/s1052623497327994.
- [40] T. Nomura, A. Kawamoto, T. Kondoh, E. M. Dede, J. Lee, Y. Song, N. Kikuchi, Inverse design of structure and fiber orientation by means of topology optimization with tensor field variables, *Composites Part B: Engineering* 176 (2019) 107187. doi:10.1016/j.compositesb.2019.107187.
- [41] O. Hasançebi, S. Çarbas, M. P. Saka, Improving the performance of simulated annealing in structural optimization, *Struct. Multidiscip. Optim.* 41 (2010) 189–203. doi:10.1007/s00158-009-0418-9.
- [42] D. Reuschel, C. Mattheck, Three-dimensional fibre optimisation with computer aided internal optimisation, *Aeronaut. J.* 103 (1027) (1999) 415–420. doi:10.1017/S0001924000027962.
- [43] H. Voelkl, S. Wartzack, Design for composites: Tailor-made, bio-inspired topology optimization for fiber-reinforced plastics, *Proc. Int. Des. Conf. Des.* 1 (2018) 499–510. doi:10.21278/idc.2018.0126.
- [44] K. Svanberg, The method of moving asymptotes a new method for structural optimization, *Int. J. Numer. Methods Eng.* 24 (1987) 359–373. doi:10.1002/nme.1620240207.
- [45] P. D. Dunning, H. A. Kim, Introducing the sequential linear programming level-set method for topology optimization, *Structural and Multidisciplinary Optimization* 51 (2015) 631–643. doi:10.1007/s00158-014-1174-z.
- [46] A. G. M. Michell, Lxiii. the limits of economy of material in frame-structures, *The London, Edinburgh, and Dublin Philosophical Magazine and Journal of Science* 8 (47) (1904) 589–597.
- [47] P. Pedersen, On optimal orientation of orthotropic materials, *Struct. Optim.* 1 (1989) 101–106. doi:10.1007/BF01637666.
- [48] P. Pedersen, Bounds on elastic energy in solids of orthotropic materials, *Struct. Optim.* 2 (1990) 55–63. doi:10.1007/BF01743521.
- [49] P. Pedersen, On thickness and orientational design with orthotropic materials, *Struct. Optim.* 3 (1991) 69–78. doi:10.1007/BF01743275.
- [50] H. C. Cheng, N. Kikuchi, Z. D. Ma, An improved approach for determining the optimal orientation of orthotropic material, *Struct. Optim.* 8 (1994) 101–112. doi:10.1007/BF01743305.
- [51] M. Zhou, G. I. N. Rozvany, DCOC: An optimality criteria method for large systems part i: theory, *Structural optimization* 5 (1992) 12–25. doi:10.1007/BF01744690.
- [52] M. Zhou, G. I. Rozvany, DCOC: An optimality criteria method for large systems Part II: Algorithm, *Struct. Optim.* 6 (1993) 250–262. doi:10.1007/BF01743384.
- [53] K. Suzuki, N. Kikuchi, A homogenization method for shape and topology optimization, *Comput. Methods Appl. Mech. Eng.* 93 (3) (1991) 291–318. doi:10.1016/0045-7825(91)90245-2.
- [54] A. R. Díaz, M. P. Bendsoe, Shape optimization of structures for multiple loading conditions using a homogenization method, *Struct. Optim.* 4 (1992) 17–22. doi:10.1007/BF01894077.
- [55] H. C. Gea, J. H. Luo, On the stress-based and strain-based methods for predicting optimal orientation of orthotropic materials, *Struct. Multidiscip. Optim.* 26 (2004) 229–234. doi:10.1007/s00158-003-0348-x.
- [56] J. H. Luo, H. C. Gea, Optimal orientation of orthotropic materials using an energy based method, *Struct. Optim.* 15 (3-4) (1998) 230–236. doi:10.1007/BF01203536.
- [57] J. H. Luo, H. C. Gea, Optimal bead orientation of 3D shell/plate structures, *Finite Elem. Anal. Des.* 31 (1998) 55–71. doi:10.1016/S0168-874X(98)00048-1.
- [58] X. Yan, Q. Xu, H. Hua, D. Huang, X. Huang, Concurrent topology optimization of structures and orientation of anisotropic materials, *Eng.*

- Optim. 52 (9) (2020) 1598–1611. doi:10.1080/0305215X.2019.7001663186.
URL <https://doi.org/0305215X.2019.1663186>
- [59] Y. Shen, D. Branscomb, Orientation optimization in anisotropic materials using gradient descent method, *Compos. Struct.* 234 (2020) 111680. doi:10.1016/j.compstruct.2019.111680.
- [60] N. H. Kim, T. Dong, D. Weinberg, J. Dalidd, Generalized optimality criteria method for topology optimization, *Appl. Sci.* 11. doi:10.3390/app11073175.
- [61] M. Bruyneel, S. Zein, A modified Fast Marching Method for defining fiber placement trajectories over meshes, *Comput. & Struct.* 125 (2013) 45–52. doi:10.1016/j.compstruc.2013.04.015.
- [62] E. Lemaire, S. Zein, M. Bruyneel, Optimization of composite structures with curved fiber trajectories, *Compos. Struct.* 131 (2015) 895–904. doi:10.1016/j.compstruct.2015.06.040.
- [63] P. Hao, C. Liu, X. Liu, X. Yuan, B. Wang, G. Li, M. Dong, L. Chen, Isogeometric analysis and design of variable-stiffness aircraft panels with multiple cutouts by level set method, *Compos. Struct.* 206 (2018) 888–902. doi:10.1016/j.compstruct.2018.08.086.
- [64] H. Ghiasi, K. Fayazbakhsh, D. Pasini, L. Lessard, Optimum stacking sequence design of composite materials Part II: Variable stiffness design, *Compos. Struct.* 93 (2010) 1–13. doi:10.1016/j.compstruct.2010.06.001.
- [65] C. J. Brampton, K. C. Wu, H. A. Kim, New optimization method for steered fiber composites using the level set method, *Struct. Multidiscip. Optim.* 52 (2015) 493–505. doi:10.1007/s00158-015-1256-6.
- [66] V. S. Papadimitriou, C. Patel, A. Y. Tamijani, Stiffness-based optimization framework for the topology and fiber paths of continuous fiber composites, *Compos. Part B Eng.* 183 (2020) 107681. doi:10.1016/j.compositesb.2019.107681.
- [67] Y. Tian, S. Pu, T. Shi, Q. Xia, A parametric divergence-free vector field method for the optimization of composite structures with curvilinear fibers, *Comput. Methods Appl. Mech. Eng.* 373 (2021) 113574. doi:10.1016/j.cma.2020.113574.
- [68] M. P. Bendsøe, O. Sigmund, Material interpolation schemes in topology optimization, *Arch. Appl. Mech.* 69 (1999) 635–654. doi:10.1007/s004190050248.
- [69] L. Yin, G. K. Ananthasuresh, Topology optimization of compliant mechanisms with multiple materials using a peak function material interpolation scheme, *Struct. Multidiscip. Optim.* 23 (2001) 49–62. doi:10.1007/s00158-001-0165-z.
- [70] M. Bruyneel, SFPa new parameterization based on shape functions for optimal material selection: application to conventional composite plies, *Struct. Multidiscip. Optim.* 43 (2011) 17–27. doi:10.1007/s00158-010-0548-0.
- [71] T. Gao, W. Zhang, P. Duysinx, A bi-value coding parameterization scheme for the discrete optimal orientation design of the composite laminate, *Int. J. Numer. Methods Eng.* 91 (2012) 98–114. doi:<https://doi.org/10.1002/nme.4270>.
- [72] C. Y. Kiyono, E. C. N. Silva, J. N. Reddy, A novel fiber optimization method based on normal distribution function with continuously varying fiber path, *Compos. Struct.* 160 (2017) 503–515. doi:10.1016/j.compstruct.2016.10.064.
- [73] M. Arian Nik, K. Fayazbakhsh, D. Pasini, L. Lessard, Surrogate-based multi-objective optimization of a composite laminate with curvilinear fibers, *Compos. Struct.* 94 (2012) 2306–2313. doi:10.1016/j.compstruct.2012.03.021.
- [74] A. L. F. da Silva, R. A. Salas, E. C. N. Silva, Topology optimization of composite hyperelastic material using SPIMFO-method, *Meccanica* 56 (2) (2021) 417–437. doi:10.1007/s11012-020-01277-0.
- [75] R. A. Salas, F. J. Ramirez-Gil, W. Montealegre-Rubio, E. C. N. Silva, J. N. Reddy, Optimized dynamic design of laminated piezocomposite multi-entry actuators considering fiber orientation, *Comput. Methods Appl. Mech. Eng.* 335 (2018) 223–254. doi:10.1016/j.cma.2018.02.011.
- [76] Y. Luo, W. Chen, S. Liu, Q. Li, Y. Ma, A discrete-continuous parameterization (dcp) for concurrent optimization of structural topologies and continuous material orientations, *Composite Structures* 236 (2020) 111900.
- [77] T. Nomura, E. M. Dede, J. Lee, S. Yamasaki, T. Matsumori, A. Kawamoto, N. Kikuchi, General topology optimization method with continuous and discrete orientation design using isoparametric projection, *Int. J. Numer. Methods Eng.* 101 (2015) 571–605. doi:<https://doi.org/10.1002/nme.4799>.
- [78] Q. Xia, T. Shi, Optimization of composite structures with continuous spatial variation of fiber angle through Shepard interpolation, *Compos. Struct.* 182 (2017) 273–282. doi:10.1016/j.compstruct.2017.09.052.
- [79] Q. Xia, T. Shi, A cascading multilevel optimization algorithm for the design of composite structures with curvilinear fiber based on Shepard interpolation, *Compos. Struct.* 188 (2018) 209–219. doi:10.1016/j.compstruct.2018.01.013.
- [80] F. Fernandez, W. S. Compel, J. P. Lewicki, D. A. Tortorelli, Optimal design of fiber reinforced composite structures and their direct ink write fabrication, *Computer Methods in Applied Mechanics and Engineering* 353 (2019) 277–307. doi:10.1016/j.cma.2019.05.010.
- [81] D. Jiang, R. Hoglund, D. E. Smith, Continuous fiber angle topology optimization for polymer composite deposition additive manufacturing applications, *Fibers* 7 (2) (2019) 14.
- [82] A. Chandrasekhar, T. Kumar, K. Suresh, Build optimization of fiber-reinforced additively manufactured components, *Structural and Multidisciplinary Optimization* 61 (1) (2020) 77–90.
- [83] A. Desai, M. Mogra, S. Sridhara, K. Kumar, G. Sesha, G. K. Ananthasuresh, Topological-derivative-based design of stiff fiber-reinforced structures with optimally oriented continuous fibers, *Struct. Multidiscip. Optim.* 63 (2) (2021) 703–720. doi:10.1007/s00158-020-02721-1.
- [84] S. Setoodeh, M. M. Abdalla, Z. Gürdal, Combined topology and fiber path design of composite layers using cellular automata, *Struct. Multidiscip. Optim.* 30 (2005) 413–421. doi:10.1007/s00158-005-0528-y.
- [85] Y. Zhou, T. Nomura, K. Saitou, Multi-component topology and material orientation design of composite structures (MTO-C), *Comput. Methods Appl. Mech. Eng.* 342 (2018) 438–457. doi:10.1016/j.cma.2018.07.039.
- [86] T. Liu, S. Wang, B. Li, L. Gao, A level-set-based topology and shape optimization method for continuum structure under geometric constraints, *Struct. Multidiscip. Optim.* 50 (2) (2014) 253–273. doi:10.1007/s00158-014-1045-7.
- [87] I. Ferreira, M. Machado, F. Alves, A. Torres Marques, A review on fibre reinforced composite printing via FFF, *Rapid Prototyping Journal* 25 (2019) 972–988. doi:10.1108/RPJ-01-2019-0004.
- [88] Y. Chen, L. Ye, Topological design for 3D-printing of carbon fibre reinforced composite structural parts, *Compos. Sci. Technol.* 204 (2021) 108644. doi:10.1016/j.compscitech.2020.108644.
- [89] T. Wang, N. Li, G. Link, J. Jelonnek, J. Fleischer, J. Dittus, D. Kupzik, Load-dependent path planning method for 3d printing of continuous fiber reinforced plastics, *Composites Part A: Applied Science and Manufacturing* 140 (2021) 106181. doi:10.1016/j.compositesa.2020.106181.
- [90] J. Liu, H. Yu, Concurrent deposition path planning and structural topology optimization for additive manufacturing, *Rapid Prototyping Journal* 23 (2017) 930–942. doi:10.1108/RPJ-05-2016-0087.
- [91] M. P. Schmidt, L. Couret, C. Gout, C. B. Pedersen, Structural topology optimization with smoothly varying fiber orientations, *Struct. Multidiscip. Optim.* 62 (2020) 3105–3126. doi:10.1007/s00158-020-02657-6.
- [92] J. R. Kubalak, A. L. Wicks, C. B. Williams, Investigation of parameter spaces for topology optimization with three-dimensional orientation fields for multi-axis additive manufacturing, *Journal of Mechanical Design* 143. doi:10.1115/1.4048117.
- [93] B. Fedulov, A. Fedorenko, A. Khaziev, F. Antonov, Optimization of parts manufactured using continuous fiber three-dimensional printing technology, *Composites Part B: Engineering* 227 (2021) 109406. doi:10.1016/j.compositesb.2021.109406.