CIVILTECH CONSTRUCTION CHEMICALS
Sustainable Solutions

CIVILTECH CONSTRUCTION CHEMICALS LLP
H No.1-115/1/s.R/504-Flat No.504, 5th,Sri Rama Residency, White Fields Road, Hyderabad, Be Side Three Cube Tower, State Name : Telangana, Code : 36
Ph: +91 8978785341, Off: +91 9966643051
Email: mailtociviltech@gmail.com

TECHNICAL DATA SHEET

RockFix GP (Polyester Resin Jointing Mortar / Adhesive)

Product Description:

RockFix GP is a high-performance, unsaturated polyester resin-based jointing mortar formulated for precision segmental joints, structural bonding, and high-strength masonry applications. It combines General Purpose (GP) polyester resin with high-purity quartz fillers to provide excellent adhesion, durability, and chemical resistance.

Designed for joint applications (2mm–25 mm), it offers superior strength, low shrinkage, and fast curing compared to traditional cement mortars.

Composition & Mix Design:

Component	% by Weight
GP Polyester Resin	100%
MEKP Hardener	1-2%
Cobalt Octoate Accelerator	1-2%
Quartz / Filler/ Binders (0.1–0.6 mm)	150%
Optional Additives (Thixotropic / Flexibilizer / Pigment)	1–3%

Physical Properties (Cured Composite):

Property	Value / Range
Density	1.85 – 2.0 g/cm³
Compressive Strength	60 – 90 MPa
Flexural Strength	15 – 25 MPa
Tensile Strength	8 – 12 MPa
Bond Strength (to concrete/brick)	1.5 – 3.0 MPa
Water Absorption (24h)	< 0.5%
Shrinkage	0.05 – 0.15%
Pot Life (25°C)	10-15 minutes
Full Cure	24 hours
Hardness (Shore D)	80 – 85

CIVILTECH CONSTRUCTION CHEMICALS LLP Hyderabad

CIVILTECH CONSTRUCTION CHEMICALS
Sustainable Solutions

CIVILTECH CONSTRUCTION CHEMICALS LLP
H No.1-115/1/s.R/504-Flat No.504, 5th,Sri Rama Residency, White Fields Road, Hyderabad, Be Side Three Cube Tower, State Name : Telangana, Code : 36
Ph: +91 8978785341, Off: +91 9966643051
Email: mailtociviltech@gmail.com

Key Features & Advantages:

- High compressive and bond strength – ideal for precision joints.
- Low shrinkage and zero water requirement.
- Excellent adhesion to AAC blocks, concrete, and stone surfaces.
- Fast curing for early handling strength.
- Waterproof and chemical resistant – suitable for internal and external works.
- Superior dimensional stability and low thermal expansion.

Areas of Application:

- Segmental bridge joints and precast element bonding.
- AAC / concrete block jointing (thin-bed mortar).
- Stone and tile adhesive for structural applications.
- Industrial flooring repair and patching compound.
- Grouting and anchoring where fast cure and high strength are required.

Application Guidance:

1. Surfaces must be clean, dry, and free from dust, oil, or contaminants.
2. Mix GP resin with accelerator and hardener in the recommended ratio (1% each by weight of resin).
3. Add quartz filler gradually and mix thoroughly until a uniform mortar consistency is achieved.
4. Apply within 15–20 minutes of mixing; ensure proper alignment of joints.
5. Allow curing for 24 hours before full load application.

Packaging & Storage:

RockFix GP is supplied in 10 kg composite kits. Store in a cool, dry place below 30°C, away from direct sunlight. Shelf life: 18 months in sealed containers.

Safety Precautions:

- Avoid contact with skin and eyes; wear gloves and goggles during use.
- Use in well-ventilated areas.
- In case of contact, rinse immediately with clean water and seek medical advice.
- Refer to the Safety Data Sheet (SDS) for detailed information.

CIVILTECH CONSTRUCTION CHEMICALS LLP Hyderabad

END OF THE REPORT