



CIVILTECH CONSTRUCTION
CHEMICALS

Sustainable Solutions

GALAXY MEP

TWO COMPONENT MULTI PURPOSE EPOXY PUTTY/ CONCRETE CRACK FILLER

TWO COMPONENT MULTI PURPOSE EPOXY PUTTY/ CONCRETE CRACK FILLER



Galaxy MEP is a solvent free two-pack adhesive system based on specially selected epoxy resin and hardener, yielding high strength material. Galaxy MEP is in pasty or thixotropic consistency finds an easy application as Expansion joint Tape adhesive, Concrete crack filler or structural repairs. Galaxy MEP also complies with the performance criteria recommended by the FIP as epoxy bonding agent for segmental construction and also complies with ASTM C881 on epoxy bonding agents.

USES:

GALAXY MEP is most suitable as bonding medium in the assembly of concrete segmental units and segmental bridge construction. It also finds application in crack and surface sealing, concrete repairs, rehabilitation and carbon fiber wrapping for surface reinforcing of distress concrete structures. GALAXY MEP can be used for bonding additional reinforcement as structural adhesive between concrete and steel or fresh concrete. By doing so, the load bearing capacity or structural strength of a reinforced concrete structure can be enhanced. GALAXY MEP remains unaffected by the high moisture content of the fresh concrete.

FEATURES

- Packing comes in 2:1 ratio.
- Simple dosing ratio in terms of packs.
- Easy to mix even at low temperature.
- NON-SAG; suitable for use on dry and damp surfaces.
- Thick non-drip consistency at high temperature.
- Non-Shrinking material.
- Excellent squeezability.
- High early strength according to the grade used.
- Superb adhesion with concrete and many other substrates.
- High quality product under rigid quality control system.
- Applicable for wide range of temperature (5°C to 45°C)



CIVILTECH CONSTRUCTION CHEMICALS

Sustainable Solutions

APPLICATION

All surfaces should be clean, free from stagnant water, cement laitance and loosely adhering particles. NO PRIMER IS REQUIRED. Mix Pack 'B' with Pack 'A' with a manual mixing for at least three minutes or till uniform colour results. Mixed material is used by trowel or spatula over the surface. Material should be well rubbed over the application surface. Maximum thickness in one horizontal layer may be upto 30mm and on vertical surfaces, the built-up thickness may be upto 12mm.

Technical Information

Compressive Strength	≥ 55 MPa 7 days @ +30 °C	ASTM C881
Tensile Strength	~ 18-20 MPa 14 days @ +30 °C	ISO 527
Shear Strength	≥ 10 MPa 14 days @ +30 °C	ASTM C882

APPLICATION INFORMATION

Mixing Ratio Part A : Part B = 2 : 1 by weight

Consumption	~ 0.3-0.5 kg/m ² , depending on substrate condition.
Ambient Air Temperature	+25 °C min. / +40 °C max.
Substrate Temperature	+25 °C min. / +40 °C max.
Substrate Moisture Content	When applied to mat moisture concrete, brush the adhesive well into substrate.
Pot Life	4 hours @ +30 °C FIP 5.1
The pot life begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the pot life. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C). Open Time 7 hours @ +30 °C	

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.



**CIVILTECH CONSTRUCTION
CHEMICALS**

Sustainable Solutions

GALAXY FLEXI TAPE

FLEXXIBLE THERMO PLASTIC EXPANSION JOINT TAPE

DESCRIPTION

Galaxy Flexitape is a flexible waterproofing tape based on modified flexible thermo plastic elastomers with advanced adhesion properties. Thickness 1.5 mm the product is part of the Galaxy Expansion Joint System which includes Galaxy MEP as its adhesive in protecting the expansion joints for a durable time.

USES:

- Sealing all types of joints and cracks in many different structures and applications including:
- Tunnels and culverts
- Hydroelectric power plants
- Sewage treatment plants
- Basements
- Water retaining structures
- Drinking water reservoirs
- Sealing of Construction joints
- Cracks

PROPIERTIES	Unit	Test method	Galaxy FlexiTape
Thickness	mm	EN 1849-2	1.2
Mass per unit area	Kg/m ²	EN 1849-2	1.5
Water tightness		EN 1928 (B)	Pass
Tensile strength to Break	N/5cm	EN 12311-2 (A)	≥ 1100
Elongation to Break	%	EN 12311-2 (A)	≥ 15
Impact resistance	mm	EN 12691 (A)	≥ 450
Static puncture resistance	kg	EN 12730	≥ 20
Tear resistance	N	EN 12310-2	≥ 200
Joint peel resistance	N/50 mm	EN 12316-2	≥ 200
Joint shear resistance	N/50 mm	EN 12317-2	> 600
Foldability at low temperatures	°C	EN 495-5	≤ - 25
Root resistance		EN 13948	Pass
Artificial aging due to prolonged exposure to UV radiation high temperatures and water	Visual (1000h)	EN 1297	Pass
Dimension stability	%	EN 1107-2	≤ 0.5
Water vapor transmission properties	μ	EN 1931	20000



**CIVILTECH CONSTRUCTION
CHEMICALS**

Sustainable Solutions

CHARACTERISTICS / ADVANTAGES

- Advanced adhesion, no activation on site required
- Highly flexible - high crack and joint bridging ability
- Good chemical resistance
- Good resistance to ageing
- Resistant to UV exposure
- Resistant to root penetration
- Performs well within a wide range of temperatures ☐
- Plasticizer-free
- Hot air weld able
- Can be used in contact with potable/drinking water

PRODUCT INFORMATION

Chemical Base:	Modified modified flexible thermo plastic elastomers
Packaging:	1 roll of 25 Mtr lengths (Refer to price list for packaging variations)
Appearance / Colour:	Flexible light grey membrane
Effective Thickness:	1.2 mm (-5 % / +10 %)
Mass per Unit Area:	1250 g/m ² (-5 % / +10 %) (EN 1850-2)
Width:	10, 15, 20, 25, 30, 40, 50, 100, 200 cm Length 25 m roll
Shelf Life:	36 months from date of production

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.



**CIVILTECH CONSTRUCTION
CHEMICALS**

Sustainable Solutions

POLY-BOND 2K

Two Component Polymeric Cementitious
Waterproof Coating

Uses: POLY-BOND 2K is a high performance elastomeric cementitious coating used for waterproofing and to protect atmospherically exposed reinforced concrete structures from attack by acid gases, chloride ions, oxygen & water.

Poly-bond 2k is suitable for all types of structures including those in coastal environments.

The product can be used on concrete, brick and blockwork substrates and is equally suitable for new and existing structures and is designed to reface and even out variations in concrete and masonry surfaces and bridge shrinkage cracks.

It provides a seamless, flexible waterproof coating suitable for water tanks, reservoirs, drainage culverts basements, roofs, toilets & wet areas.

The product provides a tough and durable water resistant coating which can withstand light foot traffic and also has excellent weather resistance for exterior applications.



Advantages

- Excellent barrier to carbon dioxide, chloride and sulphate ions.
- Allows water vapour to escape from the structure.
- Waterproof-suitable for water retaining structures.
- High resistance to the effect of long-term weathering, durable in all climate conditions including UV attack.
- Non toxic - ideal for potable water tanks.
- Flexible, with thermal expansion similar to concrete.
- Excellent bond to concrete and masonry.
- Good crack accommodation capacity.
- Minimum surface preparation needed and low labour costs.

Application Instructions

Surface Preparation

All surfaces which are to receive the coating must be free from oil, laitance, grease, wax, dirt or any other form of foreign matter which might affect adhesion. Typically concrete surfaces can be cleaned using high pressure water jet or grit blasting or by proper wire brushing or mechanical grinding to achieve proper adhesion between the concrete surface and coatings.

Spalled surfaces or those containing large blow holes, cracks and other such defects should be repaired using polymer concrete repair mortars. For further advice on suitable repair mortars, contact the local application engineer.

Mixing

POLY-BOND 2K liquid concentrate should be poured into a plastic container or metal drum. Clean fresh water is added in the proportions shown below and mixing commenced with a propeller agitator attached to a slow speed drill (500rpm). The powder component should be added gradually to the liquid to avoid lump formation and mixed for 2-4 minutes. Poly-Bond 2k should be immediately used after mixing. Do not mix more material than can be used within the pot life. Keep stirring the mixture during the application

Application

For best results, surfaces should be damp. In order to obtain the protective properties. Apply Poly-bond 2k in 2 coats to achieve 1mm thickness. The second coat shall be applied as soon as the first coat has

reached touch dry state. It is recommended that for general surfacing Poly-Bond 2k should be applied at a minimum thickness of 1mm. Areas subjected to moderate and heavy loads/hydrostatic pressure, minimum 2mm thickness coating is recommended with screed above.

Cleaning Poly Bond 2k should be removed from tools and equipment with clean water immediately after use. Hardened material can only be removed mechanically. Estimating Packing Powder component : Part A 17kg Liquid polymer component : Part B 5kg (3Kg water used) Coverage This depends on the required consistency. The approximate coverage per pack at even consistency (1mm thickness) is as follows Consistency Brush application Coverage (Part A+B+3Kg water) 20SQM (Approx)	Shelf life 12 months in unopened packs if kept in a dry store. Precautions Health and Safety instruction Poly-Bond 2k is non-toxic but alkaline in nature. Gloves and goggles should be worn. Any splashes to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, seek medical advice. Use a dust mask while handling the powder. Fire Poly-Bond 2k components are non inflammable. Mock up It is advised that a mock up trial is made and signing off with applicator is mandatory to proceed with actual work.
--	---

CIVILTECH CONSTRUCTION CHEMICALS INDIA PVT. LTD.

Plot No. 125/126, Sardar Patel Colony, Trimulgherry, Secunderabad-500 015.
Ph: +91 8978785341, Off: +91 8978645341 Email: mailtociviltech@gmail.com



**CIVILTECH CONSTRUCTION
CHEMICALS**
Sustainable Solutions

POLYBOND FLEXICOAT

HEAVY DUTY REINFORCED ELASTOMERIC WATERPROOF COATING FOR TERRACE

PRODUCT DESCRIPTION

POLYBOND FLEXICOAT is a specially formulated heavy duty terrace waterproofing system, composed of specially developed highly elastic and durable acrylic polymers, graded fillers, pigments, micro-fibers, additives and best quality fungicidal in water medium. It is used as a liquid applied waterproofing membrane for all types of building terraces. Polybond Flexicoat is a three layered system and the coats are available in variety of colours.

Standards:

It confirms ASTM D412 : 2002, ASTM D 2240 : 2002, ASTM D 2240 : 2002, ASTM C 836 : 1995, ASTM C 1202 : 1997, BS EN 12390, ASTM D 4541 : 2002, ASTM C 836 : 1995 and ASTM E 96 : 2000, AS/NZS 4859 : 1: 2002

PRODUCT PROPERTIES	POLYBOND FLEXICOAT	STANDARDS
Solid Content %	70	-
Dry Film Thickness Per 3 Coat, Mm	1 To 1.25	-
Elongation At Break %	300	ASTM D 412 :2002
Hardness (Shore A)	80	ASTM D 2240 : 2002
Crack Bridging	A) No Cracks Upto 2mm Width	
	B) No Cracks Upto 1mm (10 Cycles)	
Weathering (1000 Hours)	No Cracking, Chalking And Discoloration	-
Rapid Chloride Permeability	Very Low	ASTM C 1202 : 1997
Water Permeability (Depth Of Penetration At 5 Bar Pressure)	6	BS EN 12390
Tensile Strength , N/Mm ²	2.6	ASTM D 412 : 2002
ADHESION STRENGTH, N/Mm ²	0.9	ASTM D 4541 : 2002
UV Resistant – Accelerated	Excellent	-
Algae and Fungus Resistant	No Growth	ASTM C 836 : 1995
Water Vapour Transmission	19 g/m ² /day	ASTM E 96 : 2000
Thermal Insulation	2-5° C	AS/NZS 4859 : 1 : 2002



CIVILTECH CONSTRUCTION
CHEMICALS
Sustainable Solutions

ADVANTAGES

- Suitable for flat as well as sloping roofs
- Higher tear resistance and bond strength
- It is breathable and provides high resistance to abrasion
- Easily applicable by brush or roller
- High elongation and recovery for durable performance over dynamic cracks up to 2mm.
- Excellent UV resistance provides colour retention for long lasting attractive finish

AREA OF APPLICATION:

- Building roofs or terraces-Flat and sloping
- Overexisting cementitious waterproofing treatments like brickbat coba, concrete screeds, acrylic coatings, etc.

➤ APPLICATION METHODOLOGY

Surface Preparation:

- Surface for treatments must be thoroughly cleaned of all laitance, loose material, oils, grease, algal growth, etc.
- Mechanical means such as wirebrushing, sandblasting can be used and finally vacuum cleaned of all loose solids and liquids. Where moss, algae or similar growths have occurred, proper treatment should be carried out. Visible cracks should be first treated with POLYBOND SBR.

➤ Application:

- Dilute PolyBond FlexiCoat with 40 to 50% water and use it as a primer.
- Allow to dry it for 5 to 6 hrs.
- All prime substrates should be treated with three coats of PolyBond FlexiCoat with time gap of 6 hours between each coat.
- Allow coated surface to air cure fully for 7 days.
-

➤ THEORETICAL COVERAGE

- 2.5 sq. meter/liter/coat.

➤ HEALTH AND SAFETY

- Use mask and hand gloves during application. Clean hands with soap water after application. Avoid contact with skin/eyes. In case of accidental contact with eyes, rinse immediately with plenty of clean water and seek medical



**CIVILTECH CONSTRUCTION
CHEMICALS**
Sustainable Solutions

advice. Do not use solvent to clean the contacted area. If swallowed accidentally, contact a physician and avoid inducing vomiting.

➤

➤ **PACKAGING**

➤ Available in 10 Liter and 20 Liter container.

➤

➤

➤ **STORAGE AND SHELF LIFE**

➤ 12 months from the date of manufacturing in unopened airtight condition.

➤ Store in cool and dry place under shade away from direct sunlight and heat.



CIVILTECH CONSTRUCTION CHEMICALS INDIA PVT. LTD.

Plot No. 125/126, Sardar Patel Colony, Trimulgherry, Secunderabad-500 015.
Ph: +91 8978785341, Off: +91 8978645341 Email: mailtociviltech@gmail.com



CIVILTECH CONSTRUCTION
CHEMICALS
Sustainable Solutions

POLYBOND SBR™ **MULTIPURPOSE SBR LATEX FOR REPAIR, BONDING AND WATERPROOFING**

PRODUCT DESCRIPTION

POLYBOND SBR is a single component speciality Styrene Butadiene Latex synthetic rubber emulsion which can be used in cementitious formulation for repair of mortar, damaged concrete, flooring, bonding and waterproofing and other concrete modification purposes. It improves elasticity, flexibility, tensile strength of cement and reduces cracking there by making the mortar waterproof and reducing susceptibility to acids and gases, salt penetration etc. It reduces viscosity of cement injection grout and improves bond cured injected material with substrates.

Appearance	Milky white pourable liquid
Emulsifying System	Synthetic anionic and nonionic
Total Solids (%)	48 ± 2
pH at 25 °C	9.5 ± 0.5
Viscosity LVF (CPS) SP.1,12 RPM at 25 °C	80 - 300
Surface Tension (Dynes/cm) at 25 °C	40 ± 5
Specific Gravity	1.023 ± 0.005
Dilutability with water	Can be diluted in any proportion
Compatibility	Compatible with Cement and Concrete mixture
Coverage	0.5 kg / sqm ²

AREA OF APPLICATION

POLYBOND SBR is used for modification of hydraulic binders in common applications like repair mortar, flooring, rendering, bonding, mineral sealing slurries and as cement based adhesives

For waterproofing of roof slabs, sunken slabs, basements, water tanks, sunshades etc in combination with cement

As a bonding agent for used in repair and plastering

For making polymer mortar for repairs etc

Treatment for leaching and salt penetration

Multipurpose mortar admixture for injection grouts

ADVANTAGES

Provides excellent water impermeability

Good workability at reduced water/cement ratio

Improved bonding and adhesion to substrates

Superior toughness and flexibility

Can be applied in thinner sections

Improved abrasion resistant flooring

Highly durable waterproof cementitious system against UV



CIVILTECH CONSTRUCTION
CHEMICALS
Sustainable Solutions

APPLICATION METHODOLOGY

SURFACE PREPARATION: Surface should be clean and free from dust, oil and grease and should be saturated surface dry. **MIX PROPORTIONS:** Mix **POLYBOND SBR** in the following ration and proportions as per the applications.

Repair / Patch mortar - 5% to the total value of cement sand mortar.

Bonding Agent - 15 % to the total value of cement sand mortar. **Corrosion Protection**

Slurry - In a ration 1:2 to cement.

Injection Grouting - 25 % to the total value of cement.

PACKAGING

Available in 1kg and 5kg PVC container

STORAGE

Store the material in cool and dry place.

Shelf Life is 1 year in unopened containers



CIVILTECH CONSTRUCTION CHEMICALS INDIA PVT. LTD.

Plot No. 125/126, Sardar Patel Colony, Trimulgherry, Secunderabad-500 015.
Ph: +91 8978785341, Off: +91 8978645341 Email: mailtociviltech@gmail.com