



**CIVILTECH CONSTRUCTION
CHEMICALS**

Sustainable Solutions

POLY-BOND 2K

Two Component Polymeric Cementitious
Waterproof Coating

Uses: POLY-BOND 2K is a high performance elastomeric cementitious coating used for waterproofing and to protect atmospherically exposed reinforced concrete structures from attack by acid gases, chloride ions, oxygen & water.

Poly-bond 2k is suitable for all types of structures including those in coastal environments.

The product can be used on concrete, brick and blockwork substrates and is equally suitable for new and existing structures and is designed to reface and even out variations in concrete and masonry surfaces and bridge shrinkage cracks.

It provides a seamless, flexible waterproof coating suitable for water tanks, reservoirs, drainage culverts basements, roofs, toilets & wet areas.

The product provides a tough and durable water resistant coating which can withstand light foot traffic and also has excellent weather resistance for exterior applications.



Advantages

- Excellent barrier to carbon dioxide, chloride and sulphate ions.
- Allows water vapour to escape from the structure.
- Waterproof-suitable for water retaining structures.
- High resistance to the effect of long-term weathering, durable in all climate conditions including UV attack.
- Non toxic - ideal for potable water tanks.
- Flexible, with thermal expansion similar to concrete.
- Excellent bond to concrete and masonry.
- Good crack accommodation capacity.
- Minimum surface preparation needed and low labour costs.

Application Instructions

Surface Preparation

All surfaces which are to receive the coating must be free from oil, laitance, grease, wax, dirt or any other form of foreign matter which might affect adhesion. Typically concrete surfaces can be cleaned using high pressure water jet or grit blasting or by proper wire brushing or mechanical grinding to achieve proper adhesion between the concrete surface and coatings.

Spalled surfaces or those containing large blow holes, cracks and other such defects should be repaired using polymer concrete repair mortars. For further advice on suitable repair mortars, contact the local application engineer.

Mixing

POLY-BOND 2K liquid concentrate should be poured into a plastic container or metal drum. Clean fresh water is added in the proportions shown below and mixing commenced with a propeller agitator attached to a slow speed drill (500rpm). The powder component should be added gradually to the liquid to avoid lump formation and mixed for 2-4 minutes. Poly-Bond 2k should be immediately used after mixing. Do not mix more material than can be used within the pot life. Keep stirring the mixture during the application

Application

For best results, surfaces should be damp. In order to obtain the protective properties. Apply Poly-bond 2k in 2 coats to achieve 1mm thickness. The second coat shall be applied as soon as the first coat has

reached touch dry state. It is recommended that for general surfacing Poly-Bond 2k should be applied at a minimum thickness of 1mm. Areas subjected to moderate and heavy loads/hydrostatic pressure, minimum 2mm thickness coating is recommended with screed above.

Cleaning Poly Bond 2k should be removed from tools and equipment with clean water immediately after use. Hardened material can only be removed mechanically. Estimating Packing Powder component : Part A 17kg Liquid polymer component : Part B 5kg (3Kg water used) Coverage This depends on the required consistency. The approximate coverage per pack at even consistency (1mm thickness) is as follows Consistency Brush application Coverage (Part A+B+3Kg water) 20SQM (Approx)	Shelf life 12 months in unopened packs if kept in a dry store. Precautions Health and Safety instruction Poly-Bond 2k is non-toxic but alkaline in nature. Gloves and goggles should be worn. Any splashes to the skin or eyes should be washed off with clean water. In the event of prolonged irritation, seek medical advice. Use a dust mask while handling the powder. Fire Poly-Bond 2k components are non inflammable. Mock up It is advised that a mock up trial is made and signing off with applicator is mandatory to proceed with actual work.
---	---

CIVILTECH CONSTRUCTION CHEMICALS INDIA PVT. LTD.

Plot No. 125/126, Sardar Patel Colony, Trimulgherry, Secunderabad-500 015.
Ph: +91 8978785341, Off: +91 8978645341 Email: mailtociviltech@gmail.com