CIVILTECH CONSTRUCTION CHEMICALS
Sustainable Solutions

POLYBOND FLEXICOAT

HEAVY DUTY REINFORCED ELASTOMERIC WATERPROOF COATING FOR TERRACE

PRODUCT DESCRIPTION

POLYBOND FLEXICOAT is a specially formulated heay duty terrace waterproofing system, composed of specially developed highly elastic and durable acryli polymers, graded fillers, pigments, micro-fibers, additives and best quality fungicidal in water medium. It is used as a liuid applied waterproofing membrane for all types of building terraces. Polybond Flexicoat is a three layered system and the coats are available in variety of colours.

Standards:

It confirms ASTM D412 : 2002, ASTM D 2240 : 2002, ASTM D 2240 : 2002, ASTM C 836 : 1995, ASTM C 1202 : 1997, BS EN 12390, ASTM D 4541 : 2002, ASTM C 836 : 1995 and ASTM E 96 : 2000, AS/NZS 4859 : 1: 2002

PRODUCT PROPERTIES	POLYBOND FLEXICOAT	STANDARDS
Solid Content %	70	-
Dry Film Thickness Per 3 Coat, Mm	1 To 1.25	-
Elongation At Break %	300	ASTM D 412 :2002
Hardness (Shore A)	80	ASTM D 2240 : 2002
Crack Bridging	A) No Cracks Upto 2mm Width	
	B) No Cracks Upto 1mm (10 Cycles)	
Weathering (1000 Hours)	No Cracking, Chalking And Discoloration	-
Rapid Chloride Permeability	Very Low	ASTM C 1202 : 1997
Water Permeability (Depth Of Penetration At 5 Bar Pressure)	6	BS EN 12390
Tensile Strength , N/Mm^2	2.6	ASTM D 412 : 2002
ADHESION STRENGTH, N/Mm^2	0.9	ASTM D 4541 : 2002
UV Resistant – Accelerated	Excellent	-
Algae and Fungus Resistant	No Growth	ASTM C 836 : 1995
Water Vapour Transmission	19 $g/m^2/day$	ASTM E 96 : 2000
Thermal Insulation	2-5° C	AS/NZS 4859 : 1 : 2002

ADVANTAGES

- Suitable for flat as well as sloping roofs
- Higher tear resistance and bond strength
- It is breathable and provides high resistant to abrasion
- Easily applicable by brush or roller
- High elongation and recovery for durable performance over dynamic cracks upto 2mm.
- Excellent UV resistance provides colour retention for long lasting attractive finish

AREA OF APPLICATION:

- Building roofs or terraces-Flatandsloping
- Overexisting cementitious waterproofing treatments like brickbat coba, concrete screeds, acrylic coatings,etc.

APPLICATION METHODOLOGY

Surface Preparation:

- Surface for treatments must be thoroughly cleaned of all Laitance, loose material, oils, grease, algal growth ,etc.
- Mechanical means such as wirebrushing, sandblasting can be used and finally vacuum cleaned of all loose solids and liquids. Were moss , algae or similar growths have occurred, proper treatment should be carried out. Visible cracks should be first treated with POLYBOND SBR.

- Application:
- Dilute PolyBond FlexiCoat with 40to50% water and use it as a primer.
- Allow to dry it for 5to6hrs.
- All prime substrates should be treated with three coats of PolyBond FlexiCoat with time gap of 6hours between eachcoat.
- Allow coated surface to air cure fully for 7 days.
-

- THEORETICAL COVERAGE
- 2.5sq.meter/liter/coat.

- HEALTH AND SAFETY
- Use mask and hand gloves during application. Clean hands with soap water after application. Avoid contact with skin/eyes. Incase of accidental contact with eyes, rinse immediately with plenty of clean water and seek medical

advice. Do notuse solvent to clean the contacted area. If swallowed accidentally, contact a physician and avoid inducing vomiting.

-

- **PACKAGING**
- **Available in 10Liter and 20 Liter container.**
-
-

- **STORAGEAND SHELF LIFE**
- **12months from the date of manufacturing in unopened airtight condition.**
- **Store in cool and dryplace under shade away from direct sunlight and heat.**

CIVILTECH CONSTRUCTION CHEMICALS INDIA PVT. LTD.
Plot No. 125/126, Sardar Patel Colony, Trimulgherry, Secunderabad-500 015.
Ph: +91 8978785341, Off: +91 8978645341 **Email: mailtociviltech@gmail.com**