Fabric Test Results
布料测试结果

PASS

Form # : Lab VF 005

SATRA Accredited Laboratory No.18823

ETRF.No: TR202510267585

Lab Ref.No: DTP20251008FBU-1

Supplier/Factory(厂商):	TSAN CHEN
Supplier's country(国家):	CHINA
Material Description(材料):	36" White11-4300TPG TS164205 Woven Canvas
Color (颜色):	DUCK CANVAS MARSHMALLOW
Model No./Style(型体):	VN0007QZCD3/UA LX AUTHENTIC REISSUE 44 /
P.O/Lot No(订单):	IB0437-00018/VSP25080364 /
Quantity(数量):	239
Send by (提供方):	

◉ Prod.Material量产材料 ○ Prod Re-test量产重测

O New/Development 开发段新材料

o Tech 1 o Tech 2 o Tech 3 o Tech 4

O Sales Sample (销售样品)

Received Date (收到日期):	2025/10/13
Tested Date (测试时间):	2025/10/14
Finished Date (完成时间):	2025/10/20
Technician (技术人员):	JESS/KATH/SHAI

Test Items 测试项目	VF Test Method	Units 单位	Test Results 测试结果	Max/Min 最大/小值	Average 平均值	Standard 标准	Tolerance 容许量	Rating 等级
Gauge 规格	VF-A03 (2014/04)	mm	0.59 0.6 0.59 0.6 0.6 0.6	0.6 / 0.59	0.6	Refer to specification		P
Weight 重量	VF-A02 (2018/11)	g/m²	323 318.1 327.1		322.73	Refer to specification		P
Yarn Count 经纬密度	VF-A07 (2008/05)	# of yarns	Warp :			Refer to specification		
			Welf :					
Tensile 抗拉	VF-B01 (2022/11)	kgf/cm	L= 26.96 38.22 41.16		35.45	6		P
			W= 19.28 14.54 17.39		17.07	6		P
Elongation 延伸	VF-B01 (2022/11)	%	L= 10.19 10.84 14.54		11.86	10		P
			W= 10.25 10.2 10.19		10.21	10		P
Trouser Tear - 裤形撕裂	VF-B07 (2022/11)	kgf	L= 2.1 2.4 2.2		2.23	2		P
			W= 2.9 2.2 2.9		2.67	2		P
Stitch tear 车缝撕裂	VF-B08 (2019/05)	kgf/cm	L= 16.658 14.555 16.091		15.77	3		P
			W= 9.899 11.775 12.171		11.28	3		P
Bally Flex Bally 耐挠	VF-D01 (2019/06)	cycles	Dry干 : L1: L2:					
			Dry干 : W1: W2:					
			Wet湿 : L1: L2:					
			Wet湿 : W1: W2:					
			After hydrolysis水解 : L1: L2:					
			After hydrolysis水解 : W1: W2:					
Martindale Abrasion Martindale 耐磨	VF-C04 (2024/12)	cycles	Dry=Fabric:1. 2.					
			Dry=Ink 1. 2.					
			Wet=Fabric:1. 2.					
			Wet=Ink: 1. 2.					
Taber Abrasion Taber 耐磨 CS-17,500g	VF-C05 (2024/12)	cycles						
Mullen Burst 爆破	VF-B02 (2019/05)	kgf/cm²	11.83 10.38 12.71		11.64	10		P
Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面)	VF-E16 (2018/11)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维			3.5		
Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面)	VF-E01 (2008/05)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维			3.5		
UV Light紫线 (24hrs, 50℃)	VF-E03 (2019/05)	AATCC	5 5			3		P
Colorfastness to Crocking 摩擦褪色	VF-E02 (2024/08)	AATCC	Dry干 =			3.5		
			Wet湿 =			3		
Abrasion Crocking 摩擦	VF-E02 (2024/08)		Dry干 =					
			Wet湿 =					
Ink adhesion on Substrate 3M Stotch tape # 600	VF-F05 (2014/07)		Dry干 =					
			Wet湿 =					
Reaction with solvents 溶液反应	VF-I03 (2012/08)		Acetone 丙酮: Ethyl Acetate 乙酸乙酯: MEK 丁酮 :					
Peeling Strength 剥离强度	VF-F03 (2024/12)	kgf/cm						
Wicking 虹吸	VF-E14 (2014/07)	mm						
Maeser Test Maeser防水测试	VF-E11 (2018/11)	cycles						
Glow in the dark	VF-E28 (2024/08)							
Heat Aging 热老化 (72hrs 70℃)	VF-E04 (2022/09)		5 5			4		P
Hydrolysis 水解 (7Days,60℃ 95%RH)	VF-E19 (2024/12)							P

Comments 备注:

Reviewed by 审查: KATE GOLDBERG LABORATORY SUPERVISOR

Approved by 核准: KATE GOLDBERG LABORATORY SUPERVISOR