

Air-circulating oven, capable of maintaining temperature of 60 +/-1C and relative humidity at 95+/- 1%.
Water for oven must be distill water



Place the test material in an oven at 60 ± 1oC for 7 days at 95 ± 1 % relative humidity



After 7 days, remove the test material from the oven. Remove the specimen from the oven, and let it cool for 24 hours at 23+/-2oC and 55+/-10% relative humidity.



Check change of appearance – shrinkage, blooming, color change, ink migration,



Check delamination of components.



Check the corrosion of metal parts.



Compare the color of the darkest portion of the uncovered area of the test sample to the AATCC Chromatic Transference Scale and rate to the nearest 0.5.
Chromatic Transference Scales must be replaced at least every 24 months.

Prepared by	Approved by	REVISION		DATE	