VF Asia Footwear Laboratory Testing Manual

Test Method for Yarn Count	Test method # VF-A07 Page 1 of 1
Date Issued : May 27, 2008 Revision # :	Created by : Nila Babia Erazo

PURPOSE AND SCOPE: To measure the number of warp yarns (ends) and filling yarns (picks) per unit length of fabric test material.

REFERENCES: ASTM D3775

EQUIPMENT AND MATERIAL:

1. Linen tester (incremented magnifying glass with or without a movable pointer) or microscope with an incremented scale.
2. Steel scale , capable of measuring to 0.5 m
3. Woven and knitted fabrics.

SAMPLE PREPARATION:

The test material should be at least 30 cm by 30 cm.

REPETITIONS: Take two measurements for each of the warp and the filling (weft) yarns. Two measurements must be at least ten (10) cm apart from each other, such that the same warp or filling yarns are not being counted, and no closer that 10 cm from any edge.

TEST PROCEDURE:

Test should be conducted at standard laboratory environment @ 23.0±2.0˚C temperature and 55 ±10 % Relative Humidity.

1. Place the test fabric on flat, stable, horizontal surface, such that the fabric has zero tension and no folds or wrinkles.
2. Count the number of warps and filling yarns (weft) per 2.54 cm , using one of the following techniques:
    a) Using a linen tester visually count the number of yarns.
    b) Using a microscope visually count the number of yarns.
    c) For fabrics in which individual yarns cannot be readily visually distinguished for counting, unravel a piece of fabric parallel to the direction to be counted to obtain a straight edge. Then manually unravel and count the yarns over a 2.54 cm length.

REPORT: The average of the two measurements to the nearest one (1) yarn -always round off.