VF Asia Footwear Laboratory Testing Manual

Test Method for Courtauld Yellowing Test	Test method # VF- E07 Page 1 of 1
Date Issued : May 27, 2008 Revision # :	Created by : Nila Babia Erazo/

PURPOSE AND SCOPE: To determine the discoloration of yarns or fabrics caused by the action of oxides or nitrogen on yellowable phenols.

REFERENCE: SOP 25

EQUIPMENT AND MATERIAL:

1. Courtauld Test equipment kit
2. Light colored Textile

SAMPLE PREPARATION:

1. Condition the sample for at least 24 hours at standard laboratory environment at 23.0±2.0 ˚C temperature and 55 ±10 % Relative Humidity.
2. Die or hand cut the test sample 50 mm width x 75 mm long

REPETITIONS: Test two (2) samples per material.

TEST PROCEDURE:

1. Fold the test paper in half along its axis.
2. Insert the textile sample between the layers of the paper.
3. Place the sandwich between two glass plates (5 test pieces plus control fabric is the highest amount which can be done in one test)
4. Wrap the package in 3 layers of BHT (= 2,6 Di-tert-butyl-4-nitrophenol) free polyethylene film and seal it with an adhesive tape.
5. Place the package in an oven at 50± 3 °C for 16 hrs.
6. Remove the package from the oven after the requested time and let it cool down to room temperature.
7. Check visually if the control fabric is yellow. If so the test is successful.
8. Check the intensity of the yellowing by using the grey scale for staining.

REPORT: Degree of is reported to the nearest 0.5 unit based on the AATCC Grey Scale.