VF Asia Footwear Laboratory Testing Manual

Test Parameters for Assembled Footwear	Test method # VF- G01 Page 1 of 1
Date Issued : September 11, 2014 Revision # : 1 Reason for Revision: Include TBL	Created by : Nila Babia Erazo / Chris Adam

PURPOSE AND SCOPE: To evaluate the construction /materials of assembled shoes.

REFERENCES: See Specified Method

MATERIALS: Assembled footwear.

SAMPLE PREPARATION:

NOTE: ***Condition the shoe sample for at least 48 hours at standard laboratory environment at 23.0±2.0˚C temperature and 55 ±10 % Relative Humidity to allow the cement to crosslink complete***ly.

1. **BOND TEST**: Test at least 1 midsole to outsole bonds and at least 1 midsole to upper bonds per shoe type.
2. **WHOLE SHOE FLEX**: Test one pair per shoe type.
3. **WHOLE SHOE FLEX - GB :** Test one pair per shoe type intended for China Market
4. **WATER PROOF – FLEX :** Test one pair for water proof style
5. **WATER PROOF –STATIC :** Test one pair for water proof style
6. **WATER PROOF –WATER ABSORPTION :** Test one pair for water proof style
7. **WASH TEST :** Test one pair per shoe type
8. **HYDROLYSIS TEST:** Test one pair per shoe type.
9. **AGING TEST:** Test one pair per shoe type.
10. **CLOSURE STRENGTH**: Test two lace holes /hooks/loops.
11. **LACE STRENGTH**: Test one shoe lace per pair of shoes.
12. **MIDSOLE /OUTSOLE EVALUATIONS** : Test one pair for the following:
    - Specific Gravity
    - Durometer Hardness
    - UV –Light Discoloration
    - DIN Abrasion
    - Marking outsole
    - Slip Resistance
13. **UPPER AND LINING MATERIAL EVALUATIONS**:
    - Colorfastness to Water
    - Colorfastness to Perspiration
    - Colorfastness to Crocking
    - Ultraviolet Light Discoloration
    - Surface Contact Discoloration