VF Asia Footwear Laboratory Testing Manual

Test Method for Reaction of Dyestuff to Chemical Solvent	Test method # VF-I03 Page 1 of 2
Date Issued : August 1, 2012 **Revision # : 1** **Reason for Revision :** - **Cutting size of sample** - **Revise some terminology of test procedures**	**Created by : Nila Babia Erazo /**

PURPOSE AND SCOPE: To determine the reaction of color pigment or dye use in upper and lining material, lace webbing to chemical solvent.

REFERENCES: None

EQUIPMENT AND MATERIAL:

1. Test tubes
2. Beakers
3. Test tube rack
4. Graduated cylinder
5. Solvents : acetone, ethyl acetate , MEK , toluene
6. Funnels
7. Hotplate with stirrer or water bath
8. Iron stand with clamps
9. Thermometer
10. Fabric, Leather (natural and synthetic), lace , closures made of fabric and leather

SAMPLE PREPARATIONS:

1. Condition the sample for at least 24 hours at the standard laboratory environment at 23.0±2.0˚ C temperature and 55 ±10 % Relative Humidity.

2. Upper material :
   - Get sample approximately 3 cm x 3 cm
   - Cut into small pieces so that these won't clog in the test tube
3. Lace / webbing :
   - Cut 2-3 pieces, approximately 30 mm long
   - Cut further to smaller pieces so that these won't clog in the test tube

REPETITIONS: Test two (2) samples per material**.**

Test Method for Reaction of Dyestuff to Chemical Solvent	Test method # VF-I03 Page 2 of 2
Date Issued : August 1, 2012 Revision # : 1 Reason for Revision : - Cutting size of sample - Revise some terminology of test procedures	Created by : Nila Babia Erazo /

TEST PROCEDURES:

Note: *Solvents are flammable material which should be handled carefully. Contact with the skin and inhalation must be avoided. Protective gloves, gas mask and safety glasses should be worn.*

1. Place the cut samples at the bottom of the test tube.
2. Add the solvent to the test tube. Ensure that the samples fully submerged in the solvent. Let it stand for 10 minutes.
3. Check discoloration of the solvent.
4. If there's NO discoloration noticed , may proceed to elevated temperature test: (This is optional test)
   - Place the test tube with the samples in the water that was pre-heated at 80 ± 5 °C. Let it stand for 10 minutes.
   - Check discoloration of the solvent

REPORT: Color change of solvent