Fabric Test Results
布料测试结果

PASS

Form # : Lab VF 005

SATRA Accredited Laboratory No.18823

ETRF.No: TR202510267564

Lab Ref.No: DTP20251008FBL-21

Supplier/Factory(厂商):	YEE CHAIN	◉ Prod.Material量产材料 ○ Prod Re-test量产重测	
Supplier's country(国家):	CHINA	O New/Development 开发段新材料	
Material Description(材料):	44" White YH-S535 Mesh	o Tech 1 o Tech 2 o Tech 3 o Tech 4	
Color (颜色):	CANVAS WHITE/WHITE	O Sales Sample (销售样品)	
Model No./Style(型体):	VN000VA3WWW/WM VERO LS /	Received Date (收到日期):	2025/10/13
P.O/Lot No(订单):	BE0050-00116/VSP25080136 /	Tested Date (测试时间):	2025/10/14
Quantity(数量):	1053	Finished Date (完成时间):	2025/10/20
Send by (提供方):		Technician (技术人员):	JESS/KATH/SHAI

Test Items 测试项目	VF Test Method	Units 单位	Test Results 测试结果	Max/Min 最大/小值	Average 平均值	Standard 标准	Tolerance 容许量	Rating 等级
Gauge 规格	VF-A03 (2014/04)	mm	0.72 0.72 0.73 0.74 0.72 0.73	0.74 / 0.72	0.73	Refer to specification		P
Weight 重量	VF-A02 (2018/11)	g/m²	160.4 160.1 160.2		160.23	Refer to specification		P
Yarn Count 经纬密度	VF-A07 (2008/05)	# of yarns	Warp :			Refer to specification		
			Welf :					
Tensile 抗拉	VF-B01 (2022/11)	kgf/cm	L= 6.63 6.45 6.7		6.59	3		P
			W= 10.28 10.56 11.53		10.79	3		P
Elongation 延伸	VF-B01 (2022/11)	%	L= 711.7 744.63 727.47		727.93	10		P
			W= 511.73 494.96 490.82		499.17	10		P
Trouser Tear - 裤形撕裂	VF-B07 (2022/11)	kgf	L= 6.5 7 6.5		6.67	1.5		P
			W= 6.5 5.4 5.5		5.8	1.5		P
Stitch tear 车缝撕裂	VF-B08 (2019/05)	kgf/cm	L= 5.9 5.1 6.4		5.8	3		P
			W= 4.5 5.8 4.6		4.97	3		P
Bally Flex Bally 耐挠	VF-D01 (2019/06)	cycles	Dry干 : L1: L2:					
			Dry干 : W1: W2:					
			Wet湿 : L1: L2:					
			Wet湿 : W1: W2:					
			After hydrolysis水解 : L1: L2:					
			After hydrolysis水解 : W1: W2:					
Martindale Abrasion Martindale 耐磨	VF-C04 (2024/12)	cycles	Dry=Fabric:1. 25000 No damage or No abrasion of ink 2. 25000 No damage or No abrasion of ink			25000		P P
			Dry=Ink 1. 2.					
			Wet=Fabric:1. 6500 No damage or No abrasion of ink 2. 6500 No damage or No abrasion of ink			6500		P P
			Wet=Ink: 1. 2.					
Taber Abrasion Taber 耐磨 CS-17,500g	VF-C05 (2024/12)	cycles						
Mullen Burst 爆破	VF-B02 (2019/05)	kgf/cm²	18.87 17.38 14.41		16.8867	10		P
Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面)	VF-E16 (2018/11)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维			3.5		
Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面)	VF-E01 (2008/05)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
UV Light紫线 (24hrs, 50℃)	VF-E03 (2019/05)	AATCC	4.5 4.5			4		P
Colorfastness to Crocking 摩擦褪色	VF-E02 (2024/08)	AATCC	Dry干 =			3.5		
			Wet湿 =			3		
Abrasion Crocking 摩擦	VF-E02 (2024/08)		Dry干 =					
			Wet湿 =					
Ink adhesion on Substrate 3M Stotch tape # 600	VF-F05 (2014/07)		Dry干 =					
			Wet湿 =					
Reaction with solvents 溶液反应	VF-I03 (2012/08)		Acetone 丙酮: Ethyl Acetate 乙酸乙酯: MEK 丁酮 :					
Peeling Strength 剥离强度	VF-F03 (2024/12)	kgf/cm						
Wicking 虹吸	VF-E14 (2014/07)	mm						
Maeser Test Maeser防水测试	VF-E11 (2018/11)	cycles						
Glow in the dark	VF-E28 (2024/08)							
Heat Aging 热老化 (72hrs 70℃)	VF-E04 (2022/09)		5 5			4		P
Hydrolysis 水解 (7Days,60℃ 95%RH)	VF-E19 (2024/12)							

Comments 备注:

Reviewed by 审查: KATE GOLDBERG LABORATORY SUPERVISOR

Approved by 核准: KATE GOLDBERG LABORATORY SUPERVISOR