Fabric Test Results
布料测试结果

PASS

Form # : Lab VF 005

SATRA Accredited Laboratory No.18823

ETRF.No: TR202510267542

Lab Ref.No: DTP20251008FBL-18

Supplier/Factory(厂商): YEE CHAIN

Supplier's country(国家): CHINA

Material Description(材料): 44" Blue129-27-12 YH-S535 Mesh

Color (颜色): SUEDE/CANVAS Deep Twilight

Model No./Style(型体): VN000Y7HEMT/MN VERO LS /

P.O/Lot No(订单): BE0050-01058/VSP25080144 /

Quantity(数量): 536

Send by (提供方):

◉ Prod.Material量产材料 ○ Prod Re-test量产重测

O New/Development 开发段新材料

o Tech 1 o Tech 2 o Tech 3 o Tech 4

O Sales Sample (销售样品)

Received Date (收到日期): 2025/10/13

Tested Date (测试时间): 2025/10/14

Finished Date (完成时间): 2025/10/20

Technician (技术人员): JESS/KATH/SHAI

Test Items 测试项目	VF Test Method	Units 单位	Test Results 测试结果	Max/Min 最大/小值	Average 平均值	Standard 标准	Tolerance 容许量	Rating 等级
Gauge 规格	VF-A03 (2014/04)	mm	0.75 0.76 0.74 0.74 0.75 0.74	0.76 / 0.74	0.75	Refer to specification		P
Weight 重量	VF-A02 (2018/11)	g/m²				Refer to specification		P
Yarn Count 经纬密度	VF-A07 (2008/05)	# of yarns	Warp :			Refer to specification		
			Welf :					
Tensile 抗拉	VF-B01 (2022/11)	kgf/cm	L= 6.89 6.53 6.55		6.66	3		P
			W= 8.69 10.28 9.71		9.56	3		P
Elongation 延伸	VF-B01 (2022/11)	%	L= 507.6 651.85 649.09		602.85	10		P
			W= 515.74 552.93 540.66		536.44	10		P
Trouser Tear - 裤形撕裂	VF-B07 (2022/11)	kgf	L= 5.7 4.3 3.8		4.6	1.5		P
			W= 5 5.9 4.3		5.07	1.5		P
Stitch tear 车缝撕裂	VF-B08 (2019/05)	kgf/cm	L= 5.1 6.4 4.7		5.4	3		P
			W= 5.5 4.9 4.6		5	3		P
Bally Flex Bally 耐挠	VF-D01 (2019/06)	cycles	Dry干 : L1: L2:					
			Dry干 : W1: W2:					
			Wet湿 : L1: L2:					
			Wet湿 : W1: W2:					
			After hydrolysis水解 : L1: L2:					
			After hydrolysis水解 : W1: W2:					
Martindale Abrasion Martindale 耐磨	VF-C04 (2024/12)	cycles	Dry=Fabric:1. 25000 No damage or No abrasion of ink 2. 25000 No damage or No abrasion of ink			25000		P P
			Dry=Ink 1. 2.					
			Wet=Fabric:1. 6500 No damage or No abrasion of ink 2. 6500 No damage or No abrasion of ink			25000		P P
			Wet=Ink: 1. 2.					
Taber Abrasion Taber 耐磨 CS-17,500g	VF-C05 (2024/12)	cycles						
Mullen Burst 爆破	VF-B02 (2019/05)	kgf/cm²	11.18 11.17 11.3		11.2167	10		P
Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面)	VF-E16 (2018/11)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
			4.5 5 5 5 5 5			3.5		P
Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面)	VF-E01 (2008/05)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
UV Light紫线 (24hrs, 50℃)	VF-E03 (2019/05)	AATCC				3		
Colorfastness to Crocking 摩擦褪色	VF-E02 (2024/08)	AATCC	Dry干 = 5			3.5		P
			Wet湿 = 5			3		P
Abrasion Crocking 摩擦	VF-E02 (2024/08)		Dry干 =					
			Wet湿 =					
Ink adhesion on Substrate 3M Stotch tape # 600	VF-F05 (2014/07)		Dry干 =					
			Wet湿 =					
Reaction with solvents 溶液反应	VF-I03 (2012/08)		Acetone 丙酮: Ethyl Acetate 乙酸乙酯: MEK 丁酮 :					
Peeling Strength 剥离强度	VF-F03 (2024/12)	kgf/cm						
Wicking 虹吸	VF-E14 (2014/07)	mm						
Maeser Test Maeser防水测试	VF-E11 (2018/11)	cycles						
Glow in the dark	VF-E28 (2024/08)							
Heat Aging 热老化 (72hrs 70℃)	VF-E04 (2022/09)		5 5			4		P
Hydrolysis 水解 (7Days,60℃ 95%RH)	VF-E19 (2024/12)							

Comments 备注:

APPROVED: Eigeman Go (QA Manager)
Signed 2026-10-30 15:33

Reviewed by 审查: KATE G.

Approved by 核准: KATE G.