# Fabric Test Results
# 布料测试结果

PASS

Form # : Lab VF 005

SATRA Accredited Laboratory No.18823

ETRF.No: TR202510267534

Lab Ref.No: DTP20251008FBL-25

| | | | |
|---|---|---|---|
| Supplier/Factory(厂商): | YEE CHAIN | ◉ Prod.Material量产材料 ○ Prod Re-test量产重测 | |
| Supplier's country(国家): | CHINA | O New/Development 开发段新材料 | |
| Material Description(材料): | 44" Red010-34-33 YH-S519 Textile | o Tech 1 o Tech 2 o Tech 3 o Tech 4 | |
| Color (颜色): | Color Check Sunset Ruby | O Sales Sample (销售样品) | |
| Model No./Style(型体): | VN000EDJGH3/JN ASHWOOD HI DECON / | Received Date (收到日期): | 2025/10/13 |
| P.O/Lot No(订单): | BE0022-01511/VSP25080336 / | Tested Date (测试时间): | 2025/10/14 |
| Quantity(数量): | 160 | Finished Date (完成时间): | 2025/10/20 |
| Send by (提供方): | | Technician (技术人员): | JESS/KATH/SHAI |

| Test Items 测试项目 | VF Test Method | Units 单位 | Test Results 测试结果 | Max/Min 最大/小值 | Average 平均值 | Standard 标准 | Tolerance 容许量 | Rating 等级 |
|---|---|---|---|---|---|---|---|---|
| Gauge 规格 | VF-A03 (2014/04) | mm | 0.82 0.83 0.82 0.83 0.82 0.83 | 0.83 / 0.82 | 0.82 | Refer to specification | | P |
| Weight 重量 | VF-A02 (2018/11) | g/m² | 202.2 203.1 203.1 | | 202.8 | Refer to specification | | P |
| Yarn Count 经纬密度 | VF-A07 (2008/05) | # of yarns | Warp : | | | Refer to specification | | |
| | | | Welf : | | | | | |
| Tensile 抗拉 | VF-B01 (2022/11) | kgf/cm | L= 9.2 13.51 8.85 | | 10.52 | 3 | | P |
| | | | W= 8.27 15.89 13.17 | | 12.44 | 3 | | P |
| Elongation 延伸 | VF-B01 (2022/11) | % | L= 583.48 524.26 568.2 | | 558.65 | 10 | | P |
| | | | W= 583.98 570.96 559.44 | | 571.46 | 10 | | P |
| Trouser Tear - 裤形撕裂 | VF-B07 (2022/11) | kgf | L= 5.8 3.9 5.4 | | 5.03 | 1.5 | | P |
| | | | W= 6 3.9 4.2 | | 4.7 | 1.5 | | P |
| Stitch tear 车缝撕裂 | VF-B08 (2019/05) | kgf/cm | L= 9.7 8.3 8.4 | | 8.8 | 3 | | P |
| | | | W= 8 9.6 8.6 | | 8.73 | 3 | | P |
| Bally Flex Bally 耐挠 | VF-D01 (2019/06) | cycles | Dry干 : L1: L2: | | | | | |
| | | | Dry干 : W1: W2: | | | | | |
| | | | Wet湿 : L1: L2: | | | | | |
| | | | Wet湿 : W1: W2: | | | | | |
| | | | After hydrolysis水解 : L1: L2: | | | | | |
| | | | After hydrolysis水解 : W1: W2: | | | | | |
| Martindale Abrasion Martindale 耐磨 | VF-C04 (2024/12) | cycles | Dry=Fabric:1. 25000 No damage or No abrasion of ink<br>2. 25000 No damage or No abrasion of ink | | | 25000 | | P<br>P |
| | | | Dry=Ink 1.<br>2. | | | | | |
| | | | Wet=Fabric:1. 6500 No damage or No abrasion of ink<br>2. 6500 No damage or No abrasion of ink | | | 25000 | | P<br>P |
| | | | Wet=Ink: 1.<br>2. | | | | | |
| Taber Abrasion Taber 耐磨 CS-17,500g | VF-C05 (2024/12) | cycles | | | | | | |
| Mullen Burst 爆破 | VF-B02 (2019/05) | kgf/cm² | 16.402 13.3108 10.7349 | | 13.4826 | 10 | | P |
| Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面) | VF-E16 (2018/11) | AATCC | Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维 | | | | | |
| | | | 4.5 5 4.5 5 5 5 | | | 3.5 | | P |
| Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面) | VF-E01 (2008/05) | AATCC | Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维 | | | | | |
| | | | | | | | | |
| UV Light紫线 (24hrs, 50℃) | VF-E03 (2019/05) | AATCC | | | | | | |
| Colorfastness to Crocking 摩擦褪色 | VF-E02 (2024/08) | AATCC | Dry干 = 5 | | | 3.5 | | P |
| | | | Wet湿 = 5 | | | 3 | | P |
| Abrasion Crocking 摩擦 | VF-E02 (2024/08) | | Dry干 = | | | | | |
| | | | Wet湿 = | | | | | |
| Ink adhesion on Substrate 3M Stotch tape # 600 | VF-F05 (2014/07) | | Dry干 = | | | | | |
| | | | Wet湿 = | | | | | |
| Reaction with solvents 溶液反应 | VF-I03 (2012/08) | | Acetone 丙酮:<br>Ethyl Acetate 乙酸乙酯:<br>MEK 丁酮 : | | | | | |
| Peeling Strength 剥离强度 | VF-F03 (2024/12) | kgf/cm | | | | | | |
| Wicking 虹吸 | VF-E14 (2014/07) | mm | | | | | | |
| Maeser Test Maeser防水测试 | VF-E11 (2018/11) | cycles | | | | | | |
| Glow in the dark | VF-E28 (2024/08) | | | | | | | |
| | | | | | | | | |
| Heat Aging 热老化 (72hrs 70℃) | VF-E04 (2022/09) | | 5 5 | | | 4 | | P |
| Hydrolysis 水解 (7Days,60℃ 95%RH) | VF-E19 (2024/12) | | | | | | | |

Comments 备注:

Reviewed by 审查: KATE GOLDBERG LABORATORY SUPERVISOR

Approved by 核准: KATE GOLDBERG LABORATORY SUPERVISOR