Leather Test Results
皮料测试结果

SATRA Accredited Laboratory No.18B23

PASS

Form # : Lab VF 006

ETRF.No: TR202511281216

Lab Ref.No: DTP20251022LEU-4

Supplier/Factory(厂商):	Prime Asia (PATB)	◉ Prod.Material量产材料 ○ Prod Re-test量产重测	
Supplier's country(国家):	CHINA	O New/Development 开发段新材料	
Material Description(材料):	44"3.5N Black Cotton Canvas	o Tech 1 o Tech 2 o Tech 3 o Tech 4	
Color (颜色):	FTP LOGO BLACK	O Sales Sample (销售样品)	
Model No./Style(型体):	VN000DC0BLA/UA OTW OLD SKOOL 36 /	Received Date (收到日期):	24-Oct-25
P.O/Lot No(订单):	VSP24090524/AA0350-00012 /	Tested Date (测试时间):	25-Oct-25
Quantity(数量):	57	Finished Date (完成时间):	04-Nov-25
Send by (提供方):		Technician (技术人员):	JESS/KATH/SHAI

Test Items 测试项目	VF Test Method	Units 单位	Test Results 测试结果	Max/Min 最大/小值	Average 平均值	Standard 标准	Tolerance 容许量	Rating 等级
Gauge 规格	VF-A03 (2014/04)	mm	1.45 1.46 1.43 1.46 1.45 1.45	1.46 1.43	1.45	Refer to specification		P
Weight 重量	VF-A02 (2018/11)	g/m²	900.3 888.4 888		892.23	Refer to specification		P
Softness柔软度	VF-A06 (2014/08)	mm						
Tensile 抗拉	VF-B01 (2022/11)	kgf/cm	L= 24.17 23.06 24.32		23.85	20		P
			W= 20.84 23.73 21.68		22.08	20		P
Elongation 延伸	VF-B01 (2022/11)	%	L= 124.46 21.16 102.42		82.68	25		P
			W= 228.51 195.83 119.95		181.43	25		P
Trouser Tear - 裤形撕裂	VF-B07 (2022/11)	kgf	L=					
			W=					
Baumann Tear Baumann 撕裂	VF-B09 (2019/05)	kgf	L= 8.65 8.24 8.51		8.47	8		P
			W= 8.9 8.11 8.57		8.53	8		P
Bally Flex Bally 耐挠	VF-D01 (2019/06)	cycles	Dry干: L1: 100000 L2: 100000			100000		P
			Dry干: W1: 100000 W2: 100000					
			Wet湿: L1: 20000 L2: 20000			20000		P
			Wet湿: W1: 20000 W2: 20000					
			After hydrolysis水解: L1: 50000 L2: 50000			50000		P
			After hydrolysis水解: W1: 50000 W2: 50000					
			Freezing L1: L2:					
			Freezing W1: W2:					
Martindale Abrasion Martindale 耐磨	VF-C04 (2024/12)	cycles	Dry干= ,					
			Wet湿= ,					
Taber Abrasion Taber 耐磨 H-22/1000g	VF-C05 (2024/12)	cycles	150, No damage of coating 150, No damage of coating					
Mullen Burst 爆破	VF-B02 (2019/05)	kgf/cm²	21.9112 21.8956 21.2753		21.694	16		P
Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面)	VF-E16 (2018/11)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
Colorfastness to Perspiration Back side耐汗测试(反面)			Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面)	VF-E01 (2008/05)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
			4.5 4.5 5 4.5 5 5					P
Colorfastness to Water Back side耐水测试(反面)			Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
			4.5 4.5 5 5 5 5					P
UV light紫外线 (24hrs, 50℃)	VF-E03 (2019/05)	AATCC						P
Colorfastness to Crocking 摩擦退色	VF-E02 (2024/08)	AATCC	Dry干= 5					P
			Wet湿= 5					P
Abrasion Crocking 摩擦	VF-E02 (2024/08)	AATCC	Dry干=					
			Wet湿=					
			ASW人工海水=					
Ink adhesion on Substrate 3M Scotch tape #600	VF-F05 (2014/07)	AATCC	Dry干=					
			Wet湿=					
			ASW人工海水=					
PVC Migration	VF-E06 (2014/07)	AATCC				3.5		
Reaction with solvents 溶剂反应	VF-I03 (2012/08)		Acetone 丙酮: Ethyl Acetate 乙酸乙酯: MEK 丁酮:					
Wicking 虹吸	VF-E14 (2014/07)	mm						
Maeser Test Maeser防水测试	VF-E11 (2018/11)	cycles						
Peeling Strength 剥离强度	VF-F03 (2024/12)	kgf/cm						
Glow in the dark	VF-E28 (2024/08)		D65 CWF					
			After Washing D65 CWF					
Heat Aging 热老化 (72hrs,70℃)	VF-E04 (2022/09)		5, 5			4		P
Hydrolysis 水解 (7Days,60℃ ,95%RH)	VF-E19 (2024/12)		5, 5 No damage or No delamination of coating			4		P

Comments 备注:

Reviewed by 审查: Eigeman Go

Approved by 核准: Eigeman Go

APPROVED: Eigeman Go (QA Manager)
Signed: 2025-11-20 15:57:27