Leather Test Results
皮料测试结果

SATRA Accredited Laboratory No.18B23

Form # : Lab VF 006

ETRF.No:

Lab Ref.No:

Supplier/Factory(厂商):

Supplier's country(国家):

O New/Development 开发段新材料

Material Description(材料):

o Tech 1 o Tech 2 o Tech 3 o Tech 4

Color (颜色):

O Sales Sample (销售样品)

Model No./Style(型体): /

Received Date (收到日期):

P.O/Lot No(订单): /

Tested Date (测试时间):

Quantity(数量):

Finished Date (完成时间):

Send by (提供方):

Technician (技术人员):

Test Items 测试项目	VF Test Method	Units 单位	Test Results 测试结果	Max/Min 最大/小值	Average 平均值	Standard 标准	Tolerance 容许量	Rating 等级
Gauge 规格	VF-A03 (2014/04)	mm				*Refer to specification*		
Weight 重量	VF-A02 (2018/11)	g/m²				*Refer to specification*		
Softness柔软度	VF-A06 (2014/08)	mm						
Tensile 抗拉	VF-B01 (2022/11)	kgf/cm	**L=**					
			W=					
Elongation 延伸	VF-B01 (2022/11)	%	**L=**					
			W=					
Trouser Tear - 裤形撕裂	VF-B07 (2022/11)	kgf	**L=**					
			W=					
Baumann Tear Baumann 撕裂	VF-B09 (2019/05)	kgf	**L=**					
			W=					
Bally Flex Bally 耐挠	VF-D01 (2019/06)	cycles	Dry干: L1: L2:					
			Dry干: W1: W2:					
			Wet湿: L1: L2:					
			Wet湿: W1: W2:					
			After hydrolysis水解: L1: L2:					
			After hydrolysis水解: W1: W2:					
			Freezing L1: L2:					
			Freezing W1: W2:					
Martindale Abrasion Martindale 耐磨	VF-C04 (2024/12)	cycles	Dry干=,					
			Wet湿=,					
Taber Abrasion Taber 耐磨 H-22/1000g	VF-C05 (2024/12)	cycles	,					
			,					
Mullen Burst 爆破	VF-B02 (2019/05)	kgf/cm²						
Colorfastness to Perspiration (Top Side/Finished Surface Only) 耐汗测试(正面)	VF-E16 (2018/11)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
Colorfastness to Perspiration Back side耐汗测试(反面)			Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
Colorfastness to Water (Top Side/Finished Surface Only) 耐水测试(正面)	VF-E01 (2008/05)	AATCC	Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
Colorfastness to Water Back side耐水测试(反面)			Wool 毛料 / Acrylic 丙烯酸树脂纤维 / Polyester 聚酯 / Nylon 尼龙 / Cotton 棉 / Acetate 醋酸纤维					
UV light紫外线 (24hrs, 50℃)	VF-E03 (2019/05)	AATCC						
Colorfastness to Crocking 摩擦退色	VF-E02 (2024/08)	AATCC	Dry干=					
			Wet湿=					
Abrasion Crocking 摩擦	VF-E02 (2024/08)	AATCC	Dry干=					
			Wet湿=					
			ASW人工海水=					
Ink adhesion on Substrate 3M Scotch tape #600	VF-F05 (2014/07)	AATCC	Dry干=					
			Wet湿=					
			ASW人工海水=					
PVC Migration	VF-E06 (2014/07)	AATCC						
Reaction with solvents 溶剂反应	VF-I03 (2012/08)		Acetone 丙酮: Ethyl Acetate 乙酸乙酯: MEK 丁酮:					
Wicking 虹吸	VF-E14 (2014/07)	mm						
Maeser Test Maeser防水测试	VF-E11 (2018/11)	cycles						
Peeling Strength 剥离强度	VF-F03 (2024/12)	kgf/cm						
Glow in the dark	VF-E28 (2024/08)		**D65 CWF**					
			After Washing D65 CWF					
Heat Aging 热老化 (72hrs,70℃)	VF-E04 (2022/09)		,					
Hydrolysis 水解 (7Days,60℃ ,95%RH)	VF-E19 (2024/12)		,					

Comments 备注:

Reviewed by 审查:

Approved by 核准: