

HIND COAT REPEL

SILANE/SILOXANE-BASED WATER-REPELLENT
COATING FOR CONCRETE AND MASONRY.



DESCRIPTION

Hind Coat Repel is a dilutable, 40% active single component Silane/Siloxane based water repellent emulsion for use on concrete and masonry substrates. It can be diluted to between 5% to 20% depending on the nature of application and substrate to be treated. The unique formulation of the product when applied will penetrate into the substrate and provide water repellent properties by reacting chemically with the substrate. The treated substrate becomes hydrophobic and retains its original look. It conforms to **BS 3826-1969, Class A & B**, as a Silicon resin based water repellent coating.

USES

Hind Coat Repel is a ready to use coating and can be used both in external & internal conditions. It can be applied to old as well as new surfaces. It can be applied externally on brick work, stone, concrete & masonry surfaces, cement plaster, joints, pre-cast block and stone claddings. For internal coating when applied over Plaster of Paris, plaster, brick walls it prevents dampness, ingress of moisture, cracking of wall plaster and peeling of paints from the walls.

ADVANTAGES

- Dilutable with water for ready to use.
- Excellent bonding and adhesion to concrete & masonry substrates.
- Substrate becomes hydrophobic on its application that does not allow water absorption.
- Deeply penetrable into absorbent substrates due to smaller molecule size providing excellent water repellent properties.
- The substrate life gets increased due to reduction in water absorption which resist spalling due to efflorescence and freeze-thaw effect.
- The surface become highly water repellent and is durable in aggressive environment.
- The original colour of the surface remains unaltered after the coating.
- When applied to vertical surface it gets cleaned with rain water without leaving any stains.
- Gives excellent performance & stability at (5%-20%) active ingredient content levels.
- Less VOC content.

APPLICATION

DILUTION

Hind Coat Repel dilutable water repellent emulsion gets readily diluted in water and stable dilutions containing 5% to 20% active ingredient levels can be made. It is always advisable to add water to the emulsion only. To obtain a stable dilution with 5% active ingredient level **7 parts of water** to be added to **1 part of Hind Coat Repel**. For example to make a **1000gm** stable dilution with 10% active ingredient level, **750 gm of water** is to be mixed to **250 gm of Hind Coat Repel (Ratio 3:1)**. For preservation of the dilutions for extended use, preservatives can be added to the dilutions after testing only. The performance of **Hind Coat Repel** depends on content of active ingredient content after dilution and to be done as per requirement of the different selected substrates.

HIND COAT REPEL

SILANE/SILOXANE-BASED WATER-REPELLENT
COATING FOR CONCRETE AND MASONRY.

APPLICATION

Before application of **Hind Coat Repel** the surface should be thoroughly cleaned and surface dry. Any cracks visible should be repaired. **Hind Coat Repel** is applied preferably with brush, roller or low pressure spray equipment (45-100 kPa). Areas covered with Glass should be protected while spraying.

Hind Coat Repel when applied with a brush or roller the application is to be repeated until the surface remains moist for 2-3 minutes. When applied with a low pressure spray the substrate of application should be completely saturated. For vertical surface application the coating should flow down 15 cm downward from the point of application. All surfaces to be coated from bottom up. If two coats are required the second coat to be applied after 2-3 hours interval. If Brush application of the coating is done it is to be applied very smooth & liberally.

Note: Not recommended to be applied over substrates subjected to hydrostatic pressure.

PROPERTIES

Aspect	White Liquid
Active Ingrdeint Content	40%
Specific Gravity at 27°C	0.970 ± 0.005
Density (lb/gal)	8.0 ± 0.02
pH	3.4 -5.6
VOC Content (g/L)	< 300 (excluding water and exempt compounds)
	122 (including water and exempt compounds)
Flash Point (Closed cup)	> 100°C
Thinning	Water
Application Temperature	Above 5°C
Coverage	10-12m ² / Kg of diluted material depending on the porosity of the surface. If the surface is porous, second coat application is to be done.

TABLE-1

Performance of **Hind Coat Repel** on different Substrates

Alkaline Substrates and % of Active Ingredient		Percentage of Water Exclusion versus Control after 1 day in immersed condition
Mortar Cubes		
5% active Ingredient		94.2
10% active Ingredient		94.9
20% active Ingredient		94.0
Concrete Cubes		
5% active Ingredient		86.6
10% active Ingredient		85.9
20% active Ingredient		76.2

HIND COAT REPEL

SILANE/SILOXANE-BASED WATER-REPELLENT
COATING FOR CONCRETE AND MASONRY.

Neutral Substrates and % of Active Ingredient

Percentage of Water Exclusion versus Control after 1 day in immersed condition

Brick Class I

5% active Ingredient	87.3
10% active Ingredient	69.9
20% active Ingredient	41.1

Brick Class II

5% active Ingredient	88
10% active Ingredient	48.2
20% active Ingredient	43.4

- Results and Calculation are based on the weight gain of control sample.
- Samples casted in 50mm X50mmX50mm cubes.
- 1/8 th portion of bricks used instead of half of a brick with 5 specimen.

SHELF LIFE

Best before 12 months from the date of manufacture in unopened condition . To be stored in a cool and dry place away from direct sunlight at a temperature ranging between 5°C to 50°C.

PACKING

Available in 1, 20, & 250 Kg HDPE Container.

HANDLING PRECAUTIONS

Hind Coat Repel is non-toxic. Any splashes on skin happen, immediately wash with water. If contacts with eyes occur, immediately wash with water and seek medical advice. When it comes into contact acids, bases, amines and heavy metal or their compounds the rate of evolution gets increased and it has to be kept away from these materials. Should not be use near naked flame. During application use of safety goggles and gloves is always recommended.

IMPORTANT NOTICE :

Hindcon Chemicals maintains a team of technically trained professionals to provide full support to your problems in construction, and recommend the correct product to suite your specific requirements. Our authorized applicators can attend your site for application of the products. The content of the Technical datasheet are for general information and guideline. The result shown here are generated from our laboratory or from our site experiences.

Quality of our products are maintained as per ISO9001:2008 recommendations and continuous researches. The behaviour can change as per the prevailing conditions at the time of applications. Since **HINDCON CHEMICALS LIMITED** has no control over the use to which the users may put the material, it does not claim or warrant that in the user's particular circumstances, the result that the user will obtain from the product will be the same as those described in this communication or that the user will find the information or recommendations complete, accurate or useful. The client must test and ascertain the safety and fitness for the product for use. The right to change the properties of the products is reserved with us. The proprietary rights of third parties must be observed. All orders are accepted subject to the terms of sale and delivery. Users must always refer to the most recent issue of the latest Data Sheet for the product concerned, copies of which will be supplied on request.



✉ contactus@hindcon.com
☎ +91 33 24490839, 9830599113
☎ +91 33 24490849
📍 Kolkata, West Bengal, India

VISIT OUR WEBSITE

