

Herculite® 20

TYPICAL PROPERTIES REPORT

| PROPERTY | | TEST METHOD | AVERAGE TEST RESULTS | |
|--------------------------------|------------------|-----------------------|----------------------|---------------|
| PHYSICAL PROPERTIES | | | | |
| English | Metric | | English | Metric |
| Weight, (oz./yd ²) | g/m ² | ASTM D3776 | 10 oz. +/- 10% | 284 g +/- 10% |
| Adhesion. (lbs./2 in.) | N/50 mm | ASTM D751 (Free Peel) | 6 minimum | 27 minimum |
| Breaking Strength (lbs./in) | N/25 mm | ASTM D5035 | W 135 F 130 | W 601 F 578 |
| Tear Strength (lbs.) | N | ASTM D2261/1 | W 45 F 45 | W 200 F 200 |
| Hydrostatic Burst (PSI) | kPa | ASTM D751/A | 250 | 1724 |
| Flame Resistance | | ASTM D6413 | Pass | |

The information contained in this report is believed to be reliable. It is offered in good faith and intended for use as a general guide. Herculite makes no guarantee of results and assumes no obligation or liability whatsoever in connection with the possible use of this information. This report, including any statements concerning the possible use of our products, is not a license to operate under, or intended to suggest infringement of any existing patents.

Herculite® is a registered trademark of Herculite Products, Inc., Emigsville, PA

HERCULITE PRODUCTS, INC.
 P.O. Box 435, Emigsville, PA 17318
 (800) 772-0036 (717) 764-1192
 FAX: (717) 764-5211
www.herculite.com customercare@herculite.com