



# SHANGHAI BRILLIANT TEXTILE CO.,LTD.

Addr.:4 Floor,Building 2,No.6372 Yinggang East Road,Qingpu District,Shanghai,China(201703)

Tel:+86 21-36582868

E-mail:info@brilliant-tex.com

## Technical Confirmation

TC No.:

TC25010011

Download No.:

Customer:

Delta V S.A.

Atten.:

Fernando Quinodoz

Date:

2025-01-14

Customer Art.:

NXR2/JUOO6O

Product Name:

Nylon 420D 3mm size ripstop oxford fabric with PU coating

Finishing:

Dyed+C6 W/R+PU clear coating

### Mechanical Properties

### Care Instructions

| TEST ITEMS                                       | UNIT  | TEST STANDARD        | REQUIRED DATA | CONFIRM DATA |
|--------------------------------------------------|-------|----------------------|---------------|--------------|
| Cutable width                                    | cm    | EN 1773              |               | 147          |
| Total weight                                     | g/m2  | EN 12127             |               | 200±5%       |
| Dimensional change in washing-warp               | %     | ISO 5077;ISO 6330-4N |               | ±3           |
| Dimensional change in washing-weft               | %     | ISO 5077;ISO 6330-4N |               | ±3           |
| Breaking force-warp                              | N     | EN ISO 13934-1       |               | 1600         |
| Breaking force-weft                              | N     | EN ISO 13934-1       |               | 1200         |
| Elongation at break-warp                         | %     | EN ISO 13934-1       |               |              |
| Elongation at break-weft                         | %     | EN ISO 13934-1       |               |              |
| Tear force-warp                                  | N     | ISO 13937-2          |               | 70           |
| Tear force-weft                                  | N     | ISO 13937-2          |               | 60           |
| Water penetration Hydrostatic head-Original      | mm    | ISO 811 60cm         |               |              |
| Spray test-Original                              | Grade | EN 24920, ISO 4920   |               | 4            |
| Colour fastness to laundering, change in shade   | Grade | EN ISO 105-C06       |               | 4            |
| Staining of multifibre: CA, CO, PA, PES, AC, WO  | Grade | EN ISO 105 C06       |               | 4            |
| Colour fastness to perspiration, change in shade | Grade | EN ISO 105-E04       |               | 4            |
| Staining of multifibre: CA, CO, PA, PES, AC, WO  | Grade | EN ISO 105-E04       |               | 4            |
| Colour fastness to rubbing, dry                  | Grade | EN ISO 105-X12       |               | 4            |
| Colour fastness to rubbing, wet                  | Grade | EN ISO 105-X12       |               | 3-4          |
| Colour fastness to light- Xenon arc light        | Grade | EN ISO 105-B02       |               | 4            |

Remark:BR25010006