

BALLISTIC RESISTANCE TEST

NTS-Belcamp

4603B Compass Point Road
Belcamp, MD 21017

Client: Premier Body Armor
Project No.: OH000011420
Test Date: 06/29/2023
Page 1 of 1

Test Panel Description: Torso plate tested stand alone

Manufacturer: Premier Armor

Sample No.: (Multi Threat, V0) 0362254

Size: 9.75 x 11.50 in
Avg. Thickness: N/A
Thicknesses: N/A

Weight: 7.280 lbs
Plies/Laminates: N/A

Date Received: 06/26/2023
Received Via: UPS Ground
Returned Via: UPS Ground

Setup

Shot Spacing: NIJ-STD-0101.06
Level IV (modified)
Witness Panel: Clay
Backing Material: 5.5-in clay/plywood
Condition: Ambient

Primary Vel. Screens (ft): 37.000, 37.333,
46.666, 47.000
Primary Vel. Location (ft): 42.000
Range to Target (ft): 50.200
Target to Witness (in): 0.000

Range No.: Range 2
Temp: 69 °F
BP: 30 inHg
RH: 42 %
Barrel/Gun: N/A
Gunner: Brett Erisman
Recorder: Bernard Carr

Ammunition

Projectile	Lot No.	Manufacturer	Powder
(1) .30-06 cal, 166-grain APM2 (2) 5.56 x 45-mm, 62-grain M855	TW45 NA	Military Military	N133 N 110

Applicable Standards or Procedures

Clay Drop 1 - Drop Time: 3:00 PM; Block No. WC074173; Temp: 92.3 °F; Drop Depths: 20 mm, 19.7 mm, 18.5 mm, 17 mm, 18.2 mm
(1) NIJ-STD-0101.06 Level IV (Modified)
(2) Customer Request

Shot No.	Ammo	Powder/ Seating	Weight (gr)	Time 1 (μs)	Vel. 1 (ft/s)	Time 2 (μs)	Vel. 2 (ft/s)	Avg. Vel. (ft/s)	Penetration	Deformation (mm)	Obliq. (°)	Footnotes
1	1	43.5	166	3446	2902	3219	2899	2901	None	35.8	0	
2	2	19.6	62	3180	3145	2970	3142	3144	None	14.5	0	

Remarks:

APM2 Required Velocity: 2880 ± 30 ft./s.
Projectile Yaw Check: 0° Yaw on all Impacts.

M855 Required Velocity: 3115 ± 30 ft./s.
Projectile Yaw Check: 0° Yaw on all Impacts.

Footnotes:

N/A