
SOLARWATT M250-60 GET AK black

GLASS-FOIL-SOLAR MODULE



SOLARWATT modules supply the highest yield through optimally matched materials and sorting in tight performance classes. Tested source material, the most careful processing and the strictest test procedures guarantee the longevity of the modules. SOLARWATT modules are exclusively manufactured in Germany. The solar module SOLARWATT M250-60 GET AK black for grid-connected plants connects SOLARWATT's familiar high quality with efficient installation and an outstanding costperformance ratio.

- » more active cell area per module thanks to full square cells
- frame with hollow chamber profile and drainage opening
- high mechanic stability and torsional stiffness
- insulated and against reverse polarity protected connectors
- positive classification range (-0 Wp to + 5 Wp)
- Max. system voltage 1000 V
- cells and used materials are tested disengaged on the basis of test routines
- quality test during all manufacturing steps
- 5 years warranty acc. to Special Warranty Conditions
- resource-conserving, patented packing system QUICKSTAXX®









SOLARWATT AG

Maria-Reiche-Str. 2a 01109 Dresden, Germany Tel. +49 351 8895-0 Fax +49 351 8895-111 info@solarwatt.de www.solarwatt.de

CERTIFIED ACC. TO: DIN EN ISO 9001 and 14001

[NOMENCLATURE OF NAMES OF SOLARWATT MODULES]

TYPE OF CELLS

A=amorphous silicon M = monocristalline silicon P=polycristalline silicon

250

sheet

BENCHMARK FOR

MODULE PERFORMANCE

performance class are

specified in the data

Nominal Power and

NO. OF CELLS

60

GET

LAYER CONSTRUCTION E = EVA

G=Glass K=Synthetics T=Tedlar-composite film

A=Aluminium E = Stainless Steel

L=Laminate (without frame)


CONNECTION

B = RibbonD = Box

K=Cable








GENERAL DATA					
Module Technology	Glass-Foil-Laminate; Aluminium Frame, black				
Cover material Encapsulation Back material	High transparent solar glass (tempered), 4 mm EVA-Solar Cells-EVA Tedlar-Polyester-Tedlar, black				
No. and Type of Cells	60 full square monocrystalline solar cells				
Dimensions of Cells	156 x 156 mm				
Cables	Junction box with tyco plug connector cables 2 x 1,00 m/4 mm²				
Bypass-Diodes	3 pcs.				
Application Class	Class A at IEC 61730				
Dimensions (LxWxH)	1680 x 990 x 50 mm				
Weight	24 kg				
Max. System Voltage	1000 V				
IP Protection Level	IP 65				
Mechanical Ratings	Suction pressure of 2400 Pa approved (Wind speed 130 km/h with safety factor 3) Load of 5400 Pa approved				
Qualifications	IEC 61215 Ed.2, IEC 61730 in preparation				

ELECTRICAL DATA (STC)		STC: Standard Test Conditions: measurement conditions: Radiation strength 1000 W/m², spectral distribution AM 1.5, temperature 25 2 °C, in accordance with EN 60904-3			
Specification	SOLARWATT M250-60 GET AK black				
Nominal Power P _N	225 Wp	230 Wp	235 Wp	240 Wp	245 Wp
Nominal Voltage U _{mpp}	28,2 V	28,4 V	28,5 V	28,7 V	29,0 V
Nominal Current I _{mpp}	7,97 A	8,10 A	8,25 A	8,37 A	8,45 A
Open Circuit Voltage Uoc	36,0 V	36,2 V	36,4 V	36,5 V	36,7 V
Short Circuit Current I _{SC}	8,86 A	8,89 A	8,91 A	8,93 A	8,98 A
I _R *	20 A				
Measuring tolerances P _{max} ±5%; *Reverse current power rating: Operation	n of the modules with an exte	rnal power source is only permitted	with a string fuse with a release curre	ent of < 2 x ISC @ NOCT.	

Reduction in the module efficiency with reduction in radiation strength of 1000 W/m² to 200 W/m² (25°C): $4^{\pm 2}$ % (relative) / -0,6 $^{\pm 0.3}$ % (absolute).

ELECTRICAL DATA (NOCT)			NOCT: Normal Operation Cell Temperature, measurement conditions: Radiation strength 800 W/m², AM 1.5, temperature 20 °C, wind speed 1m/s, electrical open-circuit operation		
Specification	SOLARWATT M250-60 GET AK black				
Nominal Power P _N	164 W	167 W	171 W	175 W	178 W
Nominal Voltage U _{mpp}	25,5 V	25,7 V	25,8 V	26,0 V	26,3 V
Open Circuit Voltage U _{OC}	33,3 V	33,5 V	33,7 V	33,8 V	34,0 V
Short Circuit Current I _{SC}	7,14 A	7,17 A	7,19 A	7,20 A	7,24 A



THERMAL FEATURES	
Operating Temperature Range	-40 +80 °C
Ambiente Temperature Range	-40 +45 °C
Temperature Coefficient of P _N	-0,45%/K
Temperature Coefficient of U _{OC}	-0,37%/K
Temperature Coefficient of I _{SC}	0,04%/K
NOCT	45°C