

BUREAU OF INDIAN STANDARDS

INDIAN STANDARD: IS 269 : 2015

ORDINARY PORTLAND CEMENT (33, 43 AND 53 GRADE) - SPECIFICATION — SPECIFICATION

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002

1 SCOPE

Covers manufacture, chemical and physical requirements of ordinary Portland cement across 33, 43, and 53 strength grades.

Table 1: Physical and Mechanical Properties (Clause 6.1)

Grade	3-Day Strength (Min)	7-Day Strength (Min)	28-Day Strength (Min)	Soundness (Max)
OPC 33	16 MPa	22 MPa	33 MPa	10 mm
OPC 43	23 MPa	33 MPa	43 MPa	10 mm
OPC 53	27 MPa	37 MPa	53 MPa	10 mm