

Ratio In Mixing Cement And Concrete

1. When Mixing With A Bucket

	Cement	River Sand	Stone
Low-strength concrete	15 Mpa 1 	3 1/2   	3 1/2   
Medium-strength concrete	25 Mpa 1 	2 1/2  	2 1/2  
High-strength concrete	30 Mpa 1 	1 3/4  	1 3/4  

2. When Mixing With A Wheelbarrow

Low -strength Concrete

Cement	River Sand	Stone
15 Mpa  1 Bag	2 Wheelbarrows  	2 Wheelbarrows  

Medium-strength Concrete

Cement	River Sand	Stone
25 Mpa  1 Bag	1 1/2 Wheelbarrows  	1 1/2 Wheelbarrows  

High-strength Concrete

Cement	River Sand	Stone
30 Mpa  1 Bag	1 Wheelbarrow 	1 Wheelbarrow 

Feedback : Activity

Kwa Thema Skills School

Subject : Maintenance

Marks : 12

Grade : Year 2

Time : 30 mins

Date : / /

Question : 1

1. Complete The Concrete Mixing Ratio When Using A Bucket.

	Cement	River Sand	Stone
Low-strength concrete	15Mpa 1 Bucket		
Medium-strength concrete	25Mpa 1 Bucket		
High-medium concrete	30Mpa 1 Bucket		

2. Complete The Concrete Mixing Ratio When Using A Wheelbarrow.

	Cement	River Sand	Stone
Low-strength concrete	15Mpa 1 Wheelbarrow		
Medium-strength concrete	25Mpa 1 Wheelbarrow		
High-strength concrete	30Mpa 1 Wheelbarrow		

How To Do Wet Work In A Foundation And On A Floor

1. Foundation

Step 1 : Main soil moisture.

Step 2 : Prevent soil erosion.

Step 3 : Counteract drought effects.

Step 4 : Minimize swelling in expansion soil.

Step 5 : Water your foundation.

2. Flooring

Step 1 : Spread the concrete.

Step 2 : Screed the surface.

Step 3 : Float the surface.

Step 4 : Edge the floor.

Step 5 : Groove joint.

Step 6 : Trowel the surface or floor.

Video :

- https://youtu.be/3D11YX_DhZA

Feedback : Demonstration