

Building and Plastering Materials

1. River Sand



- It is used for making surfaces or floors.

3. Plaster Sand



- It is used plastering walls.

5. Cement



- It is used for mixing with sands or concrete mix and water to make mortar

3. Building Sand



- It is used for building walls.

4. Concrete Mix



- It is used for making foundations and floors.

6. Water



- It is used for mixing with sands or concrete mix and cement to make mortar.

7. Stock Bricks



- It is used for building walls..

9. Blocks Bricks



- It is used for building walls.

Video :

- <https://youtu.be/a1cQclJfjPw>

Feedback : 1. Activity

2. Demonstration

8. Maxi Bricks



- It is used for building walls.

10. Paving Bricks



- It is used for paving floors.

Kwa Thema Skills School

Subject : Maintenance

Grade : Year 4

Date :

Marks : 10

Time : 30 mins

Question:1

1. Identify the following building and plastering materials.



1. _____



2. _____



3. _____



4. _____



5. _____



7. _____



9. _____



6. _____



8. _____



10. _____

Ratio of Concrete Mix

When using a bucket

	Cement	River Sand	Stone
Low-strength concrete 15 Mpa	 1	 $3\frac{1}{2}$	 $3\frac{1}{2}$
Medium-strength concrete 25 Mpa	 1	 $2\frac{1}{2}$	 $2\frac{1}{2}$
High-strength concrete 30 Mpa	 1	 $1\frac{3}{4}$	 $1\frac{3}{4}$

Video :

- <https://youtu.be/4QqG5HN5ZnM>

When using a wheelbarrow

Low-strength Concrete

Cement	River Sand	Stone
15 Mpa 		
1 Bag	2 Wheelbarrows	2 Wheelbarrows

Medium-strength Concrete

Cement	River Sand	Stone
25 Mpa 		
1 Bag	1½ Wheelbarrows	1½ Wheelbarrows

High -strength Concrete

Cement	River Sand	Stone
30 Mpa 		
1 Bag	1 Wheelbarrow	1 Wheelbarrow

Video :

- <https://youtu.be/up8M8RWz1-0>

Feedback : 1. Activity

2. Demonstration

Kwa Thema Skills School

Subject : Maintenance

Grade : Year 4

Date : / /

Marks : 10

Time : 30 mins

Question:1

1. Complete the ratios below

When using a bucket

	Cement	River Sand	Stones
Low-strength Concrete 15 Mpa	1 bucket		
Medium-strength Concrete 25 Mpa	1 bucket		
High-strength Concrete 30 Mpa	1 bucket		

When using a wheelbarrow

	Cement	River Sand	Stones
Low-strength Concrete 15 Mpa	1 bag		
Medium-strength Concrete 25 Mpa	1 bag		
High-strength Concrete 30 Mpa	1 bag		