Material	V ₂ O ₅	Cu-zeolite	Fe-zeolite
Thermal stability and thermal resistance	-	++	+
Low temperature performance with low NO ₂	0	+	-
High temperature performance	Ο	0	+
Performance at low NH ₃ storage level	+	+	0
HC poisoning	Ο	0	-
Sulfur resistance	0	-	O
Influence of NO ₂ /NO _x ratio on efficiency	Ο	+	-
NH ₃ storage capacity	0	++	+
Explanation: +: high, o: medium, -: low			