



3D Printing PLA+ (pro) Filament

TECHNICAL DATA SHEET

VOXELPLA+ (PRO)

TRADING NAME: VOXELPLA+ (PRO)

RAW MATERIAL: PLA

FORM: 1.75MM FILAMENT

APPLICATIONS: 3D PRINTING

The product is modified on the base PLA material to increase strength(layer adherence and toughness), reliability, and ease of printing. Our PLA+ (PRO) is excellent for rapid prototyping, cosplay, mechanical parts, models, or other applications.

MATERIAL SPECIFICATION:

PROPERTIES	TESTING METHODOLOGY	TYPICAL VALUE	UNITS
Density	GB/T 1033	1.23	g/cm ³
Melt Flow Index	GB/T 3682 (200C/2.16KG)	5-10	g/10 min
Tensile Strength	GB/T 1040	47	MPa
Elongation at Break	GB/T 1040	7	%
Flexural Strength	GB/T 9341	95	MPa
Flexural Modulus	GB/T 9341	3580	MPa
IZOD Impact Strength	GB/T 1843	5	KJ/m ²
Heat Distortion Temputure	GB/T 1634	53	C

RECOMMENDED PRINTING SETTING:

BOWDEN STYLE EXTRUDER

Extruder Temperature:	200 - 210C
Bed Temperature:	45 - 60C
Fan Speed:	100%
Retraction Speed:	60mm/s
Retraction Amount:	5mm

DIRECT EXTRUDER

Extruder Temperature:	200 - 210C
Bed Temperature:	45 - 60C
Fan Speed:	100%
Retraction Speed:	50mm/s
Retraction Amount:	1mm

TESTING SPECIFICATION:

		
GB/T 1040 Tensile	GB/T 9341 Bending	GB/T 1043 Impact

Testing Specimen	Testing Specimen	Testing Specimen
------------------	------------------	------------------

PRINTING SETTING

Extruder Temperature:	200C
Bed Temperature:	45 C
Fan Speed:	100%
Retraction Speed:	60mm/s
Retraction Amount:	5mm
Infill Percentage:	20%
Perimeter:	4
Top/Bottom Layer:	4

Disclaimer:

The typical values presented in this data sheet are intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. Actual values may vary significantly with printing conditions. End-use performance of printed parts depends not only on materials, but also on part design, environmental conditions, printing conditions, etc. Product specifications are subject to change without notice. Each user is responsible for determining the safety, lawfulness, technical suitability, and disposal/ recycling practices of VOXELPLA materials for the intended application. VOXELPLA makes no warranty of any kind, unless announced separately, to the fitness for any use or application. VOXELPLA shall not be made liable for any damage, injury, or loss induced from using VOXELPLA materials in any application.