

MoldPilot Process Sheet Export
Project: M-PILOT-01

Trial Result

T0: Not Approved / Rework Required

T1: No result

Process Sheet Comparison

Material Rep Name and Company: - | -

Material Grade: ABS PA-757 | ABS PA-757

Drying Time (hr): 3 | -

Drying Temperature (deg C): 80 | -

Machine Name: LianChuang | LianChuang

Machine Number: 10 | 10

Press Tonnage (T): 408 | 408

Clamp Tonnage Used (T): 240 | 250

Nozzle Orifice (mm): 5 | -

Shot Capacity (g): 1145 | -

Cycle Time (sec): 42 | 44

Cooling Time (sec): 18 | 20

Injection Time (sec): 2.8 | -

Barrel Zone 1 Temperature (deg C): 215 | -

Barrel Zone 2 Temperature (deg C): 220 | -

Barrel Zone 3 Temperature (deg C): 225 | -

Nozzle Temperature (deg C): 230 | -

Velocity Stage 1 (mm/s): 60 | -

Velocity Stage 2 (mm/s): 45 | -

Velocity Stage 3 (mm/s): 28 | -

Hold Pressure Stage 1 (bar): 720 | 760

Hold Pressure Stage 2 (bar): 560 | 590

Hold Time (sec): 8 | -

Back Pressure (bar): 55 | -

Screw Speed (rpm): 85 | -

Cushion (mm): 5.2 | -

Tool Name / Number: M-PILOT-01 | -

Number of Cavities: 1 | -

Part Weight Average (g): 553.1 | -

Hot Runner Zone 1 Temperature (deg C): - | -

Hot Runner Zone 2 Temperature (deg C): - | -

Shot 1 Part Weight (g): 553.2 | -

Shot 2 Part Weight (g): 552.8 | -

Shot 3 Part Weight (g): 553.4 | -

Shot 4 Part Weight (g): 553 | -

Shot 5 Part Weight (g): 552.9 | -

Shot 6 Part Weight (g): 553.3 | -

Issue Summary

Gate insert needs vent and land correction (T0) (In Progress)

Packing window unstable during T0 (T0) (Open)

Critical dimension out of tolerance (T0) (Waiting Verification)

Client feedback: cosmetic witness line (T0) (Waiting Customer)

Next Step

Verify T0 mold correction, injection window, QC dimensions, and sanitized customer cosmetic feedback.