

foil paste

Character:

Appearance: light yellow color paste

Viscosity: 100000-120000 CPS

Application: cotton, lycra and swimsuit, etc.

Operation suggestions:

1.100-120 mesh;

2.Printing paste 2-3 times—130-150 °C baking 2-3 minutes by tunnel or natural drying
24h---150°C press 10-15 seconds.

Performance test: 40°C washing 2hours by machine will not fall off the foil.

