

Technical data sheet

Photochromic paste

Appearance: milky white light red/yellow/blue/orange/purple/pink/green paste
Viscosity: 120000 cps Application: normal knitted fabric photochromic color printing.

Operation suggestions:

1. 100-120 mesh.
2. **For light color fabric,** directly printing 1-2 times or print the clear rubber paste then print photochromic paste 2-4 times.
3. **For dark color fabric,** printing white rubber paste 2-3 times---then printing photochromic paste 2-3 times Natural drying 24 hours or 130°C drying 2-3 mins by tunnel (drying machine).

info@spi-egy.com

www.spi.com.eg

Prepared by:

SPI Scientific team