

# MSE 160 Lecture Notes

Hei Shing Cheung

Molecules and Materials, Winter 2024

MSE 160

The up-to-date version of this document can be found at <https://github.com/HaysonC/skulenotes>

*"In this class we are mostly understanding solids"*  
- Prof. SCOTT RAMSAY

## 1 Mechanical Behavior

**Classes of Materials** In this class, we look at three classes of materials (non-exhaustive):

- **Metal** held together with metallic bonds, typically **ductile** and **conductive**.
- **Ceramics** (often metal oxides [excp: diamond]) held together via covalent & ionic bonds, typically **brittle** and **insulating**.
- **Polymers Molecules** (often hydrocarbons) typically **ductile** and **insulating**

**Engineering Stress** For normal stress, we know that:

$$\sigma = \frac{F}{A_0} \quad (1)$$

**Engineering Strein** Also:

$$\epsilon = \frac{\Delta l}{l_0} \quad (2)$$

**Young's Moduclus** For elastic deformation,  $E$ , is given, by Hooke's Law, as follows:

$$\sigma = E\epsilon \quad (3)$$

**Tensile Test** We apply force as to the ends of a dogbone-sample, with  $l_0$  being the gauge length and  $A_0$  being the area of the cross-section at the middle.

**Tensile Strein** Maximum tensile strain on the engineeing stress-strain curve.

## 1.1 Understanding Elastic Properties in terms of Atomic Configuration

**Atomic Configuration** We can understand the elastic properties of a material by looking at the atomic configuration. Schematically, we can represent the atomic configuration as a spring system:

1. **Initial - Before Loading** Atoms are in equilibrium, with the interatomic forces being balanced.
2. **Loading** We apply a force to the material, causing the atoms to move from their equilibrium positions. The bond stretches and the atoms move further apart.
3. **Unloading** We remove the force, causing the atoms to return to their equilibrium positions.

**Atom Positions** Elastic modulus is dependent on the atomic interatomic bonding force. Thus, The elastic modulus is proportional to the slope of the interatomic force-separation curve.

**Force-Separation Curve** The force-separation curve is a plot of the force between two atoms as a function of the distance between them. The slope of the curve is proportional to the elastic modulus near the equilibrium position.




Figure 1: Force-Separation Curve (Lennard-Jones Force)

$$E \propto \left. \frac{dF}{dr} \right|_{r_0} \quad (4)$$

**Definition 1.1.1** (Equilibrium interatomic separation distance). The equilibrium interatomic separation distance,  $r_0$ , is the distance between two atoms at which the interatomic force is zero. This is due to the interatomic forces being the sum of attractive and repulsive forces.

**Elastic Modulus** Thus, strongly bonded materials have a higher elastic modulus and the slope of the force-separation curve is steeper at  $r_0$ .

## 1.2 Understanding Other Properties in terms of Atomic Configuration

**Potential Energy-Separation Curve** The potential energy-separation curve is a plot of the potential energy between two atoms as a function of the distance between them. The potential energy is the area under the force-separation curve.

**Depth of the Minimum Energy Well** The depth of the minimum energy well,  $E_0$ , is the energy required to break the bond between two atoms. This is the energy required to move the atoms from the equilibrium position to infinity. It is proportional to the melting temperature of the material.




Figure 2: Potential Energy-Separation Curve

**Coefficient of Thermal Expansion** The coefficient of thermal expansion,  $\alpha$ , is the fractional change in length per degree change in temperature.

**Depth of Potential Energy Curve** The deeper the potential energy curve, the higher the melting temperature and more symmetric the curve near  $E_0$ . This would give the following three properties:

1. **Higher Melting Temperature** The higher the melting temperature, the deeper the potential energy curve.
2. **Higher Elastic Modulus** The steeper the slope of the force-separation curve at  $r_0$ , the higher the elastic modulus.
3. **Lower Coefficient of Thermal Expansion** The more symmetric the potential energy curve near  $E_0$ , the lower the coefficient of thermal expansion.

### 1.3 Shear and Tensile Stress

#### 1.3.1 Shear

**Shear Stress** Shear stress is the force per unit area acting parallel to the surface. It is given by:

$$\tau = \frac{F}{A_0} \quad (5)$$

**Shear Strain** Shear strain is the change in angle between two lines originally perpendicular to each other. It is given by:

$$\gamma = \frac{\Delta l}{l_0} \approx \tan \theta \approx \theta = \frac{\pi}{2} - \phi \quad (6)$$

**Shear Modulus** The shear modulus,  $G$ , is the ratio of shear stress to shear strain. It is given by:

$$\tau = G\gamma \quad (7)$$

**Relationship between Shear and Tensile Modulus** The shear modulus is related to the tensile modulus by the following equation:

$$G = \frac{E}{2(1 + \nu)} \quad (8)$$

where  $\nu$  is the Poisson's ratio.

**Poisson's Ratio** Poisson's ratio,  $\nu$ , is the ratio of lateral strain to axial strain. It is given by:

$$\nu = -\frac{\epsilon_{\text{lat}}}{\epsilon_{\text{axial}}} \quad (9)$$

### 1.4 Testing

**Definiton 1.4.1** (Gauge Length). The gauge length,  $l_0$ , is the length of the sample over which the strain is measured.

**Definiton 1.4.2** (Reduced Section). The reduced section is the part of the sample where the cross-sectional area is reduced to a smaller value.

Gauge length is always no longer than the reduced section. The reduced section is where the sample will likely break.

---

**Testing Ceramics** In relation to tensile testing, ceramics have the following properties:

- **Brittle** Ceramics are brittle and will break suddenly.
- **High Strength** Ceramics have high strength and thus difficult to machine the sample.
- **Sample Alignment** The sample must be aligned properly to test for pure tension. Unlike metals and polymers, which are self-aligning.
- **Fracture** Ceramics will fracture while still off-axis. Hence, there would be a large shear component.

Thus, we often approximate tensile behaviour with a point loading on a horizontal beam, with two point support (3 point bending test). Peak stress is given by:

$$\sigma_{\text{peak}} = \frac{3FL}{2bd^2} \quad (10)$$

, where:

- $L$  (span) is the distance between the two supports.
- $b$  is the width of the sample
- $d$  is the thickness/depth of the sample

## 2 Selection of Materials

### 2.1 Material Performance

**Example 2.1.1** (Aircraft Wing Spar). The aircraft wing spar is beam (loaded in bending) that supports the wing. The spar is made of a material with the objective of minimize mass under the following constraints:

- **Deflection** There is a maximum allowable deflection of the wing.
- There is more..., but for this example, we will only consider the deflection.

The material selection solve for a **light stiff beam**.

**Mass** The mass of the beam is given by:

$$m = \rho V = \rho AL$$

## 2.2 Density

---

**Deflection** The deflection of the beam is given by:

$$\delta = \frac{FL^3}{48EI} \quad (11)$$

For a beam with a rectangular cross-section, we have:

$$\delta = \frac{FL^3}{48E} \cdot \frac{12}{bh^3} = \frac{FL^3}{4Ebh^3}$$

We can set  $b$  proportional to  $h$ :

$$\delta = \frac{FL^3}{cE} \cdot \frac{1}{A^2}, \quad \text{for some constant } c$$

We can then isolate for  $A$ , the free variable, and minimize the mass via the objective equation  $m = \rho AL$ :

$$A = \sqrt{\frac{FL^3}{cE\delta}}$$
$$m = \rho L \sqrt{\frac{FL^3}{cE\delta}} = \rho L \sqrt{\frac{FL^3}{cE\delta}}$$

Arrange into the form (functional)(geometric)(material):

$$m = \left(\frac{F}{c\delta}\right)^{\frac{1}{2}} \cdot \left(L^{\frac{5}{2}}\right) \cdot \left(\frac{\rho}{E^{\frac{1}{2}}}\right)$$

**Material Performance Index** The material performance index is given by:

$$\text{Material Performance Index (MSI)} = \frac{E^{\frac{1}{2}}}{\rho} \quad (12)$$

**MPI Graph** We plot  $\log E$  against  $\log \rho$  to get the MPI graph.

**Tempered Glass** Tempered glass are made to resist tension. It is done by applying a compressive stress to the surface of the glass. This is done by cooling the surface of the glass faster than the core or chemically treating the surface.

## 2.2 Density

**Density** The density of a material is given by:

$$\rho = \frac{m}{V} \quad (13)$$

---

**Archimedes' Principle** The buoyant force on an object is equal to the weight of the fluid displaced by the object. Derive from that, we have:

$$\rho = \frac{m}{V} = \frac{m_{\text{object}}}{m_{\text{object}} - m_{\text{object in fluid}}} \quad (14)$$

## 3 Atomic Structures

### 3.1 General Definitions

**Ordered structures** We have the following three orders:

1. **Long Range Order (LRO)** Atoms are arranged in a well-defined pattern over long distances in repeating units.  
(Example) Diamonds, some polymers, most metals, many ceramics, graphite, quartz, etc.
2. **Short Range Order (SRO)** Periodic arrangement of atoms over a few atomic or molecular spacings.  
(Example) Most polymers, glasses, amorphous materials, etc.
3. **No Order (NO)** Atoms are randomly arranged.  
(Example) Ideal gases, etc.

**Describing Crystal Structures** We can describe crystal structures by the following:

- **Unit Cell** The smallest repeating unit of a crystal structure that could be used to represent the entire crystal.
- **Lattice** The repeating arrangement of points that represent the positions of atoms in the unit cell.  
(Example) Simple Cubic, Body-Centered Cubic, Face-Centered Cubic, etc.
- **Lattice Plus Basis** *Not required for this course*

**Theoretical Density of Metals** The theoretical density of metals is given by:

$$\rho = \frac{nM}{V_c N_A} \quad (15)$$

, where:

- $n$  is the number of atoms in the unit cell.
- $M$  is the atomic mass of the element (amu = g/mol).
- $V_c$  is the volume of the unit cell.
- $N_A$  is Avogadro's number ( $6.022 \times 10^{23} \text{mol}^{-1}$ )

### 3.2 Describing Basic Unit Cells

**Definiton 3.2.1** (Coordination Number (CN)). The coordination number is the number of nearest neighbors an atom has in a crystal structure.

**Definiton 3.2.2** (Atomic Packing Factor (APF)). The atomic packing factor is the fraction of the volume of the unit cell that is occupied by hard spheres. It is given by:

$$\text{APF} = \frac{\text{Volume of atoms in unit cell}}{\text{Volume of unit cell}} \quad (16)$$

**Simple Cubic (SC)** The simple cubic structure has the following properties:

- **Centers of atoms** Located at the eight corners of a cube
- **Rare Packing Density** Due to low packing density (only known example: Polonium, Po)
- **Close-packed directions** As cube edges.
- **Coordination Number** Number of nearest neighbor: 6

**Face-Centered Cubic (FCC)** The face-centered cubic structure has an atom on the centre of each face of the cube. It has the following properties:

- **Ductile and Malleable** due to the close-packed planes. Common examples include: Al, Cu, Au, Ag.
- **Coordination Number** Number of nearest neighbor: 12
- **Close-packed directions** As cube diagonals.
- **Theoretical Density** The theoretical density of FCC is derived from Equation (15):

$$\rho = \frac{nM}{V_c N_A}$$

With  $n = 4$  (8 corners  $\times \frac{1}{8}$  atom each + 6 faces  $\times \frac{1}{2}$  atom each) and  $V_c = a^3$  (where  $a$  is the **lattice parameter**):

$$\rho_{\text{FCC}} = \frac{4M}{a^3 N_A}$$

We can then obtain  $a$  via the relationship between the atomic radius,  $r$ , and the lattice parameter via the geometry on the close-packed direction (face diagonal):

$$a = 2\sqrt{2}r$$

Substitute  $a$  back into the equation:

$$\begin{aligned} \rho_{\text{FCC}} &= \frac{4M}{(2\sqrt{2}r)^3 N_A} = \frac{4M}{16\sqrt{2}r^3 N_A} \\ &= \frac{M}{4\sqrt{2}r^3 N_A} \end{aligned} \quad (17)$$



- **Atomic Packing Factor** The atomic packing factor of FCC is given by:

$$\text{APF}_{\text{FCC}} = \frac{\text{Volume of atoms in unit cell}}{\text{Volume of unit cell}} = \frac{4 \times \frac{4}{3}\pi r^3}{a^3} = \frac{4 \times \frac{4}{3}\pi r^3}{(2\sqrt{2}r)^3} = \frac{\pi}{6\sqrt{2}} = \mathbf{0.74} \quad (18)$$

This is the highest possible packing factor for spheres. Thus, no other structure can have a higher packing factor.

**Example 3.2.3** (Density of Aluminum). Given that the atomic radius of aluminum is  $r = 143$  pm and the atomic mass is  $M = 26.98$  g/mol, we can calculate the density of aluminum with FCC structure. We have:

$$\begin{aligned} \rho_{\text{Al}} &= \frac{M}{4\sqrt{2}r^3 N_A} = \frac{26.98}{4\sqrt{2} \times (143 \times 10^{-12})^3 \times 6.022 \times 10^{23}} \\ &= \frac{26.98}{4\sqrt{2} \times (143 \times 10^{-12})^3 \times 6.022 \times 10^{23}} = 2.7 \text{ g/cm}^3 \end{aligned}$$

## 4 Geometric Descriptions of Crystals

### 4.1 Crystallographic Directions and Planes

**Point Coordinates** A lattice position in a unit cell is determined as fractional multiples of the unit cell edge lengths  $a$ ,  $b$ , and  $c$ . (Defining the origin at one corner of the unit cell and  $a = b = c = 1$ )

**Crystallographic Directions** A crystallographic direction is a line between two points in a crystal. It is denoted by square brackets,  $[uvw]$ . The direction is determined from the “tail” to the “head” of the vector. Also:

1. It **shall not** include commas; and
2. It **shall be reduced** to the smallest integers; and
3. Negative signs are represented by a bar over the number.

**Example 4.1.1.** The crystallographic direction from  $(0, 0, 0)$  to  $(-1, 0, 1/2)$  is  $[\bar{2}01]$ .

**Family of Directions** A family of directions is a set of directions that are parallel to each other. It is denoted by  $\langle uvw \rangle$ .

**Example 4.1.2.** The family of directions  $\langle 100 \rangle$  is the set of directions  $[100]$ ,  $[010]$ ,  $[001]$ ,  $[\bar{1}00]$ ,  $[0\bar{1}0]$ , and  $[00\bar{1}]$ .

**Angle between Directions** The angle between two directions in a **cubic** crystal is given by:

$$\cos \theta = \frac{h_1 h_2 + k_1 k_2 + l_1 l_2}{\sqrt{h_1^2 + k_1^2 + l_1^2} \sqrt{h_2^2 + k_2^2 + l_2^2}} \quad (19)$$

, which is simply the normalized dot product of the two vectors.

Constants and conversions

1 atm = 101.325 kPa = 1.013 25 bar = 14.696 psi  
N<sub>A</sub> = 6.022 × 10<sup>23</sup> mol<sup>-1</sup>  
e = 1.602 × 10<sup>-19</sup> C  
1 eV = 1.602 × 10<sup>-19</sup> J  
ε<sub>0</sub> = 8.854 × 10<sup>-12</sup> F m<sup>-1</sup>  
R = 8.314 J mol<sup>-1</sup> K<sup>-1</sup>  
0.082 067 L atm mol<sup>-1</sup> K<sup>-1</sup>  
0 °C = 273.15 K  
k = 8.62 × 10<sup>-5</sup> eV atom<sup>-1</sup> K<sup>-1</sup>  
1.38 × 10<sup>-23</sup> J atom<sup>-1</sup> K<sup>-1</sup>  
F = 96 486 C mol<sup>-1</sup>  
h = 6.626 × 10<sup>-34</sup> J s  
4.136 × 10<sup>-15</sup> eV s  
c = 2.99 × 10<sup>8</sup> m s<sup>-1</sup>  
g = 9.81 m s<sup>-2</sup>

Microstructure

$LD = \frac{\#}{\text{Length}}$   
 $PD = \frac{\#}{\text{Area}}$   
 $V = \frac{4}{3}\pi r^3$   
 $A_{\text{triangle}} = \frac{1}{2}bh$   
 $\rho = \frac{n_A A_A + n_C A_C}{V_{CNA}}$   
 $N = \frac{N_A \rho}{A}$   
 $a = 2\sqrt{2}R$   
 $d_{\text{hkl}} = \frac{a}{\sqrt{h^2 + k^2 + l^2}}$   
 $n_n = \frac{\overline{M}_n}{\overline{m}}$   
 $n_\lambda = 2d_{\text{hkl}} \sin \theta$   
 $n_w = \frac{\overline{M}_w}{\overline{m}}$

Mechanical Behaviour

$\sigma = \frac{F}{A_0}$   
 $\sigma = E\epsilon$   
 $\sigma_T = \sigma(1 + \epsilon)$   
 $\sigma_T = \frac{F}{A_i}$   
 $E = 2G(1 + \nu)$   
 $\nu = -\frac{\epsilon_x}{\epsilon_z} = -\frac{\epsilon_y}{\epsilon_z}$   
 $\sigma_{3\text{-point}} = \frac{3FL}{2wh^2}$   
 $\epsilon_T = \ln(1 + \epsilon)$   
 $\sigma_T = K\epsilon_T^n$

Magnetic Behaviour

$H = \frac{NI}{L}$   
 $M = \chi_m H$   
 $B = (1 + \chi_m)\mu_0 H$   
 $\beta = 9.27 \times 10^{-24} \text{ Am}^2$   
 $B_0 = \mu_0 H$   
 $B = \mu_0 H + \mu_0 M$   
 $\mu_B = \frac{e\hbar}{2m_e} = \beta$

Electrical Behaviour

$\sigma = n|e|\mu_e + p|e|\mu_h$      $\sigma = n|e|\mu_e$   
 $\sigma = p|e|\mu_h$

Electrochemistry

$E = E^\circ - \frac{RT}{nF} \ln Q$      $I = \frac{nC}{t}$   
 $E_{\text{at } 25^\circ\text{C}} = E^\circ - \frac{0.0592}{n} \ln Q$   
 $w = nFE^\circ$

Thermodynamics

$PV = nRT$      $\Delta U = q + w$   
 $\Delta U = q - P_{\text{ext}}\Delta V$      $H \equiv U + PV$   
 $G \equiv H - TS$      $\Delta S = \frac{q_{\text{rev}}}{T}$   
constant T:  $\Delta G = \Delta H - T\Delta S$   
 $q = mc\Delta T$      $q = nC_P\Delta T$   
For  $aA + bB \rightarrow cC + dD$ ,  $Q = \frac{a^c c^d}{a^a a^b}$   
 $\Delta_r G = \Delta G^\circ + RT \ln Q$   
 $\Delta_r H^\circ = (\Sigma v_i \Delta_f H^\circ)_{\text{prod.}} - (\Sigma v_i \Delta_f H^\circ)_{\text{react.}}$   
 $\Delta_r S^\circ = (\Sigma v_i \Delta_f S^\circ)_{\text{prod.}} - (\Sigma v_i \Delta_f S^\circ)_{\text{react.}}$   
 $W_{\text{phase}} = \frac{\text{length of opp. side of lever}}{\text{total length of lever}}$   
 $E = h\nu = \frac{hc}{\lambda}$   
Specific heats and heat capacities

Substance	$c \left( \frac{J}{g \cdot K} \right)$	$C_P \left( \frac{J}{mol \cdot K} \right)$
Air(g)	1.0	-
CO <sub>2</sub> (g)	0.843	37.1
H <sub>2</sub> (g)	14.304	28.836
H <sub>2</sub> O(g)	2.03	36.4
H <sub>2</sub> O(l)	4.184	75.3
H <sub>2</sub> O(s)	2.09	37.7
NaCl	0.853	50.5
O <sub>2</sub> (g)	0.918	29.378

Temperatures and enthalpies of phase changes

Substance	M.P. (°C)	$\Delta_{fus} H \left( \frac{kJ}{mol} \right)$	B.P. (°C)	$\Delta_{vap} H \left( \frac{kJ}{mol} \right)$
Al	658	10.6	2467	284
Ca	851	9.33	1487	162
CH <sub>4</sub>	-182	0.92	-164	8.18
H <sub>2</sub> O	0	6.01	100	40.7
Fe	1530	14.9	2735	354

Standard formation enthalpy, standard entropy and standard formation Gibbs energy at 298.15 K

Species	$\Delta_f H^\circ \left( \frac{kJ}{mol} \right)$	$S^\circ \left( \frac{J}{mol \cdot K} \right)$	$\Delta_f G^\circ \left( \frac{kJ}{mol} \right)$
C	0	5.74	0
CH <sub>4</sub> (g)	-74.81	186.2	-50.75
C <sub>2</sub> H <sub>2</sub> (g)	-83.9	200.93	-
C <sub>3</sub> H <sub>8</sub> (g)	-103.8	269.9	-23.49
CaC <sub>2</sub> (s)	-59.8	70.3	-
CaO(s)	-635	38.1	-
CaF <sub>2</sub> (s)	-1225	68.87	-1162
CaF <sub>2</sub> (l)	-1186	92.6	-
Ca(OH) <sub>2</sub> (s)	-987.0	83.0	-
CO <sub>2</sub> (g)	-393.5	213.6	-394.4
Cu <sub>2</sub> O(s)	-168.6	93.1	-
Cu <sub>2</sub> O(l)	-154.79	-	-
Cu(s)	-	33.2	-
Fe(s)	0	27.3	0
Fe <sub>2</sub> O <sub>3</sub> (s)	-824.2	87.4	-
H <sub>2</sub> (g)	-	130.68	-
H <sub>2</sub> O(g)	-241.8	188.7	-228.6
H <sub>2</sub> O(l)	-285.8	69	-
O <sub>2</sub> (g)	0	205.0	0

Miscellaneous enthalpies

Substance	Reaction	$\Delta H \left( \frac{kJ}{mol} \right)$
F <sub>2</sub>	$F_2 \rightarrow F(g)$	157
F	$F(g) \rightarrow F^-(g)$	-328
Ca	$Ca(g) \rightarrow Ca^{2+}(g)$	1734
NaCl	$NaCl(s) \rightarrow Na^+(aq) + Cl^-(aq)$	3.9

# IUPAC Periodic Table of the Elements

1																	18	
1 <b>H</b> hydrogen 1.0080 ± 0.0002																	2 <b>He</b> helium 4.0026 ± 0.0001	
3 <b>Li</b> lithium 6.94 ± 0.06	4 <b>Be</b> beryllium 9.0122 ± 0.0001																	10 <b>Ne</b> neon 20.180 ± 0.001
11 <b>Na</b> sodium 22.990 ± 0.001	12 <b>Mg</b> magnesium 24.305 ± 0.002																	17 <b>Cl</b> chlorine 35.45 ± 0.01
19 <b>K</b> potassium 39.098 ± 0.001	20 <b>Ca</b> calcium 40.078 ± 0.004	21 <b>Sc</b> scandium 44.956 ± 0.001	22 <b>Ti</b> titanium 47.867 ± 0.001	23 <b>V</b> vanadium 50.942 ± 0.001	24 <b>Cr</b> chromium 51.996 ± 0.001	25 <b>Mn</b> manganese 54.938 ± 0.001	26 <b>Fe</b> iron 55.845 ± 0.002	27 <b>Co</b> cobalt 58.933 ± 0.001	28 <b>Ni</b> nickel 58.693 ± 0.001	29 <b>Cu</b> copper 63.546 ± 0.003	30 <b>Zn</b> zinc 65.38 ± 0.02	31 <b>Ga</b> gallium 69.723 ± 0.001	32 <b>Ge</b> germanium 72.630 ± 0.008	33 <b>As</b> arsenic 74.922 ± 0.001	34 <b>Se</b> selenium 78.971 ± 0.008	35 <b>Br</b> bromine 79.904 ± 0.003	36 <b>Kr</b> krypton 83.798 ± 0.002	
37 <b>Rb</b> rubidium 85.468 ± 0.001	38 <b>Sr</b> strontium 87.62 ± 0.01	39 <b>Y</b> yttrium 88.906 ± 0.001	40 <b>Zr</b> zirconium 91.224 ± 0.002	41 <b>Nb</b> niobium 92.906 ± 0.001	42 <b>Mo</b> molybdenum 95.95 ± 0.01	43 <b>Tc</b> technetium [97]	44 <b>Ru</b> ruthenium 101.07 ± 0.02	45 <b>Rh</b> rhodium 102.91 ± 0.01	46 <b>Pd</b> palladium 106.42 ± 0.01	47 <b>Ag</b> silver 107.87 ± 0.01	48 <b>Cd</b> cadmium 112.41 ± 0.01	49 <b>In</b> indium 114.82 ± 0.01	50 <b>Sn</b> tin 118.71 ± 0.01	51 <b>Sb</b> antimony 121.76 ± 0.01	52 <b>Te</b> tellurium 127.60 ± 0.03	53 <b>I</b> iodine 126.90 ± 0.01	54 <b>Xe</b> xenon 131.29 ± 0.01	
55 <b>Cs</b> caesium 132.91 ± 0.01	56 <b>Ba</b> barium 137.33 ± 0.01	57-71 lanthanoids	72 <b>Hf</b> hafnium 178.49 ± 0.01	73 <b>Ta</b> tantalum 180.95 ± 0.01	74 <b>W</b> tungsten 183.84 ± 0.01	75 <b>Re</b> rhenium 186.21 ± 0.01	76 <b>Os</b> osmium 190.23 ± 0.03	77 <b>Ir</b> iridium 192.22 ± 0.01	78 <b>Pt</b> platinum 195.08 ± 0.02	79 <b>Au</b> gold 196.97 ± 0.01	80 <b>Hg</b> mercury 200.59 ± 0.01	81 <b>Tl</b> thallium 204.38 ± 0.01	82 <b>Pb</b> lead 207.2 ± 1.1	83 <b>Bi</b> bismuth 208.98 ± 0.01	84 <b>Po</b> polonium [209]	85 <b>At</b> astatine [210]	86 <b>Rn</b> radon [222]	
87 <b>Fr</b> francium [223]	88 <b>Ra</b> radium [226]	89-103 actinoids	104 <b>Rf</b> rutherfordium [261]	105 <b>Db</b> dubnium [268]	106 <b>Sg</b> seaborgium [269]	107 <b>Bh</b> bohrium [270]	108 <b>Hs</b> hassium [269]	109 <b>Mt</b> meitnerium [271]	110 <b>Ds</b> darmstadtium [281]	111 <b>Rg</b> roentgenium [282]	112 <b>Cn</b> copernicium [285]	113 <b>Nh</b> nihonium [286]	114 <b>Fl</b> flerovium [290]	115 <b>Mc</b> moscovium [290]	116 <b>Lv</b> livermorium [293]	117 <b>Ts</b> tennessine [294]	118 <b>Og</b> oganesson [294]	

Key:
atomic number
Symbol
name
abridged standard
atomic weight



INTERNATIONAL UNION OF  
PURE AND APPLIED CHEMISTRY

For notes and updates to this table, see [www.iupac.org](http://www.iupac.org). This version is dated 4 May 2022.  
Copyright © 2022 IUPAC, the International Union of Pure and Applied Chemistry.

57 <b>La</b> lanthanum 138.91 ± 0.01	58 <b>Ce</b> cerium 140.12 ± 0.01	59 <b>Pr</b> praseodymium 140.91 ± 0.01	60 <b>Nd</b> neodymium 144.24 ± 0.01	61 <b>Pm</b> promethium [145]	62 <b>Sm</b> samarium 150.36 ± 0.02	63 <b>Eu</b> europium 151.96 ± 0.01	64 <b>Gd</b> gadolinium 157.25 ± 0.03	65 <b>Tb</b> terbium 158.93 ± 0.01	66 <b>Dy</b> dysprosium 162.50 ± 0.01	67 <b>Ho</b> holmium 164.93 ± 0.01	68 <b>Er</b> erbium 167.26 ± 0.01	69 <b>Tm</b> thulium 168.93 ± 0.01	70 <b>Yb</b> ytterbium 173.05 ± 0.02	71 <b>Lu</b> lutetium 174.967 ± 0.01
89 <b>Ac</b> actinium [227]	90 <b>Th</b> thorium 232.04 ± 0.01	91 <b>Pa</b> protactinium 231.04 ± 0.01	92 <b>U</b> uranium 238.03 ± 0.01	93 <b>Np</b> neptunium [237]	94 <b>Pu</b> plutonium [244]	95 <b>Am</b> americium [243]	96 <b>Cm</b> curium [247]	97 <b>Bk</b> berkelium [247]	98 <b>Cf</b> californium [251]	99 <b>Es</b> einsteinium [252]	100 <b>Fm</b> fermium [257]	101 <b>Md</b> mendelevium [258]	102 <b>No</b> nobelium [259]	103 <b>Lr</b> lawrencium [262]