3.3.3 Properties of Acetate and Triacetate

Shape	Can be modified as per requirement
Size	Thin long filament
Luster	Variation from brightness to dullness
Strength	Good
Elongation	Good up to 25%
Elastic recovery	Good
Resiliency	Low for acetate, but for triacetate it is good.
Dimensional stability	Good
Resistance to acids	Fair resistance to dilute acid, but cannot withstand concentrated acid.
Resistance to alkalis	Good resistance to dilute alkalis but cannot withstand concentrated alkalis.
Resistance to flame	Burns easily

3.3.4 Finishing Process

Depending upon the kind of yarns used and the final effect desired, different finishes can be given to acetate fabrics. The most common finishes are :

Embossing	For pattern or design
Heat setting	For crease and shape retention
Moireing	For permanent watermarking effect
Napping	On spun acetate for softness and warmth
Sizing	For better appearance
Water repellency	For resistance to water and rain
Wrinkle resistance	For better shape retention

3.3.5 Uses of Acetate

The uses of acetate are :

- The breathable nature of the fabric makes it suitable for use as a lining fabric for apparels.
- Acetate is used for making cigarette filters and other filters, ink reservoirs for fibre tip pens.
- It is used for making high absorbency products like diapers and surgical products.
- It is also used for making eyeglass frames.

3.4 NYLON

Nylon is a generic name given to a group of related compounds classified as Polyamides, just like cotton, linen and wool. Nylon is a long chain of linear concentrated polymer made from haxamethylene diamine and adipic acid. Nylon is the first synthetic fibre made in 1928 during a research at Dupont Company.

Nylon was invented by E.I.Du Pont de Nemours & Co. The credit of the discovery of the nylon goes to Dr.Wallace H. Carothers and his staff of organic chemists who worked in Du Pont's chemical department. Realizing that there is a need of more active program of research

TDD_Final_Chapter03.indd 27 21-02-2019 11.11.59 AM