There are different types of selvedges namely plain selvedge, tape selvedge, split selvedge, fringe selvedge, fused selvedge and adhesive finished selvedge (Figure 5.12).



Figure 5.12 Selvedges

5.3.2.2 Thread Count

The number of warp (ends) and weft (picks) per square inch of fabric is called thread count or fabric count. The higher the fabric count the more strong and more durable is the fabric. Fabric with higher thread count is more expensive and is denoted by X x Y. Example 30 x 50 thread count means 30 and 50 yarns in warp and weft direction for one inch. When the number of warp and weft yarns are almost equal the construction of fabric is called balanced and when the difference in warp or weft yarns is more than the other, it is called an unbalanced construction.

5.3.3 Factors Affecting the Durability of the Fabric

The durability of a fabric depends on various factors. The most common are listed below :

- The kind and quality of the fibre.
- The tensile strength of the yarn.
- The amount of twist in the yarn.
- The use of ply yarns as compared with singles.
- The use of uniform yarn rather than novelty yarns and
- The compactness of a fabric.

5.4 WEAVE STRUCTURES

The interlacing of warp and weft yarns to make woven structure is divided into different groups based upon the interlacing as basic weaves and fancy or surface figured weaves. Basic weaves are a group of weaves which are formed with interlacing of the yarns at right angles only to form a square pattern (Figure 5.13). Fancy weaves are weaves which form decorative patterns by the use of extra warp or weft yarns. Basic and fancy weaves are further classified based upon the type of interlacement and yarns used.




Figure 5.13 Weave Structure

TDD_Final_Chapter05.indd 45 21-02-2019 11.26.38 AM