Characteristics of Jack Wood

i. It is easy to work.


ii. It gives a good finish.


iii. Its weight after seasoning is 5950 N/m^3.



Uses: Used for plain furniture, boat construction, door and window panels, etc.

Inner parts of Timber







DO YOU KNOW?

The largest tree in India:

- The banyan tree (250 year-old) located in Acharya Jagadeesh Chandra Bose Indian botanic garden, Howrah near Kolkata.
- A 330 m long road was constructed around the tree to drive the visitors around the circumference of the tree. It covers 14500m^2 (3.5acres) area.





5.1.3 Defects in Timber

1. **Star Shakes**: These are the cracks which extend from bark towards the sapwood. These are wider at outside end and narrower at inside end. These are usually formed due to extreme heat or severe frost during the growth of the tree.

Civil_English_Unit_5.indd 106 12/21/2019 3:22:42 PM