5.2.2.2 Hydraulic Lime



It sets under water. There is small quantity of clay content and iron oxide. According to the quantity of clay content, it is classified in to three types. They are:

1. Feebly hydraulic lime
2. Moderately hydraulic lime
3. High quality hydraulic lime

Feebly hydraulic lime is having 5% to 10% clay. This content is easily soluble in water. It takes 21 days to set..

Moderately Hydraulic Lime is having 11% to 21% clay. This content takes two hours for dissolving. It takes one or two weeks to set.

High quality hydraulic lime is having 21% to 30% clay. This soil will not easily soluble. But set in one (or) two days.

5.2.3 I.S Classification of Lime

Indian Standard Institution classified lime into 5 classes. Class A, Class B, Class C, Class D and Class E.

Class A

It is an eminently hydraulic lime normally used for structural purposes. It is normally supplied as hydrated lime. This contains about 25% of clay. It is especially suitable for under water works.

Class B

Semi hydraulic lime is the name contains both hydraulic lime and fat lime. It contains about 15% of clay. It is supplied both as hydrated or quick lime. It is used for mortar and concrete.

Class C

It is predominantly fat lime used for finishing coat in plastering, white washing, etc., and with suitable admixtures such as surkhi (or) any other pozzolanic material to produce artificial hydraulic lime. It is supplied both quick lime and hydrated lime. This can set under water.

Class D

It is the lime containing substantial proportions of magnesium oxide and is similar to fat time. It is used for finishing coat in plastering, white washing, etc.

Class E

It is kankar lime generally used for masonry mortars and is supplied as hydrated lime.

ACTIVITY 3

Collect the lime sample and its rates in your town.

Civil_English_Unit_5.indd 116 12/21/2019 3:22:45 PM