9 DETERMINE THE FINENESS VALUE FOR THE GIVEN CEMENT SAMPLE

Aim

To find out the fineness value of the given sample of cement.

TJ9TN3

Materials and Apparatus Required

1. I.S. Sieve No. 9 (90 micron)
2. Weighing Balance
3. Trowel
4. Cement Sample (100 gms)

Procedure

1. 100 gms of cement is taken using weighing balance. Let it be 'W_1' gms.
2. The cement is placed in I.S. 90 micron sieve and the sieve is shaked for about 15 minutes.
3. The residue in the sieve is taken and weighed using weighing balance. Let it be 'W_2' gms.
4. The Fineness value of cement is worked out by using the formula.

$$\text{Fineness Value} = \frac{W_1 - W_2}{W_1} \times 100$$



I.S. Sieve no 9 (90 micron)

XI_Civil_Practical_English.indd 239 12/21/2019 5:50:41 PM