

Set of Sieves with Sieve Shaker

Note

The residue should not exceed 10% for ordinary Portland cement and 5% for rapid hardening cement.

Observation

Wt. of cement sample taken (W_1)=

Wt. of residue in the sieve (W_2) =

Fineness value $= \frac{W_1 - W_2}{W_1} \times 100$ =

=

Result

The Fineness value of the given cement sample is _____%

XI_Civil_Practical_English.indd 240 12/21/2019 5:50:42 PM