








According to general physical requirements bricks are classified into three categories. They are,

1) Class I
2) Class II
3) Class III

The bricks belongs to these three classification, differ in their general requirements and water absorption property.

As per IS classification, bricks are classified according to their compressive strength. They are 10, 7.5, 5.0 and 3.5 having compressive strength of 10 N/mm^2, 7.5 N/mm^2, 5 N/mm^2 and 3.5 N/mm^{2}respectively.



3.2.7 Properties of Good Bricks

- Good bricks should be of compact structure, free from cracks and flaws such as air bubbles, lumps and stones.
- They should be regular in shape and of uniform size with plane faces and sharp edges.
- Length should be equal to twice the width plus the thickness of mortar joints. (Length = (2 × Width) + thickness of mortar joints).
- The colour should be uniform and of deep red or copper colour.
- When soaked in water for 24 hours, a good brick should not absorb more than 20% of its own weight.
- A well burnt brick should be hard and when scratched with the finger nail, no impression should be formed.
- On striking it with each other, it should give a clear ringing or metallic sound.
- When struck against one another or thrown on end on a hard ground from a height of 1m, the bricks should not break.

Civil_English_Unit_3.indd 70 12/21/2019 2:26:06 PM