
be manufactured for minimum specified compressive strength of 3.5, 4.5, 5.5 and 7.0 N/mm^2 in 28 days.



B) **Grade B :** These are also used for load bearing walls. They may have a density below 1500 kg / m^3 but, not less than 1000 kg/m^3. They are made for specified compressive strength of 2.0, 3.0 and 5.0 N/mm^2 in 28 days.



C) **Grade C :** These are used for non-load bearing walls, and its density is not less than 1000 kg/m3. They are made for specified strength of 1.5 N/mm^3 in 28 days.



Civil_English_Unit_3.indd 72 12/21/2019 2:26:07 PM