11. Sulphate resisting cement

Hydrophobic Cement



Acidol, Napthalene soap, oxidised petroleum, etc., are used as the additional ingredients to decrease the wetting ability of cement grains. These substances form a thin film around cement grains. The fine pores in concrete are uniformly distributed. Thus frost and water resistance of the concrete are increased considerably.

Pozzolana Cement



DO YOU KNOW?

Portland cement was invented by an English man named 'Joseph Aspdin' in the year 1824 (19th century).



Pozzolana denotes volcanic powder. It is cheap, attains compressive strength with age, offers great resistance to expansion and possesses lighter tensile strength. It is used to prepare mass concrete of lean mix works and for laying concrete underwater.

Quick Setting Cement



Quick Setting cement is produced by adding a small percentage of aluminium sulphate to the ingredients of cement during

Civil_English_Unit_4.indd 81 12/21/2019 2:47:47 PM