The grades 43 and 53 in cement mainly corresponds to the average compressive strength attained after 28 days in mega Pascals (Mpa) of at least 3 mortar cubes (area of the face 50cm^2) composed of one part of cement with three parts of standard sand.

4.1.7 Storage of Cement



- Cement packed in bags should be stored in a place that it may not come into contact with water, moisture and even with moist air.
- Cement bags are stored in storage sheds on damp proof raised floors.



DO YOU KNOW?

Over two billion tons of cement is produced each year.

Ancient Chinese used cement to hold bamboo together in boats and in the Great Wall of China.

- The bags should be kept 60cm away from the walls.
- Not more than 10 bags should be stacked on one stock.
- Cement should not be stored for more than one year.
- In case of long storage for a period more than a year it should be covered with "tarpaulin" which renders water proof.



- If different brands of cement are stacked they should be stacked separately.
- For mass storage, cement should be stored in silos in loose form.



Silos

ACTIVITY 2

Visit any loose cement storage plant nearby your town and submit a report with photos.

Civil_English_Unit_4.indd 84 12/21/2019 2:47:48 PM