Comparison of Types of Magnetism (NOT FOR EXAMINATION)

Type of magnetism	Magnetising field is absent (H = 0)	Magnetising field is present ($H \neq 0$)	Magnetisation of the material	Susceptibility	Relative permeability
Diamagnetism	(Zero magnetic moment)	(Aligned opposite to the field)	M, O, H	Negative	Less than unity
Paramagnetism	(Net magnetic moment but random alignment)	(Aligned with the field)	M, O, H	Positive and small	Greater than unity
Ferromagnetism	(Net magnetic moment in a domain but they are randomly aligned)	(Aligned with the field)	M, O, H	Positive and large	Very large

3.6 HYSTERESIS

When a ferromagnetic material is kept in a magnetising field, the material gets magnetised by induction. An important characteristic of ferromagnetic material is that the variation of magnetic induction $\vec{B}$ with magnetising field $\vec{H}$ is not linear. It means that the ratio $\frac{B}{H} = \mu$ is not a constant. Let us study this behaviour in detail.

A ferromagnetic material (example, Iron) is magnetised slowly by a magnetising field $\vec{H}$. The magnetic induction $\vec{B}$ of the material increases from point A with the magnitude of the magnetising field and then attains a saturation level. This response of the material is depicted by the path AC as shown in Figure 3.23. Saturation magnetization is defined as the maximum point up to which the material can be magnetised by applying the magnetising field.




Figure 3.23 Hysteresis – plot for B vs H

UNIT-3(XII-Physics_Vol-1).indd 148 14-02-2020 20:03:25