ii. Properties:

Shape	:	Controlled by Manufactures.
Luster	:	Controlled from semi bright to dull
Elastic Recovery	:	Varies
Elongation	:	Varies by type
Resiliency	:	excellent
Density	:	1.38 g/cm
Moisture absorption	:	very low
Dimensional stability	:	Excellent
Resistance to acids	:	Strong acids destroy fibre, weak acids have little or no effect.
Alkalis	:	moderate
Sunlight	:	resistance is excellent
Insects	:	Excellent
To flame	:	will burn, but slowly and melting fibres tend to drop off, preventing further burning.

Uses:

- Polyester fibres have immediate consumer acceptance because of their easy-care and wrinkle-free properties.
- They require no ironing, easy to launder and quick to dry.
- Polyesters are not only used as apparel but also in industrial use items such as laundry bags, calendar sheeting, press covers, conveyor belts, fire hoses, fish netting, ropes and protective clothing.
- An important use of polyester is for surgical implants.

ACTIVITY 3

Obtain a total of ten advertisement and labels identifying ten different polyester trademarks used in apparel, home furnishings, automobiles tires, and industrial fabrics and list the characteristics or properties of the fibre as advertised.



Polyester

ACTIVITY 4

Collect pictures and samples of man-madefibres.

4.3 Simple Test For Fibre Identification

The burning test can be used to identify the group-cellouse protein, minerals etc., to which the fibres belong. General direction for the burning test.

i. Ravel out and test several yarns from each side of the fabric to see if they have the same fibre content. Difference in lustre twist and colour will indicate that there might be two or more kinds of fibre in the fabric.

XII Std - Home Science EM_Unit 4.indd 102 20-04-2020 6.44.13 PM