blanket and the heated cylinder. Friction between the rubber blanket and steel drum force adjacent yarns to move closer together until the unit length of fabric become equal to the unit length of rubber blanket it rests on. Heat is created by constantly stretching and relaxing the rubber blanket. The blanket is cooled by spraying water on it after the fabric exits from the unit.



Figure 1.17 Compacting / Sanforizing Machine

The degree of shrinkage can be controlled by the thickness of the blanket. The thicker the blanket, the greater is the stretched length at the bend. A longer length of fabric will be fed into the compactor causing the degree of compacting to be greater. To be effective, the degree of compacting needed should be predetermined ahead of time. This is done by characterizing the shrinking behaviour of the fabric by laundering. The degree of compacting should not exceed the degree of shrinking otherwise over compacting will cause the fabric to "grow" when relaxed.

1.3.20 Soil Release Finish

Textile materials are attracted to dirt or soil. Development of static charge electricity to hydrophobic textiles makes them prone to soiling. This is not readily removed during laundering and gets re-deposited on the fabric. Also, the hydrophobic materials are not wetted properly during laundering which causes problem with staining.



Figure 1.18 Soiling of Fabrics

Soil release finish is one of the functional finishes which work by making the textile fibres more absorbent or hydrophilic. The hydrophilic finishes increase the wet ability of the fibre and facilitate soil release during washing. It also prevents soil re-deposition on the fabric. It also reduces the static charge on the cloth by maintaining moisture on the fabric surface which is mostly observed in polyester fabrics. They also improve the antistatic properties, fabric drapability and comfort.

1.3.21 Wrinkle Resistant or Crease Resistant Finish

The ability of the fabric to resist the formation of crease or wrinkle when slightly squeezed is known as 'crease resistance' of the fabric. The ability of a fabric to recover from a definite degree from creasing is called crease recovery. Finishes to reduce the undue wrinkles on fabric or garments is called as wrinkle resistance finish. Cotton, rayon and flax are more susceptible to wrinkles due to the hydrogen bonds of the cellulosic molecules in their amorphous region. Due to application of heat or moisture, the hydrogen bond breaks and new

XII TDD_English version CHAPTER 01.indd 15 1/13/2020 2:41:00 PM