hydrogen bond occurs at new dimensions. Therefore wrinkling can be reduced if the hydrogen bond formation is less. Resins such as Formaldehyde, DMU (Di-methylol urea), DMEU (Di-methylol ethylene urea), DMDHEU (Di-methylol di-hydroxyl ethyleneurea), and Modified DMDHEU (Di-methylol di-hydroxylethylene urea) are mainly used for imparting wrinkle resistance finish to a fabric.



Figure 1.19 Fabric with Crease Resistant Finish

POINTS TO REMEMBER

- Scouring and Bleaching are done prior to other finishes, as they improve the property of raw fabric for further processing.
- The wax and non saponifiable oils present in fabrics are removed by emulsification.
- Bleach is a chemical that removes colour or whitens a fabric via oxidation or reduction method.
- Bleaching treatment is given to decolourize the natural colouring matter present in the cotton fabrics and impart a pure white colour.
- Calendaring is a mechanical process that finishes the fabric by passing them between a series of rollers and applying heat and pressure.
- Calendared fabrics with their glossy or wet look are produced in the same manner as glazing.
- Embossing is a process that alters the surface of the fabric by providing a three dimensional or raised effect on selected areas.
- Stiffening agents are applied to the cloth to increase the weight of the fabric, to improve its thickness and its lustre.

ACTIVITIES FOR TEACHER

- To show different types of finishes
- To arrange a factory visit to finishing units

ACTIVITIES FOR STUDENTS

- Prepare an assignment regarding various types of finishes
- To ask the students to do a finishing process on the sample given to them.

XII TDD_English version CHAPTER 01.indd 16 1/13/2020 2:41:00 PM